



**MOMENTIVE**  
performance materials

# FRV138

## soft fluorosilicone encapsulant

### Product Description

FRV138 is a flowable, two-component fluorosilicone encapsulant that cures to a soft, flexible silicone rubber.

FRV138 encapsulant, which has the consistency of a firm gel, is an ideal candidate to consider for use in applications where resistance to the swelling effects of fuels, oils, solvents and other chemicals is needed. The flowable consistency of this product allows it to be applied in parts where small or deep crevices need to be filled. FRV138 encapsulant is easily dispensed via manual or automated dispense equipment. Typical applications include, but are not limited to, potting and encapsulation of sensors and other electronic circuit assemblies.

### Key Features and Typical Benefits

---

- Chemical Resistance: Resists swelling by hydrocarbon solvents, dimethyl silicone fluids and fuels
- Primerless Adhesion: Adheres to many substrates
- Low Temperature Cure: 90°C for approximately 1 hour
- Broad Temperature Range: Retains elastomeric properties at temperatures of -40°C to 150°C
- Ozone Resistant: High quality weatherability
- Electrical Insulation: Excellent properties

---

Momentive Performance Materials provides versatile materials as the starting point for our creative approach to ideas that help enable new developments across hundreds of industrial and consumer applications. We are helping customers

solve product, process, and performance problems; our silanes, fluids, elastomers, sealants, resins, adhesives, urethane additives, and other specialty products are delivering innovation in everything from car engines to biomedical devices.

From helping to develop safer tires and keeping electronics cooler, to improving the feel of lipstick and ensuring the reliability of adhesives, our technologies and enabling solutions are at the frontline of innovation.

# FRV138 soft fluorosilicone encapsulant

## Typical Physical Properties

### UNCURED PROPERTIES

Appearance	Translucent flowable liquid
Pot life [hr]	> 8
Cure Time at 90°C [hr]	1
Viscosity, Part A at 25°C [cSt]	11500
Viscosity, Part B at 25°C [cSt]	8000
Mix Ratio (by weight or volume)	1:1

### CURED PROPERTIES<sup>(1)</sup>

Specific Gravity (25°C)	1.3
Hardness - Shore 00	55
Tensile Strength [psi]	44
Elongation [%]	73
Storage Modulus, G' (25°C) [psi]	6
CTE <sup>(2)</sup> [ppm/°C]	630
a <sub>1</sub> , a <sub>2</sub> [ppm/°C]	-20, 870
Glass Transition [°C]	-45

### Electrical Properties

Dielectric Constant	7.2
Volume Resistivity (Ohm·cm)	1.6 x 10 <sup>10</sup>

### Chemical Resistance<sup>(3)</sup> Swell %

ASTM Oil #1	0.2
Synthetic Motor Oil	0.5
Automatic Transmission Fluid	1.1
JP-8 Jet Fuel (25°C)	4.8

(1) Cured for 1 hour at 150°C

(2) Measured by TMA from -35°C to 170°C

(3) Properties obtained after 70-hour immersion at 150°C except as noted.

Information is provided for customer convenience. These properties are not tested on a routine basis.

## Instructions for Use

### Compatibility

FRV138 silicone encapsulant will cure in contact with most clean and dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap can cause cure inhibition. Cure inhibition is characterized by a lack of cure of the silicone rubber at the interface between it and the substrate. Compatibility tests should be performed on all materials in contact with silicone rubber, including painted surfaces, to ensure adequate cure. It is recommended that a sample patch test be performed with the silicone adhesive to determine if a barrier coating or other inhibition-preventing measures are necessary before using the material.

### Mixing

When hand mixing, select a mixing container 4-5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out equal amounts of parts A and B. With clean tools, thoroughly mix the two components, scraping the sides and bottom of the container carefully to produce a homogenous mixture. When using power mixers, avoid excessive speeds, which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

### De-Aeration

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of about 29 inches (25mm) of mercury. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. Automatic equipment designed to meter, mix, de-aerate, and dispense two component silicone rubber products will add convenience to continuous or large volume operations.

### Curing

FRV138 is designed to be thermally (heat) cured and will cure sufficiently in approximately 1 hour at 90°C. Cure times may be affected by many variables including but not limited to thickness of specimen, temperature used, oven type, oven loading, and the equipment used. For more detailed information on curing properties, contact Momentive Performance Materials at 800.295.2392.

### Equipment

Pumping and meter-mixing systems for two part silicones are available from a number of manufacturers, most of whom will provide a complete integrated system. Contact Momentive Performance Materials for further information.

### Surface Preparation

FRV138 silicone encapsulant will bond to many surfaces without the aid of a primer. Surfaces should be thoroughly cleaned with a suitable solvent to remove dirt, oil, grease and other contaminants. Particular attention should be paid to those areas that will come in direct contact with the adhesive during the curing process.

### Bonding

For best adhesion, surfaces to be bonded should be thoroughly cleaned and dry. If a solvent is used to clean the substrates prior to use, steps must be taken to ensure the solvent has completely evaporated prior to application of the silicone rubber compound. For difficult-to-bond-to substrates or where more aggressive chemical adhesion is desired, a Momentive Performance Materials silicone primer may be used. For more details on priming and adhesion, please refer to the Momentive Performance Materials product data sheet on silicone primers.

# FRV138 soft fluorosilicone encapsulant

## Patent Status

Protected by one or more pending US and foreign patent applications.

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

## Emergency Service

---

Momentive Performance Materials maintains an around-the-clock emergency service for its products. The American Chemistry Council (CHEMTREC), Transport Canada (CANUTEC), and the Chemical Emergency Agency Service also maintain an around-the-clock emergency service for all chemical products:

Location	Momentive Performance Materials Products	All Chemical Products
Mainland U.S., Puerto Rico	518.233.2500	CHEMTREC: 800.424.9300
Alaska, Hawaii	518.233.2500	CHEMTREC: 800.424.9300
Canada	518.233.2500	CANUTEC: 613.996.6666 (collect) or CHEMTREC: 800.424.9300
Europe, Middle East, Africa	+32.(0)14.58.45.45 (Belgium)	CHEMTREC: +1-703.527.3887 (collect)
Latin America, Asia/Pacific, all other locations worldwide	+518.233.2500	CHEMTREC: +1-703.527.3887 (collect)
At sea	Radio U.S. Coast Guard, which can directly contact Momentive Performance Materials at 518.233.2500 or CHEMTREC at 800.424.9300.	

---

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

# Principal Locations

Regional Information	Phone	Fax
<b>North America</b>		
World Headquarters 187 Danbury Road Wilton, CT 06897, USA	800.295.2392	607.754.7517
<b>Latin America</b>		
Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700 Brazil	+ 55.11.4534.9650	+ 55.11.4534.9660
<b>Europe, Middle East, Africa and India</b>		
Leverkusen Germany	00.800.4321.1000 + 31.164.293.276	+ 31.164.241750
<b>Pacific</b>		
Akasaka Park Building 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan	+ 81.3.5544.3100	+ 81.3.5544.3101
<b>Customer Service Centers</b>		
<b>North America</b>		
Charleston, WV 25314, USA E-mail: <a href="mailto:cs-na.silicones@momentive.com">cs-na.silicones@momentive.com</a>	<b>Specialty Fluids</b> 800.523.5862	304.746.1654
	<b>UA, Silanes, Resins, and Specialties</b> 800.334.4674	304.746.1623
	<b>RTV Products-Elastomers</b> 800.332.3390	304.746.1623
	<b>Sealants and Adhesives and Construction</b> 877.943.7325	304.746.1654
<b>Latin America</b>		
Argentina and Chile	+ 54.11.4862.9544	+ 54.11.4862.9544
Brazil	+ 55.11.4534.9650	+ 55.11.4534.9660
Mexico and Central America	+ 52.55.5899.5135	+ 52.55.5899.5138
Venezuela, Ecuador, Peru, Colombia, and Caribbean	+ 58.212.285.2149	+ 58.212.285.2149
E-mail: <a href="mailto:cs-la.silicones@momentive.com">cs-la.silicones@momentive.com</a>		
<b>Europe, Middle East, Africa and India</b>		
E-mail: <a href="mailto:cs-eur.silicones@momentive.com">cs-eur.silicones@momentive.com</a>	00.800.4321.1000 + 31.164.293.276	+ 31.164.241750
<b>Pacific</b>		
E-mail: <a href="mailto:cs-ap.silicones@momentive.com">cs-ap.silicones@momentive.com</a>		
Japan	+ 81.276.20.6182	
China	+ 86.21.5050.4666 (ext. 1523)	
Korea	+ 82.2.6201.4600	
Singapore	+ 65.6220.7022	
<b>Worldwide Hotline</b>	<b>800.295.2392</b>	<b>+ 607.786.8131</b>
<b>Worldwide Web</b>		<b>+ 607.786.8309</b>
	<b><a href="http://www.momentive.com">www.momentive.com</a></b>	

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.