

SagTex™ PHD

SagTex* PHD

Description

SagTex PhD silicone foam control agent is a high-performance antifoam emulsion designed for multiple uses in the textile industry. The product typically offers very good initial foam knockdown and excellent durability at concentrations less than half that of competitive silicone antifoams. Additionally, SagTex PhD silicone antifoam gives a homogeneous dilution in water or bath formulations with no oiling or agglomerates.

Key Features and Benefits

- Long durability in acidic or alkaline conditions
- Outstanding durability at low add-on levels
- Effective performance at significantly lower use levels than competitive antifoams
- Excellent foam control at ambient and elevated temperatures
- Rapid foam knockdown
- No oily spots or agglomerates when diluted with water
- Easily dispersed in hard water

Typical Physical Properties

Appearance	Milky white liquid
Active Content, %	45
Viscosity 25°C (77°F) (Brookfield LVT No. 3, 30 RPM), cP	1500-2500
Emulsifier Type	O/W, non-ionic
Specific Gravity at 25/25°C (77°F)	1.0
pH	8

Product Usage

SagTex PhD silicone foam control agent is a medium viscosity emulsion that can be

easily transferred from its original package using piston pumps. Centrifugal pumps are not recommended, as they risk destabilizing, and in extreme cases, separating the emulsion. In low viscosity formulations, preliminary stability and compatibility studies must be conducted prior to formulation design.

For process application, we recommend prediluting SagTex PhD silicone foam control agent with cold water (less than 18°C) in a ratio of 1:1 to 1:20. If the diluted SagTex PhD emulsion will be stored before use, then care must be taken to ensure stability of the dilution. Stability can be extended by adding small amounts of a suitable thickening agent, such as xanthan gum or polyacrylates, to the diluting water. Commercial biocides containing 2-Methyl-4 Isothiazolin-3 one and/or 2-Bromo-2-nitro-1,3-propanediol are very effective in this type of product.


A suggested starting concentration is typically between 0.1 and 2 percent, but this will vary depending on the severity of the foaming problem.

Processing Recommendations

Shake Test

Glass bottles containing a blend of a one percent octylphenol ethoxylate solution and the antifoams were shaken using a laboratory wrist action shaker at ambient temperature. Four shakes were carried out; each one lasting longer. At the end of each shake, the amount of time it took for the foam to collapse (clear break) was recorded. Figure 1 shows these results. Note that SagTex PhD silicone foam control agent was quicker at controlling foam and showed excellent durability at half the concentration of the competitive material.

Figure 1: Faster Break Time – Shake Test with One Percent Octylphenol Ethoxylate Solution at Ambient Temperature




Recirculation Tests

The following test compares antifoams under dynamic conditions. Two hundred and fifty milliliters of a one percent octylphenol ethoxylate solution is recirculated through a glass cell using a centrifugal pump. As soon as the foam height reaches twenty-four centimeters, the antifoam is injected into the solution without stopping the recirculation. The foam height versus time is recorded.

In this test, SagTex PhD silicone foam control agent showed excellent durability and equivalent foam knockdown compared to the competitive material at half the concentration.

Figure 2: Recirculation Test with One Percent Octylphenol Ethoxylate Solution



Patent Status

Standard copy to come

Product Safety, Handling and Storage

Standard copy to come

Limitations

Standard copy to come

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392

Toll free*

+704 805 6946

Direct Number

Latin America

Brazil

+55 11 4534 9650

Direct Number

EMEAI- Europe, Middle East, Africa & India

Europe

+390510924300

Direct number

ASIA PACIFIC

China

800 820 0202

Toll free

+86 21 3860 4892

Direct number

All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product,

service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SagTex™ ist ein Markenname der Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.