

## **SilFORT™ MHC2700 Clearcoat**

### **Description**

SilFORT MHC2700 Clearcoat is a thermally cured siloxane-based primerless hardcoat system used to protect glossy, matte, and colored anodized aluminum substrates against corrosion, chemicals and scratches. It offers excellent acid and alkali resistance in the range of pH 1.0 to 13.5, while maintaining the desired appearance of the substrate.

This direct-to-metal sol-gel coating system can generally be applied by either spray, dip, or flow coating, allowing for greater design freedom. Curvatures, radii and orifices can typically be managed in the coating process without making any design compromises. For brushed or matte surfaces, the gloss-level can be adjusted according to the desired optical appearance and structure of the surface by the incorporation of Momentive's SilFORT MHC Matte additive.

### **Key Features and Typical Benefits**

- Direct-to-metal / primerless adhesion to anodized aluminum
- Exceptional pH resistance (pH 1.0 to >13.5)
- Excellent corrosion resistance
- Excellent scratch resistance
- Excellent chemical resistance
- Wide application window

### Typical Physical Properties

| Property <sup>(1)</sup>      | Unit              | SiIFORT MHC2700 Clearcoat |
|------------------------------|-------------------|---------------------------|
| Physical Form                | -                 | Liquid                    |
| Color                        | -                 | Milky white               |
| Solids Content               | %                 | Approx. 25                |
| Density (@ 25°C)             | g/cm <sup>3</sup> | 0.93                      |
| Kinematic Viscosity (@ 25°C) | cSt               | Approx. 5.5               |
| pH                           | -                 | Approx. 5                 |
| Shelf Life <sup>(2)</sup>    | Days              | 180 (stored below 10°C)   |

1. As supplied. Typical properties are average data and are not to be used as or to develop specifications.

2. From date of manufacture.

### Potential Applications

- Exterior automotive parts made from anodized aluminum (e.g. window trim, roof rails)
- Interior automotive parts made from anodized aluminum
- Glossy, matte or colored substrates

### General Considerations for Use

|  | SiIFORT MHC2700 Clearcoat                             |
|--|---|
| Application Method                           | Spray, flow, dip                                      |
| Reducing Solvents <sup>(3)</sup>             | 1-Butanol (CAS# 71-36-3)<br>2-Propanol (CAS# 67-63-0) |
| Recommended Coating Thickness <sup>(4)</sup> | 4 – 6 µm  |

3. If necessary for application process, other suitable solvents may be considered.

4. Other thicknesses can be considered but may affect performance.

SiIFORT MHC2700 Clearcoat is a cross-linking product, sensitive to extended exposure to elevated temperature. Storage at lower temperatures (< 0°C) may increase typical shelf-life beyond 3 months.

Once the product has reached ambient temperature it should be used within 7 days. Re-refrigeration to less than 10°C should be considered when product will not be used within 24 hours.

For a particle-free surface, components should be processed in a climate-controlled

cleanroom environment that complies with ISO14664-1, equal to or lower than class 6. Before applying any coating, part surface temperature should be <35°C.

For more detailed guidance on the use of SilFORT MHC2700 Clearcoat, please request the accompanying Processing Guide from your local Momentive representative.

### **Packaging**

Products are currently available in:

- 25 kg Steel Pail with PE liner
- Other packaging sizes available upon request

### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### **Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

| <b>Americas</b>               | <b>Latin America</b>                               | <b>EMEAI- Europe, Middle East, Africa &amp; India</b>                        | <b>ASIA PACIFIC</b>  |
|-------------------------------|--|--|--|
| +1 800 295 2392<br>Toll free* | <b>Brazil</b><br>+55 11 4534 9650<br>Direct Number | <b>Europe</b><br>+390510924300<br>Direct number                              | <b>China</b><br>800 820 0202<br>Toll free<br>+86 21 3860 4892<br>Direct number |
| *All American countries       | <b>Mexico</b><br>+52 55 2169 7670<br>Direct Number | <b>India, Middle East &amp; Africa</b><br>+ 91 44 71212207<br>Direct number* | <b>Japan</b><br>+81 3 5544 3111<br>Direct number                               |
|                               |  | <b>*All Middle Eastern countries, Africa, India,</b>                         | <b>Korea</b><br>+82 2 6201 4600  |

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS

**PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SiIFORT™ ist ein Markenname der Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.