

SILQUEST* A-137 silane

SILANES - COATINGS ADDITIVES



Silquest A-137 silane is a monomeric alkylalkoxysilane that, when exposed to moisture, is reactive with the minerals contained in concrete, masonry and other substrates. The monomer can penetrate deeply into a substrate, and then react to form a protective surface surrounding each microscopic particle. This protective surface is extremely durable and leads to significant improvements in weather resistance. The silane is easily dissolved in organic solvents to form clear, colorless, stable solutions.

Key Features and Typical Benefits

High-Performance Penetrating Sealers

Premium-grade penetrating sealers are easily formulated by blending 10 to 40 percent Silquest A-137 silane in alcohols or organic solvents. Penetrating sealers formulated with this product can exceed the most stringent test requirements specified for traffic-bearing surfaces by government and parking structure designers when tested in accordance with:

- NCHRP-244 Series II and III
- NCHRP-244 Series IV Southern Climate Exposure
- ASTM C-672 Deicer Scaling
- AASHTO T-259/260 Salt Ponding.

Long-Lasting Wear Protection

Water repellency that lasts for years on surfaces of highway bridge decks has been documented with alkylalkoxysilanes. Reinforced concrete structures can be protected from water and waterborne salt that normally cause corrosion of reinforcing steel, deterioration and weathering. Normal abrasion resistance, surface appearance and most other desirable properties remain unchanged with Silquest A-137 silane.

Breathable, Stain-Resistant Surfaces

Water-repellent surfaces created by the use of formulations containing this silane retain normal vapor transmission. Reduced efflorescence and staining are provided with the deep-penetrating solutions of Silquest A-137 silane.

Typical Physical Properties

Physical Form	Water-white to straw-colored liquid
Active Material Content, % min	95
Viscosity at 25°C, cSt	2.1
Useful Storage Life, months	12
Diluents	Aromatic or aliphatic hydrocarbons, alcohols, mineral spirits
Flash Point, PMCC, °C (°F)	82 (180)
Specific Gravity	0.88
Color, Pt/Co	100

SILQUEST* A-137 Silane

Potential Applications

Penetrating sealers containing Silquest A-137 silane can provide excellent protection for bricks, stone, masonry, wood and other substrates. Surfaces can be put into service within a few minutes. The performance of many existing water-repellent, sealer, stain and coating formulations can also be enhanced by the addition of Silquest A-137 silane and/or other Silquest silanes.

The dispersibility and compatibility of filler and pigment particles in coating and sealant formulations can be improved by adding Silquest A-137 silane to the coating formulation, or by using it as a pre-treatment for the pigments. The particulate surface is made more hydrophobic and organic-like. Consequently, it becomes more compatible with typical coating, adhesive and sealant vehicles.

Industry Standards

Penetrating sealers based on Silquest A-137 silane have been approved for use on highways and bridges; parking structures; runways and airports; water ways; cooling towers; and marine, offshore, and coastal structures exposed to salt spray. The table below shows test results obtained with Silquest A-137 silane formulations that exceed NCHRP-244 test requirements often specified by government and parking structure designers.

NCHRP-244 Series II Test Results⁽¹⁾

	20% Silquest A-137 Silane	
	In Mineral Spirits	In Isopropanol
Weight-gain Reduction, %	>80	>84
Chloride Ion Reduction, %	>82	>86
Average Depth of Penetration, in	0.12 to 0.20	0.12 to 0.20

(1) Test results presented are only to be used as indicators of whether a product met, or did not meet, certain performance criteria. The results do not constitute a representation or warranty as to the safety or efficacy of a product or its fitness for a particular purpose or use.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.momentive.com or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

SILQUEST* A-137 Silane

Emergency Service

Momentive Performance Materials maintains an around-the-clock emergency service for its products. The American Chemistry Council (CHEMTREC) and CareChem24 International also maintain an around-the-clock emergency service for all chemical products:

<u>Location</u>	<u>Momentive Performance Materials Products</u>	<u>All Chemical Products</u>
Mainland U.S., Puerto Rico	518.233.2500	CHEMTREC: 800.424.9300
Alaska, Hawaii	518.233.2500	CHEMTREC: 800.424.9300
Canada	518.233.2500	CHEMTREC: 800.424.9300
Europe	+518.233.2500 (Albanian, Czech, Danish, Dutch, English, Finnish, French, German, Greek, Hungarian, Italian, Lithuanian, Norwegian, Polish, Portuguese, Romanian, Russian, Serbo-Croatian, Slovak, Spanish, Swedish, Turkish, Ukrainian)	+44.(0)208.762.8322 (UK)
Middle East, All countries, except Israel	+518.233.2500	+961.3.487.287 (Lebanon)
Middle East, Israel	+518.233.2500	+44.(0)208.762.8322 (UK)
Latin America, Asia/Pacific, all other locations worldwide	+518.233.2500	CHEMTREC: +1-703.527.3887 (collect)
At sea	Radio U.S. Coast Guard, which can directly contact Momentive Performance Materials at 518.233.2500 or CHEMTREC at 800.424.9300.	

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

CUSTOMER SERVICE CENTERS

North America	E cs-na.silicones@momentive.com		
	• Specialty Fluids	T +1.800.523.5862	F +1.304.746.1654
	• UA, Silanes and Specialty Coatings	T +1.800.334.4674	F +1.304.746.1623
	• RTVs and Elastomers	T +1.800.332.3390	F +1.304.746.1623
	• Consumer Sealants & Construction Sealants and Adhesives	T +1.877.943.7325	F +1.304.746.1654
Latin America	E cs-la.silicones@momentive.com		
	• Argentina & Chile	T +54.11.4862.9544	F +54.11.4862.9544
	• Brazil	T +55.11.4534.9650	F +55.11.4534.9660
	• Mexico & Central America	T +52.55.2169.7670	F +52.55.2169.7699
	• Venezuela, Ecuador, Peru, Colombia & Caribbean	T +58.212.285.2149	F +58.212.285.2149
Europe, Middle East, Africa and India	E cs-eur.silicones@momentive.com	T +00.800.4321.1000	
		T +40.21.3111848	
Pacific	E cs-ap.silicones@momentive.com		
	• China	T +1.800.820.0202 or T +86.21.3860.4892	F +86.21.5079.3725
	• Japan	T +0120.975.400 or T +81.276.20.6182	F +81.276.31.6259
	• Korea	T +82.2.6201.4600	F +82.2.6201.4601
	• Malaysia	T +60.3.9206.1532	F +60.3.9206.1533
	• Thailand	T +662.207.3456	F +66.2207.3488
Worldwide Hotline		T +1.607.786.8131	F +1.607.786.8309
		T +1.800.295.2392	

Visit us at Momentive.com



Momentive Performance Materials
22 Corporate Woods Boulevard
Albany, NY 12211

*Silquest is a trademark of Momentive Performance Materials Inc.
Momentive is a trademark of Momentive Performance Materials Holdings LLC.
Copyright 2003-2011 Momentive Performance Materials Inc. All rights reserved.

MOM-113-007-50E-GL 03/11 Printed in U.S.A.

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.