

SILQUEST* A-1120 and SILQUEST A-2120 silanes

SILANES - ADHESIVES & SEALANTS ADDITIVES



Silquest A-1120, N(beta-aminoethyl) gamma-aminopropyltrimethoxy-silane, and Silquest A-2120, N(beta-aminoethyl) gamma-aminopropylmethyldimethoxy-silane, are diaminofunctional silanes that may be used over a broad range of applications. They are used to promote the adhesion of amino-reactive resins such as silicone, silylated polyurethane, two-part urethanes and two-part epoxies to inorganic surfaces, plastic surfaces, and inorganic fillers or reinforcements.

Silquest A-1120 and Silquest A-2120 silanes find uses as:

- adhesion promoters in polysulfide, polyvinyl chloride plastisol, silicone two-part urethanes and epoxy adhesives and sealants
- additives in phenolic and epoxy molding compounds
- additives to latex coatings, adhesives and sealants
- adhesion promoters in one-part silylated urethane adhesives and sealants based on the Momentive Performance Materials SPUR+ prepolymer technology.

Key Features and Typical Benefits

Feature	Benefit
Polyamino Functionality	<ul style="list-style-type: none"> ■ Provides reactive site for amino-reactive resins ■ Good wetting of substrates
Silquest A-1120 Trifunctional Silane	<ul style="list-style-type: none"> ■ Excellent adhesion to inorganic substrates such as metal, glass, etc ■ Superior adhesion to plastics when employed in SPUR+* prepolymer technology-based adhesives or sealants
Silquest A-2120 Difunctional Silane	<ul style="list-style-type: none"> ■ Excellent adhesion to inorganic substrates such as metal, glass, etc ■ Superior adhesion to plastics when employed in SPUR+ Technology-based adhesives or sealants ■ Provides as much as a 35% improvement in elongation over Silquest A-1120 silane ■ Provides superior stability in waterborne systems over other trifunctional amino silanes

Typical Physical Properties


	Silquest A-1120 Silane	Silquest A-2120 Silane
Physical Form	Straw-colored liquid	Straw-colored liquid
Specific Gravity, 25/25°C	1.03	0.98
Refractive Index, n _D 25°C	1.448	-
Flash Point, Pensky-Martens Closed Cup ⁽¹⁾ , °C (°F)	138 (280)	>93 (>200)

(1) ASTM Method D93


SILQUEST* A-1120 silane and SILQUEST A-2120 silane

Chemical Structure

Silquest A-1120 Silane



Silquest A-2120 Silane



Potential Applications

Silquest A-1120 silane and Silquest A-2120 silane may be used as additives, helping to eliminate the need for special primers in numerous bonding applications. Specific systems that demonstrate improved adhesion when Silquest A-1120 silane or Silquest A-2120 silane are used include:

RTV Silicones and Hybrid Silane-Crosslinked Sealants

Silquest A-1120 silane or Silquest A-2120 silane addition to one- and two-part silicone-crosslinked sealants improves adhesion to a variety of substrates, including glass, steel, aluminum and concrete. These silanes can dramatically enhance adhesion to a wide array of plastics when used in combination with the Momentive Performance Materials SPUR+™ Technology for silylating urethane polymers. (For formulation and silylated prepolymer preparation information, please refer to Literature Bulletin 112-026-30, “Silquest Organofunctional Silanes – Crosslinkers and Adhesion Promoters for Urethane Adhesives and Sealants”. This bulletin may be obtained from the Momentive Performance Materials sales office nearest you.)

Silquest A-2120 silane, a difunctional variant of Silquest A-1120 silane, can be utilized to provide an enhanced adhesion performance and as much as a 35% increase elongation performance.

Loading levels of 0.5 to 2.0 percent by weight are typically recommended for both products.

The performance of Silquest A-1120 silane in a one-part SPUR+ prepolymer-based sealant is shown in the following table. Similar results would be anticipated using Silquest A-2120 silane.

Table 1: Adhesion-in-Peel⁽¹⁾ Performance of One-Part SPUR+ Sealant Using Silquest A-1120 and Silquest A-2120 Silane⁽²⁾

Substrate	Peel Strength, pli ⁽³⁾ (Failure Mode)	
	Silquest A-1120 Silane	Silquest A-2120 Silane
Aluminum	21 (100% C ⁽⁴⁾)	20 (100% C)
Glass	23 (100% C)	23 (100% C)
PVC	23 (100% C)	21 (100% C)
ABS	20 (75% C)	25 (100% C)
Polystyrene	23 (100% C)	3 (<75% C)

(1) ASTM Method C-794

(2) 1.5 weight percent silane

(3) Pounds per linear inch

(4) Cohesive failure of the bond

Potential Applications (continued)

Polysulfide Sealants

When added to one- and two-part polysulfide sealants, Silquest A-1120 silane and A-2120 silane provide better adhesion to a variety of substrates, including glass, aluminum and steel. Silquest A-1120 silane and A-2120 silane are typically used at a loading of 0.5 to 1.0 percent by weight to the sealant. They disperse well and produce cohesive failure in the sealant rather than adhesive failure of the bond between the sealant and the substrate.

Furthermore, the use of Silquest A-1120 silane or A-2120 silane can eliminate the need for primers normally required to achieve adhesion to surfaces.

Plastisol Sealants

Adding Silquest A-1120 silane (0.5 to 1.5 weight percent) as a replacement for polyaminoamide adhesion promoters in plastisol sealants improves bonding to metal substrates.

Silquest A-1120 silane-modified plastisol systems have a very light color, and the cured compound is bubble-free.

Additive in Phenolic and Epoxy Molding Compounds

Silquest A-1120 silane, as an additive in phenolic and epoxy molding compounds, reduces the water absorption of molded composites. This, in turn, leads to improved wet electrical properties, particularly at low frequencies. High-temperature strength properties are also improved.

*Silquest and SPUR+ are trademarks of Momentive Performance Materials Inc.

SILQUEST* A-1120 silane and SILQUEST A-2120 silane

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.momentive.com or, upon request, from any Momentive Performance Materials representative. Use of other materials in conjunction with Momentive Performance Materials products may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Emergency Service

Momentive Performance Materials maintains an around-the-clock emergency service for its products.

<u>Location</u>	<u>Emergency Service Provider</u>	<u>Emergency Contact Number</u>
Mainland U.S., Puerto Rico	CHEMTREC	1-800-424-9300
Alaska, Hawaii	CHEMTREC	1-800-424-9300
Canada	CHEMTREC	1-800-424-9300
Europe, Israel	NCEC	+44 (0) 1235239670
Middle East	NCEC	+44 (0) 1235239671
Asia Pacific (except China)	NCEC	+44 (0) 1235239670
China	NCEC	+86-10-5100-3039
Latin America (except Brazil)	NCEC	+44 (0) 1235239670
Brazil	SOS Cotec	08000111767 or 08007071767
All other locations world wide	NCEC	+44 (0) 1235239670
At sea	Radio U.S. Coast Guard in U.S. waters NCEC in International waters	+44 (0) 1235239670

For Health related calls, contact Momentive Performance Materials at +1-518-233-2500 (English only).

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

Customer Service Centers

Worldwide Hotline

T +1 800 295 2392 / +1 607 786 8131
F +1 607 786 8309

North America

cs-na.silicones@momentive.com

Silicones – Fluids, Urethane Additives, Silanes, Specialty Coatings, RTVs and Elastomers

T +1 800 523 5862 / +1 800 334 4674
F +1 304 746 1654 / +1 304 746 1623

Consumer Sealants/ Construction Sealants and Adhesives

T +1 877 943 7325
F +1 304 746 1654

Latin America

cs-la.silicones@momentive.com

South America

T +55 11 4534 9650
F +55 11 4534 9660

Mexico and Central America

T +52 55 2169 7670
F +52 55 2169 7699

Europe, Middle East, Africa and India

cs-eur.silicones@momentive.com

T +00 800 4321 1000 / +40 21 3111848

Pacific

cs-ap.silicones@momentive.com

China

T +800 820 0202 / +86 21 3860 4892

Japan

T +0120 975 400 / +81 276 20 6182
F +81 276 31 6259

Korea

T +82 2 6201 4600
F +82 2 6201 4601

Malaysia

T +60 3 9206 1555
F +60 3 9206 1533

Thailand

T +66 2207 3456
F +66 2207 3488

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silquest and SPUR+ are trademarks of Momentive Performance Materials Inc.

The Momentive logo is a trademark of Momentive Performance Materials Holdings LLC.



22 Corporate Woods Boulevard
Albany, NY 12211 USA

+1 800 295 2392
+1 607 786 8131
momentive.com