

# SilFORT™ PHC587 Hardcoat

## **Product Description**

SilFORT PHC587 hardcoat is a clear, non-yellowing siloxane coating, which adheres well to various grades of Polycarbonates, without the need of a primer coat. It offers protection against deterioration from weather elements, such as ultraviolet rays, heat, cold, rain, snow and ice. It also offers damage resistance from sand and dirt. SilFORT PHC587 hardcoat is an excellent candidate to consider for use on polycarbonate headlamp lenses. It is compliant with the ECE automotive forward lighting regulations<sup>①</sup> and is accepted by AMECA for three years of Florida and Arizona weathering.

## **Key Features and Typical Benefits**

- Primerless adhesion to Polycarbonate
- Excellent optical clarity
- Excellent chemical resistance
- Easy-to-clean properties
- Excellent abrasion and mar resistance
- Good ultraviolet resistance

# **Potential Applications**

• Exterior polycarbonate components

## **Typical Physical Properties**

Property	Unit	Typical Value
Physical Form	-	liquid
рН	-	approx. 7.5
Appearance	-	pale yellow
Solids Content	% by weight	approx. 20,5
Kinematic Viscosity (at 25 °C)	cSt	approx. 6
Density (at 25 °C)	g/cm <sup>3</sup>	approx. 0.91
Shelf Life <sup>②</sup>	months	12 (below 10°C)

Typical properties are average data and are not to be used as or to develop specifications.

<sup>(1)</sup> Based on the requirements as of October 2022

<sup>&</sup>lt;sup>2</sup> From date of manufacture in original, unopened container

#### **General Considerations for Use**

Typical Processing <sup>®</sup>	SilFORT PHC587 hardcoat
Application method	spray, flow, dip coating
Reducing solvents <sup>4</sup>	1-Butanol (CAS#71-36-3)
	2-Propanol (CAS#67-63-0)
	1-Methoxy-2-Propanol (CAS#107-98-2)
Relative humidity (application & ambient flash off)	typically 25 – 55 %
Room temperature flash off	20 – 30 °C for 5 – 30 minutes
Cure conditions	126 - 130 °C for 30 minutes <sup>⑤</sup>
Recommended layer thickness	6 – 12 μm

To ensure coating solution is free from particles, filtration of the hardcoat, combining a 5  $\mu$ m pre-filter, in line with a 1  $\mu$ m absolute filter is recommended.

## **Packaging**

Currently available in:

25 kg pail 180 kg drum 5G-pail (15.89 kg) 55G-drum (181.6 kg)

#### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

# **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment, if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at <a href="www.momentive.com">www.momentive.com</a> or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## Limitations

 $Customers\,must\,evaluate\,Momentive\,Performance\,Materials\,products\,and\,make\,their\,own\,determination\,as\,to\,fitness\,of\,use\,in\,their\,particular\,applications.$ 

<sup>3</sup> Recommended typical processing conditions might be adapted due to customer specific requirements

<sup>(4)</sup> Other solvents may be considered

⑤ Dwell time at recommended part surface temperature, for polycarbonate

<sup>&</sup>lt;sup>(6)</sup> When higher-heat resistant thermoplastic materials are selected, use the recommended annealing temperature of the respective plastic grade and manufacturer to choose the adequate cure temperature for the coating

#### **Contact Information**

#### Email

## commercial.services@momentive.com

Telephone			
Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
*All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number*	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka.	Korea +82 2 6201 4600 Direct number
			South East Asia, Australia & New Zealand +60 3 9206 1543 Direct number*
			*South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).

For literature and technical assistance, visit our website at: www.momentive.com

## DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter,

vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are registered trademarks of Momentive Performance Materials Inc.



260 Hudson River Road Waterford, NY 12188 USA momentive.com

Copyright 2021 Momentive Performance Materials Inc. All rights reserved.