

# Tufel™ II 94406

## Product Description

Tufel II Silicone Rubber Compounds 94406, 94506, 94606, 94706 are 40-70 durometer low volatile fast-cure addition cured silicone elastomers for extrusion and calendaring. They may be used by themselves or blended to intermediate durometers. Applications include extruded tubings, profiles and calendared sheets.

## Key Features and Typical Benefits

- LV Bases Minimize Porosity and Post Cure
- Totally Peroxide-Free Cure System
- Broad Processing Window
- High Output Rates
- High Tear Strength
- Tight Surface Cure
- Non-blooming
- Translucency

## Typical Physical Properties

Typical characteristics of uncured Tufel II silicone rubber - 94006 series

| Properties                           | 94406       | 94506       | 94506       | 94706       |
|--------------------------------------|-------------|-------------|-------------|-------------|
| Specific Gravity                     | 1.11        | 1.15        | 1.19        | 1.22        |
| Appearance                           | Translucent | Translucent | Translucent | Translucent |
| Polymer Classification (ASTM D-1418) | VMQ         | VMQ         | VMQ         | VMQ         |

Typical properties are average data and are not to be used as or to develop specifications.

Typical rheological profile - Monsanto odr with 3° arc @ 150°C (300°F)

|                         |         |         |         |         |
|-------------------------|---------|---------|---------|---------|
| Minimum Viscosity       | 1-6     | 3-7     | 3-8     | 3-9     |
| T1, Minutes             | 0.1-0.4 | 0.1-0.4 | 0.1-0.3 | 0.1-0.4 |
| 7 Min. Torque (lb./in.) | 33-48   | 34-53   | 45-60   | 45-60   |

Typical physical properties of Tufel II silicone rubber - 94006 series Catalyzed with 1.0 pphr of CA-6 per 99 pphr of base compound

| ASTM METHOD | PRESS CURE - 10 MINUTES @ 177°C (350°F) | 94406 | 94506 | 94606 | 94706 |
|-------------|---|-------|-------|-------|-------|
| D-2240      | Hardness, Durometer A                   | 39    | 48    | 56    | 71    |
| D-412       | Tensile Strength, psi                   | 1300  | 1348  | 1230  | 1320  |
|             | MPa                                     | 9.0   | 9.2   | 8.5   | 9.1   |
| D-412       | Elongation, %                           | 900   | 900   | 740   | 630   |
| D-624       | Tear Resistance, Die B, ppi             | 225   | 250   | 240   | 320   |
|             | KN/M                                    | 39    | 44    | 42    | 56    |

|        |   |      |      |      |      |
|--------|---|------|------|------|------|
| D-412  | Tensile Modulus @ 100% psi                  | 140  | 190  | 245  | 500  |
|        | MPa   | 1.0  | 1.3  | 1.7  | 3.4  |
|        | POST CURE 2 HOURS @ 177°C (350°F)           |      |      |      |      |
| D-2240 | Hardness, Durometer A                       | 43   | 53   | 61   | 73   |
| D-412  | Tensile Strength, psi                       | 1350 | 1400 | 1250 | 1350 |
|        | MPa   | 9.3  | 9.7  | 8.6  | 9.3  |
| D-412  | Elongation, %                               | 800  | 850  | 680  | 600  |
| D-624  | Tear Resistance, Die B, ppi                 | 235  | 270  | 270  | 330  |
|        | KN/M  | 41   | 47   | 47   | 58   |
| D-412  | Tensile Modulus @ 100% psi                  | 170  | 225  | 300  | 530  |
|        | MPa   | 1.2  | 1.6  | 2.1  | 3.7  |
| D-395  | Compression Set, %<br>22 hrs. @ 150 (300°F) | 20   | 20   | 20   | 20   |

#### Regulatory Compliance

- A representative sample of an analogous product to Tufel II 94406 met the requirements of USP Class VI and ISO 10993 under Good Laboratory Practices (GLP). • Listed as UL 94 HB (File No. E205753)
- The ingredients are listed in the BfR recommendation XV “Silicones” (1)
- Compositionally compliant with 21 CFR 177.2600 – Rubber articles intended for repeated use(2)

(1) Producer of the final article needs to test and confirm that the final product meets the extraction limits of BfR XV or corresponding EU legislation.

(2) It is the responsibility of the user to determine that the final product complies with the extractive limitations and other requirements of 21 CFR 177.2600, under their specific manufacturing procedures

#### General Considerations for Use

NA

#### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

#### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

#### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

## Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

#### Americas

+1 800 295 2392

Toll free\*

+704 805 6946

Direct Number

#### Latin America

##### Brazil

+55 11 4534 9650

Direct Number

#### EMEAI- Europe, Middle East, Africa & India

##### Europe

+390510924300

Direct number

#### ASIA PACIFIC

##### China

800 820 0202

Toll free

+86 21 3860 4892

Direct number

\*All American countries

#### Mexico

+52 55 2169 7670

Direct Number

#### India, Middle East & Africa

+ 91 44 71212207

Direct number\*

#### Japan

0120-975-400 Toll free

+81 27620 6182

Direct number

\*All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka.

#### Korea

+82 2 6201 4600

Direct number

#### South East Asia, Australia & New Zealand

+60 3 9206 1543

Direct number\*

\*South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### DISCLAIMER:

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any

oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.



260 Hudson River Road Waterford,  
NY 12188 USA  
[momentive.com](http://momentive.com)

Copyright 2022 Momentive Performance Materials Inc. All rights reserved.