

SPUR+* 1050MM Prepolymer



MARKETING BULLETIN

SILANES - ADHESIVES & SEALANTS ADDITIVES

SPUR+ 1050MM prepolymer is a silylated prepolymer, plasticizer-free, with low viscosity, for use in the manufacture of one-part, moisture-curing sealants. It is an excellent material of choice as a base resin for medium modulus sealants and adhesives in industrial and transportation applications where higher tensile strength is required.

Key Features and Typical Benefits

- Broad formulation latitude
- Cost-effective
- Easy application characteristics
- Excellent adhesion to many surfaces without primer
- High durability indoors and outdoors
- Good water and chemical resistance
- High elastic recovery
- Long shelf life

Typical Physical Properties

	SPUR+ 1050MM Prepolymer
Appearance	Clear, Viscous liquid
Viscosity (25 °C) (mPa)	≈ 35,000
Plasticizer	none
Shelf Life (months)	24
Tensile Strength (N/mm ²)	0.68
Elongation (%)	150
100% Modulus (N/mm ²)	0.55
Shore A	29
Elastic Recovery (%)	87

Typical properties are average data and are not to be used as or to develop specifications.

Key Features of SPUR⁺ Prepolymer Technology

Silane-terminated polyurethanes (SPUR⁺ prepolymers) have become increasingly attractive to manufacturers of adhesives, sealants and coatings. This hybrid technology is appealing because of the synergy between the silane-curing mechanism and polyurethane backbone properties.

Formulations developed through this technology offer fast room-temperature cure and good durability, while the sealants or adhesives they produce are free of unreacted isocyanate. Benefits of the resulting products also include freedom from bubbling during cure and a broadening of the formulation latitude compared to conventional polyurethane technologies. These prepolymers allow the formulator to use a wide variety of additives and adhesion promoters to meet end users' performance needs, such as:

1. Good elasticity and durability
2. Primerless adhesion to both organic and inorganic, porous and non-porous substrates
3. Superior chemical resistance, such as to automotive fluids
(e.g., glycols, motor and transmission fluids)
4. Minimal shrinkage
5. Excellent weatherability
6. Immediate paintability
7. Non-staining of porous substrates

Performance of SPUR⁺ Sealants

The following generic sealant formulae may be used to evaluate the performance characteristics of SPUR⁺ prepolymers.

Ingredients

SPUR⁺ 1050MM Prepolymer

Plasticiser (DIDP)

Moisture Scavenger (Silquest A-171* Silane)

Calcium carbonate

UV stabilizers

SiO²

TiO²

Adhesion Promoter (Silquest* A-1110 Silane)

Tin catalyst

The SPUR⁺ prepolymer content represents 23% of the total formulation.

The mechanical properties are measured after curing the sealants for 2 weeks at 23°C/50% relative humidity, and testing according to ISO 37 (tensile properties), ISO 868 (Shore A hardness).

	SPUR ⁺ 1050MM Prepolymer
Elongation at break (%)	305
100% Modulus (N/mm ²)	1.24
Tensile Strength (N/mm ²)	1.97
Hardness Shore A	46.1

References

- [1] Saunder, J.H. and K.C. Frisch, *Polyurethanes: Chemistry and Technology*, Vol. I, Part I, Interscience, NY (1962), P. 273. (b)
- [2] (a) Feng, T.M. and B.A. Waldman, "Silylated Urethane Polymers Enhance Properties of Construction Sealants," *Adhesives Age*, April 1995. (b) Landon, S.J. A. Guillet and R.R. Johnston, ("Silylated Urethane Polymers for Sealants,") *European Adhesives and Sealants*; Dec. 1995.
- [3] Landon, S.J., M.B. Dawkins, B.A. Waldman, R.R. Johnston, "The Adhesion of Hybrid Resins to Plastic Substrates;" *Adhesives Age*, April 1997.
- [4] Huang, M.W., and R. Handel, "New Developments in Silylated Polyurethane Technology," *Adhesives Age*, April 1999.
- [5] Johnston, R.R. and P. Lehmann, US 5,990,257.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative.

For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Customer Service Centers

Worldwide

Email: commercial.services@momentive.com

Americas

+1 800 295 2392
+1 614 986 2495

Europe, Middle East, Africa and India

00800 4321 1000
+40 213 044229

Asia Pacific

China
800 820 0202
+86 21 3860 4892

All Other Countries
+60 3 9206 1543

Japan

0120 975 400
+81 276 20 6182

Disclaimer

FORMULATIONS ARE ILLUSTRATIVE EXAMPLES AND DO NOT REPRESENT COMMERCIALIZED PRODUCTS. They have not been subjected to extensive testing and Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the performance, efficacy or safety of any product manufactured using such formulations. EACH USER BEARS FULL RESPONSIBILITY FOR (1) MAKING ITS OWN DETERMINATION AS TO THE SUITABILITY AND LEGAL COMPLIANCE OF ANY FORMULATION, MATERIALS, RECOMMENDATIONS, OR ADVICE FOR ITS OWN PARTICULAR USE, (2) IDENTIFYING AND PERFORMING ALL TESTS AND ANALYSES NECESSARY TO ASSURE THAT ITS FINISHED PRODUCTS BASED UPON EXAMPLE FORMULATIONS AND/OR INCORPORATING MENTIONED PRODUCTS, MATERIALS, OR SERVICES WILL BE SAFE AND SUITABLE FOR USE UNDER END-USE CONDITIONS, AND (3) OBTAINING ANY NECESSARY GOVERNMENT OR REGULATORY CLEARANCE, LICENSE OR REGISTRATION.

Any reference to a third party's materials is not an endorsement of those materials or an endorsement by the third party of Momentive materials. Momentive has not undertaken a comprehensive patent or other intellectual property search on the formulations. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

BEFORE HANDLING ANY PRODUCTS MENTIONED, REVIEW THE LATEST SAFETY DATA SHEET (SDS) AND LABEL FOR PRODUCT SAFETY INFORMATION, SAFE HANDLING INSTRUCTIONS, PERSONAL PROTECTIVE EQUIPMENT IF NECESSARY, EMERGENCY SERVICE CONTACT INFORMATION, AND ANY SPECIAL STORAGE CONDITIONS REQUIRED FOR SAFETY. MOMENTIVE MAINTAINS AN AROUND-THE-CLOCK EMERGENCY SERVICE FOR ITS PRODUCTS. SDS FOR MOMENTIVE PRODUCTS ARE AVAILABLE AT WWW.MOMENTIVE.COM OR, UPON REQUEST, FROM ANY MOMENTIVE REPRESENTATIVE. USE OF OTHER MATERIALS IN CONJUNCTION WITH MOMENTIVE PRODUCTS MAY REQUIRE ADDITIONAL PRECAUTIONS. PLEASE REVIEW AND FOLLOW THE SAFETY INFORMATION PROVIDED BY THE MANUFACTURER OF SUCH OTHER MATERIALS.

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier.