

CoatOSil* P576

CoatOSil* P576

Description

Medium-hard high solid phenylmethyl silicone resin in solvent.

Typical Physical Properties

Viscosity, 23°C, DIN 53 015	600 - 1300 mPa.s
Iodine color value, DIN 6162	max. 4

Potential Applications

Binder for anticorrosion coatings with thermal stability up to 600°C.

The main potential fields of application are the coating of machine components, engine manifolds, car exhaust silencers, drying units etc. These applications commonly use one-coat finishes. Systems of this kind may also be utilized in the sealing of spray-metallized surfaces.

Form Supplied

Approx. 75% in xylene (technical): butanol = 4 : 1

Drying

Coatings formulated with CoatOSil Resin P 576 typically dry tack-free at room temperature, yielding films with good mechanical resistance, weather stability and corrosion resistance. However, optimum mechanical properties and resistance to oil and petrol generally require a minimum exposure to temperatures above 200°C, for about one hour. Drying at room temperature may be improved by the addition of approximately 3% high molecular weight ethyl cellulose, calculated on the solid binder.

Pigments

Aluminium bronze and Micaceous iron oxide should generally be used. Micaceous iron

oxide coatings can be tinted with suitable heat-resistant inorganic color pigments. A long-term thermal stability up to 600°C can typically be achieved with aluminium bronze or micaceous iron oxide.

Black coatings should generally be pigmented with Bayferrox 303 T and Fast Black 100. The long-term heat resistance of such systems is generally 550 - 600°C.

The shelf life of coatings prepared according to recommended guidelines is generally 3 - 6 months.

The use of zinc dust is not recommended..

Solubility

Aliphatic hydrocarbons	Insoluble
Aromatic hydrocarbons	Soluble
Alcohols	Insoluble
Esters	Soluble
Ketones	Soluble
Glycol ethers	Soluble

Compatibility

CoatOSil Resins	
M range	Incompatible
UD range	Partly compatible
Organic binders	partly compatible

Packaging

200 kg steel drums, 18kg pails

Patent Status

Standard copy to come

Product Safety, Handling and Storage

When stored in its original, unopened container at 25°C, CoatOSil Resin P 576 has a shelf life of 360 days, from the date of manufacturing.

As the product contains solvents, the relevant regulations on the handling of such products should be observed.

Standard copy to come

Limitations

Standard copy to come

Contact Information

For product prices, availability, or order placement, contact our customer service at [Momentive.com/Customerservice/](https://www.momentive.com/Customerservice/)

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any

provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*CoatOSil is a trademark of Momentive Performance Materials Inc.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.