

FSL 7641

FSL 7641

Fluorinated Liquid Silicone Rubber

Description:

FSL 7641 is a two-component fluorinated liquid silicone rubber for injection molding processes. This material is an excellent candidate to consider for the manufacturing of elastomeric articles exposed to lubricants, fuels and solvents. Compared to standard liquid silicone rubbers without fluorine content, the resistance of FSL 7641 fluorinated liquid silicone rubber to oil and fuel is much better.

Key Features and Typical Benefits:

Vulcanizates consisting of FSL 7641 fluorinated liquid silicone rubber are typically distinguished by the following properties:

- Improved resistance to oils
- Balanced fluid and solvent resistance
- Low compression set without post-cure
- Fast cure
- High thermal stability
- High stability and flexibility at low temperatures
- Outstanding resistance to aging
- Easy to color

Typical Physical Properties:

		A-part	B-part
Appearance		Translucent	Translucent
Viscosity in Pa•s,	DIN 53 018	790	700

$\dot{\gamma}=10s^{-1}$ at 20°C			
Mixing Ratio of Components A:B=1:1, Vulcanization conditions: 10 min/175°C, post-curing 4h/200°C in hot air			
Density	DIN 53 479 A	g/cm ³	1.23
Hardness	DIN 53 505	Shore A	38
Tensile Strength	DIN 53 504 S2	MPa	8.5
Elongation at Break	DIN 53 504 S2	%	590
Tear Strength	ASTM D 624 die B	N/mm	24
Compression Set (22h/175°C)	DIN ISO 815	%	18

Typical properties are average data and are not to be used as or to develop product specifications.

Potential Applications:

Because of its outstanding properties, FSL 7641 fluorinated liquid silicone rubber is an excellent candidate to consider for use in the following elastomeric articles:

- O-Rings
- Seals and Gaskets
- Membranes
- Mold-Making
- Air-Intake Flaps and other 2-Component Parts (application of appropriate bonding agent necessary to bond to plastic substrates)

Processing Considerations:

Ready-to-use mixtures (of the components A and B) are typically fed directly to the injection-molding machine from the original drums by means of a metering and mixing unit. The pot-life of the mixture of the two components (closed vessel) at 20°C is typically three days. The mixture, consisting of the two components in the ratio 1:1, is injected into the heated mold. At mold temperatures of 170 - 230°C, the addition-curable silicone rubber usually cures within a few seconds. The curing process does not generate splitting products. High curing speed and easy demolding can help enable fully automated production of large numbers of articles in short cycle times. FSL 7641 fluorinated liquid silicone rubber should only be used for the production of technical

articles. For further information please contact Momentive Performance Materials.

Packaging:

FSL 7641 fluorinated liquid silicone rubber is available in 2x20kg pail kits.

Compliance:

FSL 7641 fluorinated liquid silicone rubber is not compositionally compliant with 21 CFR §177.2600.

Storage:

Correctly stored in its original unopened container at room temperature (max 27°C), FSL 7641 fluorinated liquid silicone rubber has a shelf life of 540 days from the date of manufacturing. Please check use-before/expiry date on product label and certificate. Containers which have been opened must be kept tightly closed afterwards.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their

own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		*All Middle Eastern countries, Africa, India,	Korea
			+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR

GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.