

InvisiSil* IVS4632

Description

InvisiSil IVS4632 is a two-component, addition cure silicone rubber designed for optical device coating. This product cures with heat to an elastomer.

Key Features and Benefits

- Low viscosity allows for excellent flowability
- Excellent transparency
- Convenient 1:1 mix ratio by weight
- Cures fast with heat and adheres to parts

Typical Physical Properties

UNCURED PROPERTIES		InvisiSil IVS4632(A)	InvisiSil IVS4632(B)
Appearance		Transparent	Transparent
Viscosity (23°C)	Pa•s {P}	7.5 {75}	1.4 {14}
Mixing Ratio by Weight		1:1	
Viscosity after Mixing (23°C)	Pa•s {P}	3.2 {32}	
Pot Life (23°C)	h	8	
Refractive Index (n_D^{25})		1.41	
CURED PROPERTIES (1h @ 150°C)			
(Note: When using as LED encapsulant, two-step cure process as shown below *1 is recommended)			
Density (23°C)	g/cm ³	1.05	
Hardness (Type A)		64	
Tensile Strength	MPa {kgf/cm ² }	9.0 {92}	
Elongation	%	80	
Lap Shear Strength*2	MPa {kgf/cm ² }	1.5 {15}	
Linear Expansion	1/K	2.8x10 ⁻⁴	
Volume Resistivity	Ω•cm	1.0x10 ¹⁵	
Dielectric Strength	kV/mm	20	
Dielectric Constant (60Hz)		2.8	
Dissipation Factor (60Hz)		0.001	

*1 Recommended cure condition: first cure; 1.5h at 80°C, second cure; 1h at 150°C


*2 Substrate: PPA (Polyphthalamide)

Typical property data values should not be used as specifications.

Potential Applications

- Coating and potting of optical device

Transmittance(uncured sample, thickness: 1mm)



Processing Recommendations

1. Weigh out (A) and (B) to the clean container 5 times larger than the volume of silicone rubber compound to be used.
2. Mix (A) and (B) thoroughly with clean tools.
3. Deaerate the mixture at a pressure of 0.65 kPa (5 mmHg) for more than 5 minutes to remove air entrapped during mixing.
4. Apply and cure with heat. When using as LED encapsulant, two-step cure process is recommended (first cure: 1.5h at 80°C, second cure: 1h at 150°C).

Note: All parts should be as clean and dry as possible prior to applications. Materials such as water, sulfur, nitrogen compounds, organic metallic salts, phosphorus compounds, etc. contained in the surface of the substrate can inhibit curing. It is recommended that a preliminary test be performed to determine the compatibility.

Packaging

- InvisiSil IVS4632(A): 500g bottle available in cases of 9
- InvisiSil IVS4632(B): 500g bottle available in cases of 9

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

- Wear eye protection and protective gloves as required while handling the product.
- Maintain adequate ventilation in the work place at all times

- Store in a cool and dry place out of direct sunlight.
- Keep out of the reach of children.

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products,

materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*InvisiSil is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.