

IS 5128 E

IS 5128 E

Description

IS 5128 E adhesive/sealant is a one component neutral RTV which quickly cure to form elastic, flexible silicone rubbers. This product is specially developed to be non-corrosive to metals including copper and copper alloys, coupled with fast cure. IS 5128 E has a thixotropic paste consistency, excellent dielectric properties and excellent primerless adhesion to plastics like polycarbonate, which make these materials ideal for electronic applications as well as for sealing bonding high performance plastics.

Key Features and Benefits

- non-corrosive to metals
- fast cure
- non-acid cure, low smell, no irritating vapours
- compatible with polycarbonate
- excellent dielectric properties
- temperature -50° to +150° C

Typical Physical Properties

Typical Uncured Properties

	5128 E
--	--------

Colour		Translucent
Density	g/cm ³	1.03
Tack Free Time	minutes	10
Consistency		Paste
Application rate, 6mm orifice/2bar	g/min	250

Typical Cured Properties

Property	Test Method	Unit	Typical value
Hardness	DIN 53505	Shore A	20
E Mod @ 100%	DIN 53504	MPa	0.35
Tensile Strength	DIN 53504	MPa	1.7
Elongation	DIN 53504	%	550
Dielectric Strength		kV/mm	25
Dielectric Constant (50 Hz)			2.8
Dissipation Factor (50 Hz)			0.005
Volume Resistivity		ohm-cm	1x10 ¹⁵

Patent Status

Standard copy to come

Product Safety, Handling and Storage

Standard copy to come

Limitations

Standard copy to come

Contact Information

For product prices, availability, or order placement, contact our customer service at [Momentive.com/Customerservice/](https://www.momentive.com/Customerservice/)

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.