

LIM* 6071

Description

LIM6071 is the next generation in 70-durometer liquid silicone rubber. It is a two-component product formulated for use in liquid injection molding to produce high performance parts. It is clear, but easily pigmentable with Momentive masterbatch colors. The combination of excellent tear strength and very high tensile strength makes this product suitable for a wide variety of applications. Mechanical parts such as connector inserts, seals, flexible mounts, and valve parts can be made readily from LIM6071 liquid silicone rubber.

Key Features and Benefits

- High clarity for excellent visibility
- Excellent tear strength
- Convenient 1:1 mix ratio for use with automatic equipment
- Rapid cure time: 10 to 40 seconds depending upon part size, configuration and molding temperature
- Wide range of molding temperatures: 150°C (302°F) to 232°C (450°F)
- Excellent release from metal molds
- High Bayshore resilience

Typical Physical Properties

<u>Uncured Properties</u>	<u>LIM6071 - A</u>	<u>LIM6071 - B</u>
Color	Clear	Clear
Specific Gravity, gm/cc	1.12	1.12
Application Rate, gm/min.	70	70
	<u>Mixed A + B</u>	
	<u>LIM6071 A + B</u>	
	<u>Cure Rate: (Monsanto Rheometer)MDR2000 @ 177°C (350°F)</u>	
Torque, max, in/lbs.		36.3
T02, seconds		4

Peak Rate, in/lbs./min	206
T90, seconds	50
<u>Cured Properties</u>	
<u>PRESS CURE 17 MINUTES @ 177°C (350°F)</u>	
Hardness, Shore A	70
Tensile Strength, psi (MPa)	1150 (7.9)
Elongation, %	370
Tear Strength Die B, ppi (KN/M)	230 (40.4)
Tensile Modulus, 100% psi (MPa)	430 (3.0)
Compression Set %	
22 hours @ 177C (350F)	40
Bayshore %	65
<u>POST BAKE 4 HOURS 205°C (400°F)</u>	
Hardness, Shore A	70
Elongation, %	330
Tear Strength Die B, ppi (KN/M)	210 (36.8)
Tensile Modulus, 100% psi (MPa)	460 (3.2)
Bayshore %	66

Typical product data values should not be used as specifications.

Assistance and specifications are available by contacting Momentive.

Potential Applications

- Sports goggles and masks
- Health care profiles
- Camera parts
- Metal roll coatings.

Processing Recommendations

Ready-to-use mixtures (of the components A and B) are fed directly to the injection-molding machine from the original containers by means of a metering and mixing unit. The mixture, consisting of the two components in the ratio 1:1, is injected into the heated mold. At mold temperatures of 170°C - 230°C, the addition-cross linking silicone rubber typically vulcanizes, without any dissociation products, within a few seconds. High curing speed and easy demolding can help enable fully automated production of a large number of articles in short cycle times.

Regulatory Compliance

- A representative sample of an analogous product to LIM 6071 met the requirements of USP Class VI.
- Listed as UL 94 HB (File No. E205753)
- The ingredients are listed in the BfR recommendation XV "Silicones"⁽¹⁾
- Compositionally compliant with 21 CFR 177.2600 – Rubber articles intended for repeated use⁽²⁾

- (1) Producer of the final article needs to test and confirm that the final product meets the extraction limits of BfR XV or corresponding EU legislation.
- (2) It is the responsibility of the user to determine that the final product complies with the extractive limitations and other requirements of 21 CFR 177.2600, under their specific manufacturing procedures.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING

FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*LIM is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.