

## Magnasoft\* HSSD

### Magnasoft\* HSSD

#### Description

Magnasoft HSSD is an efficient hydrophilic silicone softener for a wide range of fabrics, such as 100% cotton, polyester/ cotton blends, wool, rayon and acrylic wovens, nonwovens, and knits.

#### Key Features and Benefits

Magnasoft HSSD hydrophilic textile softener is a water-dispersible aminommodified hydrophilic softener based on new technology developed by GE Advanced Materials - Silicones. It is designed to impart the soft, silky hand characteristics of traditional aminosilicones but with the added property of hydrophilicity. Testing has shown that Magnasoft HSSD hydrophilic textile softener provides superior softening, hydrophilicity, and non-yellowing properties compared to competitive hydrophilic products.

Durable softening and hydrophilicity are achieved with Magnasoft HSSD hydrophilic textile softener in the presence or absence of durable press resins. A luxurious hand is imparted to substrates treated with Magnasoft HSSD hydrophilic textile softener at low add-on levels (1-2 weight percent).

Magnasoft HSSD hydrophilic textile softener is easy to use because it is water-dispersible. Its nonionic nature makes it compatible with other components that might be used during the finishing of nonwovens, wovens or knits.

#### Typical Physical Properties

Appearance	Clear to slight haze
Actives, %	100
Color, GVS, max	2
Viscosity at 25°C, cSt	3700
Solvent	Water-dispersible

#### Processing Recommendations

**Performance**

**Nonwoven Fabrics**

Magnasoft HSSD hydrophilic textile softener was pad bath-applied to 100% thermalbonded polyester and 100% spun bonded polypropylene at a 1.0% actives level. Magnasoft HSSD hydrophilic textile softener imparted a soft, luxurious feel to both nonwovens and reduced wetting times of both materials from >300 sec to <1 sec.

**Table 1: Magnasoft HSSD Hydrophilic Textile Softener Performance on Nonwoven Fabrics**

Fabric	Percent Silicone Add-On	Softness <sup>(1)</sup>	Wettability <sup>(2)</sup> , sec
100% Thermalbonded Polyester			
Magnasoft HSSD hydrophilic textile softener	1	1	<1
Water Only (Control)	—	10	>300
100% Spunbonded Polypropylene (1.3 oz)			
Magnasoft HSSD hydrophilic textile softener	1	1	<1
Water Only (Control)	—	10	>300

(1) Scale: 1 = Softest, 10 = Harshesht

(2) AATCC 79-1986

**Woven Fabrics**

Table 2 shows the results of applying Magnasoft HSSD hydrophilic textile softener to 100% cotton terry cloth, 65/35 = polyester/ cotton broadcloth, and 100% cotton knit fabrics. These fabrics exhibited substantially improved softness with no reduction in hydrophilicity. In addition, there was no reduction in fabric whiteness — either initially or after 100 sec exposure at 200°C.

**Table 2: Magnasoft HSSD Hydrophilic Textile Softener Performance on Woven Fabrics**

Fabric	Percent Silicone Add-On	Dp <sup>(1)</sup> Resin	Percent Reflectance <sup>(2)</sup>			Softness <sup>(3)</sup>	Wettability <sup>(4)</sup> ,sec
			at 200°C				
			Initial	50 sec	100 sec		
100% Cotton Terrycloth (S420)							
Set I							
Magnasoft HSSD							
hydrophilic textile softener	2.0	No	67	58	51	1	<1
Water Only (Control)	—	No	67	60	43	10	1
Set II							
Magnasoft HSSD							
hydrophilic textile softener	1.0	No	68	—	46	2	<1
Water Only (Control)	—	No	66	-	44	10	1
Set III							
Magnasoft HSSD							
hydrophilic textile softener	1.0	Yes	68	—	48	3	<1
Resin Only (Control)	—	Yes	68	—	49	10	<1
65/35 = -Polyester/Cotton Broadcloth (S7409)							
Magnasoft HSSD							
hydrophilic textile softener	1.0	Yes	78	—	60	3	4
Resin Only (Control)	—	Yes	80	—	69	10	4
100% Cotton Knit (S459)							
Magnasoft HSSD							
hydrophilic textile softener	1.0	Yes	76	—	51	2	<1
Resin Only (Control)	—	Yes	73	—	56	10	<1

(1) Formulations contained 15 parts DMDHEU durable press resin (38%)

(2) "Colorquest" Sphere Spectrophotometer

(3) Scale; 1 = Softest, 10 = Harshesht

(4) AATCC 79-1986

### Knit Fabrics

The performance of Magnasoft HSSD hydrophilic textile softener was compared to a competitive silicone softener on 100% cotton and 50/50 = polyester/cotton knits at 0.5% and 1.0% silicone solids (BOWF). As Table 3 shows, Magnasoft HSSD hydrophilic textile softener exhibited superior non-yellowing and softness properties on both knits. The hydrophilic properties of both silicones were comparable.

**Table 3: Magnasoft HSSD Hydrophilic Textile Softener Performance on Knit Fabrics**

Fabric	Percent Silicone Add-On	Softness <sup>(1)</sup>	Wettability <sup>(2)</sup> , sec	Percent Reflectance <sup>(3)</sup>	
				Initial	100 sec
100% Cotton Knit (S459)					
Set I					
Magnasoft HSSD hydrophilic textile softener	0.5	1	<1	79	55
Competitive Hydrophilic Silicone	0.5	3	<1	76	52
Water Only (Control)	—	10	<1	76	43
Set II					
Magnasoft HSSD hydrophilic textile softener	1.0	1	<1	80	55
Competitive Hydrophilic Silicone	1.0	4	<1	77	51
Water Only (Control)	—	10	<1	76	43
50/50 = Polyester/Cotton (S7421)					
Set III					
Magnasoft HSSD hydrophilic textile softener	0.5	1	2	96	81
Competitive Hydrophilic Silicone	0.5	4	1	88	74
Water Only (Control)	—	8	12	86	58
Set IV					
Magnasoft HSSD hydrophilic textile softener	1.0	1	1	95	80
Competitive Hydrophilic Silicone	1.0	3	1	91	77
Water Only (Control)	—	8	12	86	58

(1) Scale: 1 = Softest, 10 = Harshesht

(2) AATCC 79-1986

(3) "Colorquest" Sphere Spectrophotometer

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the

Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

**Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

**Contact Information**

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](http://Momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.**

Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Magnasoft is a trademark of Momentive Performance Materials Inc.1033

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**