

Magnasoft* HWS

Magnasoft* HWS

Description

Magnasoft HWS hydrophilic softener is a novel epoxy polyether terpolymer that provides hydrophilicity and a soft full hand when applied to a variety of knit and woven fabrics. Magnasoft HWS hydrophilic softener has been demonstrated to provide excellent softness with virtually no yellowing when applied to natural and synthetic fibers such as cotton and polyester. Magnasoft HWS hydrophilic softener imparts instant rewetting character to fabrics, and does not interfere with the soil release properties of fabrics that are treated with fluorocarbon soil release agents.

Dilutions of Magnasoft HWS hydrophilic softener are extremely shear stable and are suitable for use in Jet dye and EVAC systems. Fabrics treated with Magnasoft HWS hydrophilic softener can often be redyed unlike many traditional silicone softeners.

Key Features and Benefits

- Imparts excellent softness to all types of fabrics
- Safe and easy to use on difficult to rework fabrics
- Dilutions are extremely shear stable
- Provides instant rewetting properties to fabrics
- Does not contribute to fabric yellowing
- Will not interfere with the soil release properties of fabrics that are treated with fluorocarbon soil release agents
- Easily diluted with water
- Water dilutions have excellent compatibility with finishing baths

Typical Physical Properties

Appearance	Clear, slightly yellowish liquid
Viscosity at 25°C, cPs	3300
Specific Gravity, 25/25°C	1.0
Solubility in Water	Dispersible
Ionic Nature	Nonionic
Percent Actives, %	100

Processing Recommendations**Recommended Method for Preparing an Aqueous Dispersion of Magnasoft HWS Hydrophilic Softener**

To prepare stable aqueous dispersions of Magnasoft HWS hydrophilic softener, slowly pour the silicone into the vortex of the total water (preferably tepid) while mixing at ~400 rpm.

Viscosity of Magnasoft HWS hydrophilic softener when diluted in water

	Viscosity (cPs)
15% in Water	340
20% in Water	490

Recommended Method for Preparing a Clear Concentrate of Magnasoft HWS Hydrophilic Softener**1. Emulsion Concentrate Formulation**

Magnasoft HWS Hydrophilic Softener	70
Iconol TDA-6 ⁽¹⁾ Surfactant	1.4
Iconol TDA-10 ⁽¹⁾ Surfactant	2.8
Water	25.8

(1) BASF Corporation

Preparation

1. Premix Magnasoft HWS hydrophilic softener and mix with moderate speed for at least three minutes.
2. Increase stirring speed to generate a small vortex and slowly add water at a rate that allows the water to be incorporated. Mix for an additional ten minutes. The resulting concentrate is a clear dilutable liquid with excellent stability.

The resulting concentrate is a clear dilutable liquid with excellent stability.

Table 1: Magnasoft HWS Hydrophilic Softener Performance Results on 100% Cotton Knit (1% BOWF)

	Magnasoft HWS hydrophilic softener	Competitive Product	Untreated
Softness ⁽¹⁾	5.3	4.0	2
Wettability (s)	<1	<1	<1
Whiteness (initial)	79.45	–	82.35
Whiteness (scorched)	57.60	–	58.64

(1) Softness was rated by a hand panel of 5 people. 6 = very soft, 1 = harsh.

Table 2: Magnasoft HWS Hydrophilic Softener Performance Results on 100% Cotton Terry Cloth (1% BOWF)

	Magnasoft HWS hydrophilic softener	Competitive Product	Untreated
Softness ⁽¹⁾	5.5	4.0	2
Wettability (s)	1	1	<1
Whiteness (initial)	62.6	–	59.12
Whiteness (scorched)	49.88	–	43.87

(1) Softness was rated by a hand panel of 5 people. 6 = very soft, 1 = harsh.

Table 3: Magnasoft HWS Hydrophilic Softener Performance Results on 65/35 PE/Cotton Print Cloth (1% BOWF)

	Magnasoft HWS hydrophilic softener	Competitive Product	Untreated
Softness ⁽¹⁾	5.3	4	2
Wettability (s)	6.6	5.0	33.2
Whiteness (initial)	91.9	–	91.27
Whiteness (scorched)	79.16	–	79.81

(1) Softness was rated by a hand panel of 5 people. 6 = very soft, 1 = harsh.

Patent Status

Standard copy to come

Product Safety, Handling and Storage

Standard copy to come

Limitations

Standard copy to come

Contact Information

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](https://www.momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR

OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Magnasoft is a trademark of Momentive Performance Materials Inc.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.