

Magnasoft* Plus

Magnasoft* Plus

Description

Magnasoft Plus textile softener is a specially engineered, low-aminocontaining, silicone fluid designed to maximize the soft, silky, full handle desired from conventional amino-modified silicone fluids but with significantly less yellowing.

Emulsions prepared from Magnasoft Plus textile softener fluid impart superior softness compared to conventional silicones when applied to 100% cotton knits and wovens, polyester/cotton blends, rayon, prints, and a variety of other fabrics, with and without durable press resin.

Typical Physical Properties

Form	Liquid
Color	Water white
Percent Actives	100
Viscosity at 25°C, cSt	4000
Specific Gravity, 25/25°C	0.97
Flash Point, Pensky-Martens Closed Cup, °C (°F)	>66 (>150)

Processing Recommendations

Whiteness

The following are examples of the superior low-yellowing performance of Magnasoft Plus textile softener fluid relative to competitive aminosilicones on 100% cotton printcloth, 65/35 = polyester/cotton, 100% rayon and 100% cotton knit fabrics, both initially and after accelerated scorching. Magnasoft Plus textile softener fluid exhibited superior softness on all fabrics.

Non-Yellowing Performance of Magnasoft Plus Textile Softener Fluid vs Competitive Aminosilicone Emulsion

Pad Bath Composition	Parts by Weight		
	1	2	3
DMDHEU Resin (38%)	15.00	15.00	15.00
Mg Cl ² •6HOH Resin Catalyst (64%)	2.25	2.25	2.25
Competitive Aminosilicone Emulsion (20%)	—	5.00	—
Magnasoft Plus Emulsion (40%)	—	—	2.50
Water	82.75	77.75	80.25
Silicone Solids Add-on (100% wet pick-up), %	—	1.0	1.0
Dry/Cure at 171°C (340°F), min	1.5	1.5	1.5
Reflectance Data(1)	Scorched, 200°C		
	Initial	50 sec	100 sec
100% Cotton Printcloth			
Resin Only	74	58	46
Competitive Aminosilicone	58	38	30
Magnasoft Plus Textile Softener	70	54	41
65/35 = Polyester/Cotton Broadcloth			
Resin Only	74	66	57
Competitive Aminosilicone	58	47	38
Magnasoft Plus Textile Softener	69	60	55

(1) Reflectance was determined with a “Colorquest” Spectrocolorimeter; higher values indicate whiter fabrics

Softness and Whiteness

The data presented below demonstrate the superior softness and whiteness provided by Magnasoft Plus textile softener fluid compared to competitive silicone emulsions on a variety of fabrics.

Softness/Whiteness of Fabrics Treated with Magnasoft Plus Textile Softener Fluid vs Competitive Silicone Emulsions

100% Cotton Knit, Style 459			
Model Formulation			Parts by Weight
Silicone Emulsion (35%)			3.36
Distilled Water			96.64
Wet Pick-up, wt %		85	
Silicone Solids on Fabric, wt %		1.0	
Dry/Cure at 171°C (340°F), min		2	
Performance	Competitive Emulsion #1	Magnasoft Plus Textile Softener Fluid	Water Only
Softness Ranking ⁽¹⁾	4	1	10
Whiteness ⁽²⁾			
Initial	74	74	73
100 sec at 200°C (392°F)	46	50	58

(1) 1 = Softest, 10 = Harshesht

(2) "Colorquest" Spectrocolorimeter; higher values indicate whiter fabrics

100% Cotton Knit, Style 459

Model Formulation			Parts by Weight
Silicone Emulsion (20%)			5.88
Water			94.12
Wet Pick-up, wt %		85	
Silicone Solids on Fabric, wt %		1.0	
Dry/Cure at 171°C (340°F), min		2	
Performance	Competitive Emulsion #1	Magnasoft Plus Softener Fluid	Textile Water Only
Softness Ranking ⁽¹⁾	3	1	10
Whiteness ⁽²⁾			
Initial	77	78	74
100 sec at 200°C (392°F)	41	45	45

(1) 1 = Softest, 10 = Harshesht

(2) "Colorquest" Spectrocolorimeter; higher values indicate whiter fabrics

65/35 = Polyester/Cotton Broadcloth and 100% Cotton Printcloth

Model Formulation			Parts by Weight
DMDHEU Resin (38%)			15.00
MgCl ₂ •6HOH Catalyst (64%)			2.25
Silicone Emulsion (20%)			5.88
Water			76.87
Wet Pick-up, wt %		85	
Silicone Solids on Fabric, wt %		1.0	
Dry/Cure at 171°C (340°F), min		1.5	
Performance	Competitive Emulsion #1	Magnasoft Plus Textile Softener Fluid	Water Only
Softness Ranking ⁽¹⁾			
65/35 = PE/C Broadcloth ⁽²⁾	3	1	5
100% Cotton Printcloth ⁽³⁾	2	1	5
Whiteness ⁽⁴⁾			
65/35 = PE/C Broadcloth			
Initial	73	74	78
100 sec at 200°C (392°F)	60	62	67
100% Cotton Printcloth			
Initial	73	73	78
100 sec at 200°C (392°F)	53	53	57

(1) 1 = Softest, 5 = Harshesht

(2) Style 7409

(3) Style 400M

(4) "Colorquest" Spectrocolorimeter; higher values indicate whiter fabrics

100% Rayon Woven

Model Formulation		Parts by Weight
DMDHEU Resin (38%)		15.00
MgCl ₂ •6HOH Catalyst (64%)		2.25
Silicone Emulsion (20%)		5.88
Water		76.87
Wet Pick-up, wt %	85	
Dry/Cure Cycle		
Dry at 250°F, min	4	
Cure at 325°F, min	1.5	
Silicone Solids Add-on, %	1.0	
Softness Ranking ⁽¹⁾		
Magnasoft Plus Textile Softener Fluid	1	
Competitive Silicone Emulsion #2	3	
Untreated Control	10	

(1) 1 = Softest, 10 = Harshesht

Preparation of Milky Emulsions

When it is desirable to formulate a proprietary emulsion based on Magnasoft Plus textile softener fluid, the following model formulations and emulsification procedure are suggested as starting points. Depending on available emulsification equipment, the formulations and procedure may need to be modified.

Model Formulations

Ingredients	Weight Percent		
	A	B	C
Magnasoft Plus Textile Softener Fluid	20.0	20.0	30.0
"Tergitol" Surfactant TMN-6 ⁽¹⁾	3.0	4.0	3.3
"Tergitol" Surfactant 15-S-7 ⁽¹⁾	2.0	—	—
"Neodol" 91-6 ⁽²⁾	—	—	2.1
Initial Water #1	4.0	4.0	7.5
Initial Water #2	4.0	4.0	—
Initial Water #3	10.0	10.0	—
Final Water	57.0	57.1	46.0
Sodium Acetate (10% solution)	—	0.5	0.5
Glacial Acetic Acid	—	0.4	0.6

(1) Dow Chemical

(2) Shell Chemical Company

Emulsification Procedure

1. Charge Magnasoft Plus textile softener fluid and emulsifier(s) to a suitable vessel and mix at ~300 RPM for approximately two minutes.
2. Slowly add Water #1 and stir for 10 minutes.
3. Slowly add Water #2 and stir for 10 minutes.

4. Slowly add Water #3 (when present) and stir for 10 minutes.
5. Slowly add Final Water and stir for five minutes.
6. Slowly add Glacial Acetic Acid (when present) and stir for five minutes.
7. Slowly add Sodium Acetate solution (when present) and stir for five minutes.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Magnasoft is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.