

Niax* catalyst A-33

Niax* catalyst A-33

Description

Niax catalyst A-33 imparts a high level of activity and good physical properties to flexible foam systems. Optimum performance of this catalyst can be achieved when it is used in conjunction with Niax catalyst E-A-1 or Niax catalyst A-10 in flexible foam formulations.

Typical Physical Properties

Specific Gravity at 20°C (68°F)	1.033
Average Weight per Gallon, lb	8.59
Viscosity, cP	
at 0°F (-17.8°C)	7000
at 36°F (2.2°C)	700
at 75°F (23.9°C)	100
Solubility at 20°C (68°F)	
in Water	Infinite
in Urethane-Grade Polyol	Completely miscible
in Fluorocarbon Polyol	50% by wt
Vapor Pressure, mm Hg	
at 100°F (37.8°C)	2
at 200°F (93.3°C)	17
at 300°F (148.9°C)	65
Flash Point, Pensky-Martens Closed Cup ⁽¹⁾ , °C (°F)	88 (190)
Storage Life	Unlimited in enclosed container

(1) ASTM D 93

Processing Recommendations

Niax catalyst A-33 was evaluated using bench foam techniques. The effects of varying tin at constant amine and varying amine at constant tin were both evaluated. The ranges of tin and amine concentrations were well within the “operating range” of each. The dependent variables measured were: reactivity, top collapse, height of rise, breathability, density, cell count, and foam hardness (IFDs). Top and bottom gradients for breathability and density were defined.

Table 1 shows the foam screening formulation and foaming conditions. Table 2 provides evaluations of the foams produced at various tin and amine levels using Niax catalyst A-33 and a Niax catalyst A-10/Niax catalyst A-33 blend.

Table 1: Test Foam Formulation and Foaming Conditions

Foam Formulation	Parts by Wt
3000 MW EO/PO Polyol	100.0
CFC-11 Blowing Agent	5.0
Methylene Chloride	3.0
Water	4.5
Amine Catalyst	Varied
Niax Silicone L-580	1.5
Stannous Octoate, D-19	Varied
Toluene Diisocyanate (TDI), 80:20	
Index	114
Parts	59.7
Bench Foaming Conditions	
Polyol Charge, g	600
Mixing Speed, rpm	2700
Box Size, in	14 x 14
Oven Curing Temperature, °C (°F)	125 (257)
Oven Curing Time, min	10

Table 2: Properties of Foam with Niax Catalyst A-33

	Niax Catalyst A-33					Niax Catalyst A-10/A-33 ⁽¹⁾				
Amine Level	0.26	0.26	0.26	0.21	0.31	0.25	0.25	0.25	0.20	0.30
D-19 Level	0.22	0.25	0.28	0.25	0.25	0.22	0.25	0.28	0.25	0.25
Polyol Temperature, °F (°C)	74 (23.3)					74 (23.3)				
Cream Time, sec	14	13	12	14	12	13	13	12	13	12
Rise Time, sec	101	96	93	102	92	102	97	93	102	92
Top Collapse, in	0.4	0.4	0.4	0.3	0.2	0.4	0.3	0.3	0.3	0.2
Height of Rise, in	13.0	13.0	13.2	13.0	13.1	13.0	13.0	13.4	13.1	13.2
Cells per in	45–50					45–50				
Breathability, SCFM										
Top	5.5	5.2	4.7	5.2	4.7	5.5	5.2	4.7	4.7	5.2
Middle	3.0	2.3	1.6	2.3	2.3	2.9	2.5	1.8	2.0	2.3
Bottom	0.9	0.7	0.6	0.7	0.7	0.8	0.7	0.6	0.7	0.7
Density, pcf										
Top	1.13	1.10	1.12	1.11	1.12	1.13	1.09	1.09	1.10	1.10
Middle	1.13	1.12	1.13	1.11	1.13	1.12	1.10	1.11	1.11	1.11
Bottom	1.25	1.24	1.23	1.23	1.24	1.23	1.20	1.21	1.21	1.21
IFD, 12 in x 12 in x 4 in, lb										
25%	30	28	31.5	29	28	28	31	32	32	30
65%	53	51	55	50	50	55	53	57	57	54

(1) 3/1 Blend

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as

to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Niax is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.