

## Niax\* catalyst A-400

### Description

Niax catalyst A-400 lets you reap the benefits of extended pour times and increased open foam. A liquid, watersoluble tertiary amine composition, Niax catalyst A-400 promotes the blowing reaction in the production of your molded polyurethane foams. As flexible as it is efficient, Niax catalyst A-400 may be added as a separate stream or blended with water or polyol for metering to the mixing head of the machine.

Niax catalyst A-400 delivers the bonus of delayed-action enhancement. Both Niax catalyst A-400 and Niax catalyst A-300 belong to a new class of delayed-action catalysts with unique properties that offer a wide variety of molders the benefit of delaying the reaction while they produce substantially more open foam.

### Key Features and Benefits

Niax catalyst A-400 provides a wealth of added values.

The "Momentive Performance Materials Difference" includes:

- Delayed blow reaction for extended pour times needed to produce complex parts.
- Considerable reduction in force-to-crush, indicating enhanced production of open foam when compared with competitive delayed-action catalysts.
- Much lower amine fugitivity.
- Far less corrosive to mild steel

### Typical Physical Properties

Specific Gravity at 25°C	1.115
Viscosity at 25°C, cP	140
Solubility in Water at 20°C	Complete
Flash Point, Pensky-Martens Closed Cup <sup>(1)</sup> , °C (°F)	>93 (>200)

(1) ASTM Test Method D93

### Potential Applications

Niax catalyst A-400 may be used in the production of automotive seating.

Please note that:

- The reaction profile of Niax catalyst A-400 is similar to that of Niax catalyst A-107
- The delayed-action feature is particularly useful in high-reactivity systems
- In a typical molded foam application, the delayed blowing produced by Niax catalyst A-400 should be used in combination with a gelation catalyst such as Niax catalyst A-33 or Niax catalyst A-300

**Performance Data**

Table 1 shows formulations that are typical of North American rapid-demold seating systems. The two in columns 1-4 are firmer, cushion-type formulations. The formulation in columns 5 and 6 is a softer seatback type.

Formulations in columns 1, 3 and 5 are catalyzed by Niax catalyst A-107 and in columns 2, 4 and 6 by Niax catalyst A-400. The surfactant used in all formulations is Niax silicone surfactant Y-10366 (RS-171).

Indications:

- Niax catalyst A-400 delays the onset of the blowing reaction in a manner similar to the other delayed-action blow catalyst but, in all three formulations, Niax catalyst A-400 produces more open foam, as evidenced by the lower force-to-crush values.
- The force-to-crush reduction is 48% to 59% in the firmer cushion formulations and 64% in the softer seatback formulation.
- At the same time, the foams made with Niax catalyst A-400 have equally good stability and green strength, as illustrated by the hot ILD values.

**Table 1: Niax Catalyst A-400 Performance in TDI-Based Foams**

Formulations	Parts by Wt					
Components	1	2	3	4	5	6
Polyether Polyol (OH# 36)	25.00	25.00	50.00	50.00	75.00	75.00
Polymer Polyol (OH# 22)	75.00	75.00	50.00	50.00	25.00	25.00
Diethanolamine	1.50	1.50	1.50	1.50	1.50	1.50
Water (total)	4.00	4.00	4.00	4.00	4.00	4.00
Niax Catalyst A-33	0.35	0.35	0.35	0.35	0.35	0.35
Niax Catalyst A-107	0.20	-	0.20	-	0.20	-
Niax Catalyst A-400	-	0.26	-	0.26	-	0.26
Niax Silicone Surfactant Y-10366 (RS-171)	1.20	1.20	1.20	1.20	1.20	1.20
TDI (80:20)	45.50	45.50	46.00	46.00	46.50	46.50
Isocyanate Index	98	98	98	98	98	98
<b>Foam Properties</b>						
Density, pcf (kg/m3)	2.2 (35)	2.2 (35)	2.2 (35)	2.2 (35)	2.2 (35)	2.2 (35)
Cream Time, sec	8	7	8	7	8	7
Exit Time, sec	30	30	30	30	30	30
Weight, g	316	313	316	314	313	314
FTC, N	933	487	775	321	501	181
Hot ILD, N	241	228	180	183	148	147

Table 2 shows formulations that typically are used in Europe.

Indications:

- Niax catalyst A-400 produces more open foam than the industrial standard delayed-action blow catalyst (Niax catalyst A-107) with equivalent stability (as illustrated by the vent collapse) and equivalent cure

**Table 2: Niax Catalyst A-400 Performance in TDI-Based Foams**

Formulations	Parts by Wt	
	1	2
Components		
Polyether Polyol (OH# 36)	67.00	67.00
Polymer Polyol (OH# 30)	33.00	33.00
Water (total)	4.00	4.00
Diethanolamine	1.50	1.50
Niax Silicone Surfactant Y-10366 (RS-171)	1.10	1.10
Niax Catalyst A-33	0.25	0.25
Niax Catalyst A-107	-	0.20
Niax Catalyst A-400	0.26	-
Foam Properties <sup>(1, 2)</sup>		
Index 90		
Cream Time, sec	6.5	6.5
Exit Time, sec	43-45	36-39
Foam Weight, g	509	507
F.T.C., N	675	837
Hot ILD, N	96	98
Foam Weight, g	491	480
F.T.C., N	549	745
Hot ILD, N	87	90
Foam Weight, g	479	474
F.T.C., N	491	695
Hot ILD, N	85	89
Index 105		
Vent collapse <sup>(3)</sup> , cm	0	0
Exit Time, sec	37	30
Foam Weight, g	408	376
Index 100		
Density, pcf (kg/m <sup>3</sup> )	2.0 (32)	2.0 (32)
Cream Time, sec	6.5	6.5
Exit Time, sec	45	38
Foam Weight, g	482	474
F.T.C., N	549	803
Hot ILD, N	96	96
Foam Weight, g	478	478
F.T.C., N	541	789
Hot ILD, N	97	96

- (1) F.T.C. is the force to indent at 50% an uncrushed cushion at 1 min. after demold.
- (2) Hot ILD is the force to indent at 50% a crushed cushion at 3 min. after demold.
- (3) Vent Collapse is measured using 4 x 1 mm vents.

Figure 1: Reduction in Force-to-Crush Properties Using Niax Catalyst A-400




Figure 1 shows the significant reduction in force-to-crush with Niax catalyst A-400 as a function of foam part weight at 90 index.

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Contact Information

For product prices, availability, or order placement, contact our customer service at [Momentive.com/Customerservice/](https://www.momentive.com/Customerservice/)

For literature and technical assistance, visit our website at: [www.momentive.com](https://www.momentive.com)

### DISCLAIMER:

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.**

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Niax is a trademark of Momentive Performance Materials Inc.1033

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**