

Niax* catalyst EF-700

Niax* catalyst EF-700

Description

Our Niax EF-series catalysts are liquid, low odor tertiary amines designed to minimize or eliminate amine emissions from foam. The non-volatile nature of these amines is the result of molecular design and high molecular weight. As such these amines are not expected to adversely affect typical foam physical properties.

Niax Catalyst EF-700 is an effective blow amine that can be used to control cream time during manufacture of polyurethane flexible foams. The first application considered for this blow catalyst was in automotive seat molded foams where interior fogging and emissions must be minimized. This new amine catalyst also may be a candidate for consideration in flexible slabstock applications where it can substitute for conventional, volatile, blow amine when emissions need to be reduced.

Key Features and Benefits

- Designed to minimize or eliminate amine emissions in automobile interiors
- Is easily metered in existing equipment
- Required use level is only about 20% greater than for Niax catalyst A-1
- No expected adverse effect on typical foam physical properties

Typical Physical Properties

Form	Liquid
Viscosity at 20°C, cSt	
Flash Point, Pensky-Martens Closed Cup (ASTM D 93), °C	99
Specific Gravity, 25°C	0.955
Freezing Point, °C	11

Processing Recommendations

Performance of Niax Catalyst EF-700 Compared to Niax Catalyst A-133

We have compared Niax catalyst EF-700 with a standard blow amine used in the manufacture of flexible

slabstock foams, Niax catalyst A-1. Most foamers use a more dilute version of Niax catalyst A-1, but for the sake of comparison we show how Niax catalyst EF-700 compares to this very potent catalyst. Results reported are based on the study performed. Actual results in application use may vary.


Table 1 below contains formulations and reaction parameters that describe the performance of Niax catalyst EF-700. Foams prepared in this comparative study were all water blown in order to more easily discern the comparison with Niax catalyst A-1. Standard mix procedures were used. Foams were made in 14" x 14" x 6" cake boxes. Height-of-rise was determined using sonar. Temperature was measured using a thin gauge, thermocouple inserted through the bottom of the cake box to a height of about two inches. Foams were made using 3, 4 and 5-phpp water. For each water level, Niax catalyst EF-700 is compared with Niax catalyst A-1 at two incrementally higher concentrations above that used for Niax catalyst A-1: (A-1 concentration + 0.009) and (A-1 concentration + 0.018). These incremental changes were chosen to enhance statistical evaluation.

Table 1: Comparison of Niax catalyst EF-700 and Niax catalyst A-1

3000MW Conventional Polyol	100	100	100	100	100	100	100	100	100
Water	3	3	3	4	4	4	5	5	5
Niax silicone L-635	1	1	1	1	1	1	1	1	1
Niax catalyst A-1	0.115			0.09			0.065		
Niax catalyst EF-700		0.124	0.133		0.099	0.108		0.076	0.083
Niax catalyst D-19	0.225	0.225	0.225	0.225	0.225	0.225	0.225	0.225	0.225
TDI Index	108	108	108	108	108	108	108	108	108
80/20 TDI	40.70	40.70	40.70	51.14	51.14	51.14	61.58	61.58	61.58
Max Rise, cm	17.1	17	17.5	18.5	18.2	18.5	19.5	17.9	18.1
Settle @ 5 minutes, cm	0.21	0.45	0.12	0.16	0.36	0.18	0.02	0.23	0.15
Settling, %	1.2	2.7	0.7	0.9	2	1	0.1	1.3	0.8
Tmax, °C	119.8	111.6	113.5	124.1	129.3	131	138.8	132.8	141.4
Blow Time (sec)	98.5	118.5	107.1	87.7	107.6	88.5	83	102.4	86.7
~Air Flow, CFM	3	7.6	2.8	2.8	7	6.1	3.7	7	6.5

Figure 1 depicts differences between maximum temperatures obtained in the 12" x 12" x 4" cake box. In each case the foams made with Niax catalyst EF-700 achieved at least the same exotherm, except in the case of 3-phpp water. It can be extrapolated that an increase in catalyst concentration of about 20% would have resulted in about equivalent maximum temperature.


Figure 1: Comparison of Maximum Temperature Achieve



Note: A-1 concentration = 0.115 phpp @ 3 phpp water, 0.09 phpp @ 4 phpp water, 0.065 phpp @ 5 phpp water

Another significant measure of catalyst performance is blow-off time. Note that the blow-off time achieved using Niax catalyst A-1 can be matched with Niax catalyst EF-700. Again it can be extrapolated that had the catalyst been increased by about 20% for the 3-phpp water foam equivalent blow off time would have been achieved.

Figure 2: Comparison of Blow-off time



Note: A-1 concentration = 0.115 phpp @ 3 phpp water, 0.09 phpp @ 4 phpp water, 0.065 phpp @ 5 phpp water

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](https://www.momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Niax is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.