

RTV142

Description

RTV142 one-component, ready-to-use adhesive sealant cures to a tough, durable, resilient silicone rubber on exposure to atmospheric moisture at room temperature. Methyl alcohol vapors are released from the sealant surface as a by-product of cure. These vapors have low odor and are non-corrosive to metals. An important property of RTV142 is its low volatility.

RTV142 sealant has a thixotropic paste consistency. This allows it to be applied to vertical and overhead surfaces without sagging. Since it utilizes a moisture cure system, RTV142 sealant should not be used in thicknesses of greater than 6mm ($\frac{1}{4}$ inch). When section depths exceed 6mm ($\frac{1}{4}$ inch), Momentive Performance Materials one-component, addition cure or two-component silicone rubber compounds are suggested.

Key Features and Benefits

- One-component product
- Room temperature cure
- Primerless adhesion to many substrates
- Low odor
- Non-corrosive to metals
- Low volatility
- Low temperature flexibility
- High temperature performance
- Excellent weatherability, ozone and chemical resistance

- Excellent electrical insulation properties

Typical Physical Properties

| Uncured Properties | RTV142 |
|---|---|
| Consistency | Paste |
| Color | White |
| Application Rate, g/min | 975 |
| Specific Gravity | 1.09 |
| Tack-Free Time, hours | 4 |
| Cured Properties ⁽¹⁾ | RTV142 |
| Mechanical: | |
| Tensile Strength, kg/cm ² (lb/in ²) | 38.5 (550) |
| Percent Elongation | 400 |
| Hardness, Shore A | 34 |
| Tear Strength, kg/cm (lb/in) ⁽⁵⁾ | 9 (50) |
| Shear Strength, kg/cm ² (lb/in ²) ⁽²⁾ | 21.0 (300) |
| Peel Strength, kg/cm (lb/in) ⁽³⁾ | 10.5 (60) |
| Total Weight Loss % ⁽⁴⁾ | 0.22 |
| Volatile Condensable Materials % ⁽⁴⁾ | 0.05 |
| % Linear Shrinkage ⁽⁵⁾ | < 1.0 |
| Electrical: ⁽⁵⁾ | |
| Dielectric Strength, Kv/mm (v/mil) | 20 (500) |
| Dielectric Constant @ 60 Hz | 2.8 |
| Dissipation Factor @ 60 Hz | 0.001 |
| Volume Resistivity, ohm-cm | 4.5 x 10 ¹⁵ |
| Thermal: ⁽⁵⁾ | |
| Continuous Operating Temperature Range °C (°F) | -60 to 204 (-75 to 400) |
| Coefficient of Expansion, cm/cm, °C (in/in, °F) | 2.7 x 10 ⁻⁴ (1.5 x 10 ⁻⁴) |
| Thermal Conductivity, W/mK (cal/sec/cm ² , °C/cm) | 0.21 (0.0005) |

- (1) Cure time 10 days @ 25°C (77°F)/50% RH.
- (2) At 100% cohesive failure.
- (3) At 100% cohesive failure using 1 in. x 8 in. stainless steel screen at 180 degree pull angle.
- (4) ASTM E595 Standard Test Method.
- (5) Information is provided for customer convenience. These properties are not tested on a routine basis.

Potential Applications

The non-corrosiveness to metals and low volatility of RTV142, as well as its paste consistency, make it well suited for critical electronic adhesive, gasketing and sealing applications where a high level of volatile condensable materials cannot be tolerated.

Patent Status

Standard copy to come

Product Safety, Handling and Storage

Standard copy to come

Processing Recommendations

Surface Preparation

RTV142 sealant will bond to many clean surfaces without the aid of primers. These surfaces typically include many metals, glass, ceramic, silicone rubber and some rigid plastics. These adhesive sealant products may also produce acceptable bonds to organic rubber and to some flexible plastics not containing fugitive plasticizers (those that migrate to the surface, impairing adhesion). An evaluation should be made to determine whether acceptable bond strength develops for each specific application. For difficult-to-bond substrates, use of a primer is suggested. Primers SS4004P, SS4044P and SS4179 are recommended for use with these sealants. Complete information and usage instructions for these primer products are contained in a separate product data sheet.

Where adhesion is required, surfaces should be thoroughly cleaned with a suitable solvent such as naphtha or methyl ethyl ketone (MEK) to remove dirt, oil and grease. The surface should be wiped dry before applying the adhesive sealant.

When solvents are used, proper safety precautions must be observed.

Application and Cure Time Cycle

RTV142 sealant can be applied directly to clean or primed substrates. Where broad surfaces are to be mated, the sealant should be applied in a thin diameter (less than $\frac{1}{4}$ inch diameter), bead or ribbon around the edge of the surface to be bonded.

The cure process begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the RTV. At 25°C (77°F) and 50% relative humidity, RTV142 sealant will form a surface skin which is tack-free to the touch in 4 hours. Once the tack-free skin has begun to form, further tooling of the adhesive sealant is not advisable.

Higher temperatures and humidity will accelerate the cure process: low temperatures and low humidity will slow the cure rate. Do not exceed 110°F when curing materials.

As the adhesive sealant cures, methyl alcohol vapors are released from the sealant surface.

A 3mm ($\frac{1}{8}$ in.) section of adhesive sealant will cure through in approximately 48 hours at 25°C (77°F) and 50% R.H. Since cure time increases with thickness, use of these adhesive sealants should be limited to section thicknesses of 6mm ($\frac{1}{4}$ in.) or less.

Bond Strength Development

In addition to the effects of temperature and relative humidity, development of maximum bond strength will depend on joint configuration, degree of confinement, sealant thickness and substrate porosity. Normally, sufficient bond strength will develop in 48 hours to permit handling of parts. Minimum stress should be applied to the bonded joint until full adhesion is developed. Eventually the adhesive strength of the bond will exceed the cohesive strength of the silicone rubber adhesive sealant itself. Always allow maximum cure time available for best results.

Packaging and Dispensing

RTV142 adhesive sealant is supplied in 6 oz. (nominal size) SEMCO® cartridges and is sold on a volume basis of 5.4 fluid ounces (160 ml) per cartridge.

The SEMCO cartridge is designed for use with a hand or air-operated sealant gun manufactured by the SEMCO Company.

Clean Up and Removal

Before curing, solvent systems such as naphtha or methyl ethyl ketone (MEK) are most effective. Refer to solvent use warnings in the section on surface preparation. After cure, selected chemical strippers which will remove the silicone rubber are available from the other manufacturers.

SEMCO is a registered trademark of the SEMCO Company.

Limitations

Standard copy to come

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392

Toll free*

+704 805 6946

Direct Number

Latin America

Brazil

+55 11 4534 9650

Direct Number

EMEAI- Europe, Middle East, Africa & India

Europe

+390510924300

Direct number

ASIA PACIFIC

China

800 820 0202

Toll free

+86 21 3860 4892

Direct number

| | | | |
|-------------------------|--|--|--|
| *All American countries | Mexico +52 55 2169 7670 Direct Number | India, Middle East & Africa + 91 44 71212207 Direct number* | Japan +81 3 5544 3111 Direct number |
| | | *All Middle Eastern countries, Africa, India, | Korea +82 2 6201 4600 |

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product,

service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.