

Silcat* RHE

Silcat* RHE

Description

Silcat RHE silane is a crosslinking system (silane, peroxide and catalyst) for the manufacture of crosslinked LDPE & LLDPE polyethylene LV & MV cables using the Monosil⁽¹⁾ one-step process. It provides excellent performance on equipment designed for Monosil technology.

(1) Maillefer SA and BICC Ltd.

Key Features and Benefits

- Silcat RHE silane can be used with a wide range of stabilized LLDPE polyethylene grades for optimum cost-effectiveness. This also applies for non-stabilized resin used in association with an antioxidant masterbatch
- A high onset temperature of the silane crosslinking agent improves process stability and minimizes pregrafted/crosslinked particles in the insulation layer

Typical Physical Properties

| | |
|--|--------------|
| Appearance | Clear liquid |
| Color | Light straw |
| Viscosity, mPa s (cP), @ 23°C ⁽¹⁾ | 2.2 |
| Specific Gravity, g/cm ³ , @ 23°C | 0.962 |
| Flash Point, Tag Closed Cup, ASTM D56-79, °C | 23 |

(1) Brookfield LV/60rpm

Potential Applications

Low- and medium-voltage power cables

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

Recommended Resins

Silcat RHE silane can be used whether with non-stabilized polyethylene resins and an antioxidant masterbatch or with stabilized cable grade resins.

Test carried out have shown that the following resins have given outstanding results:

- Exxon Escorene LLN 1004YB together with an antioxidant masterbatch
- BP 3000 series

Other recommended types are:

LDPE resin:

| | |
|-----------------------------|----------------------------------|
| - Melt index(190°C/2.16 kg) | 0.2 to 0.5 g/10 min. |
| - Density | 0.915 to 0.935 g/cm ³ |

LLDPE resin:

| | |
|-----------------------------|----------------------------------|
| - Melt index(190°C/2.16 kg) | 0.5 to 6 g/10 min. |
| - Density | 0.900 to 0.935 g/cm ³ |

Processing

Moisture content of the PE resin must be less than 200 ppm. In hot and humid countries pre-drying of the

resin at 70°C by means of an air desiccator is highly recommended.

Grafting: Optimum addition levels for a given application must be determined experimentally. Data collected on Nextrom extruders indicates that the dose levels of Silcat RHE silane should be between 0.8 and 1.3 wt %.

Temperature profile setting of the extruder:

| | |
|----------------|------------|
| - Barrel | 150-220°C |
| - Head and die | 230°C |
| - Screw | 70 to 90°C |

Crosslinking: Rate of cure is dependent upon time, temperature and thickness of the layer and available moisture. Sufficient crosslinking can be achieved by any of the following methods:

- Immersion in water at 80-90°C, or
- Exposure to low pressure steam at 105°C, or
- Exposure to steam at atmospheric pressure (i.e. a sauna at 100°C)

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silcat is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.