

## Silcat\* RHS

### Silcat\* RHS

#### Description

Silcat RHS silane is a specially formulated, multi-component crosslinking system (silane, peroxide, catalyst and antioxidants) for use in moisture crosslinking of stabilized polyethylene or ethylenecopolymers. It provides excellent performance on equipment designed for Monosil<sup>(1)</sup> technology. Silcat RHS silane can provide enhanced stability when shipped or stored at elevated temperatures.

(1) Maillefer SA and BICC Ltd.

#### Key Features and Benefits

Silcat RHS silane has the following advantages over traditional silane crosslinking systems:

- Improved stability provides a SADT of 78°C for safer shipping and storage. This feature is particularly important in warm climates or for international shipments where the lack of refrigeration/air conditioning may raise safety concerns.
- The Silcat RHS silane formulation may prevent premature crosslinking or may allow higher temperatures at the feed section of the extruder, resulting in faster melting of the resin, better homogenization, and improved grafting efficiency with higher output rates.

#### Typical Physical Properties

Appearance	Clear liquid
Color	Light yellow
Viscosity, mPa s (cP), @ 23°C <sup>(2)</sup>	2.5
Specific Gravity, g/cm <sup>3</sup> , @ 25°C	0.98
Flash Point, Tag Closed Cup, ASTM D56-79, °C	24

(2) Brookfield LV/60rpm

#### Potential Applications

Silcat RHS silane contains vinylsilane, peroxide, crosslinking catalysts and stabilizers in a ratio optimized for crosslinking stabilized polyethylene in commercially available one-step extrusion equipment. It is suited for

LV and MV cable extrusion.

**Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

**Product Safety, Handling and Storage**

NEVER STORE THIS PRODUCT ABOVE 55°C (131°F)!

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

**Processing Recommendations**

Moisture-cured cables produced with Silcat RHS silane by the Monosil process can meet the IEC 502 cable specification.

**Recommended Resins**

Silcat RHS silane must be used with stabilized polyethylene resins or non-stabilized resins in association with the appropriate masterbatch. Recommended types are:

**LDPE resin:**

- Melt index(190°C/2.16 kg)	0.2 to 3 g/10 min.
- Density	0.915 to 0.925 g/cm <sup>3</sup>

**LLDPE resin:**

- Melt index(190°C/2.16 kg)	2 to 6 g/10 min.
- Density	0.915 to 0.925 g/cm <sup>3</sup>

**Processing**

The moisture content of the compound must be less than 200 ppm. Pre-drying the compound at 70°C by means of an air desiccator is highly recommended.

Grafting: Optimum addition levels for a given application must be determined experimentally. Data collected

on Nextrom extruders indicate that the dose levels of Silcat RHS silane should be between 0.8 and 1.8% by weight.

Temperature profile setting of the extruder:

- Barrel	150/150/150/170/190/200/210°C
- Head and die	210/280°C
- Screw	80 to 100°C

Crosslinking: Rate of cure is dependent upon time, temperature and thickness of the layer and available moisture. Sufficient crosslinking can be achieved by any of the following methods:

- Immersion in water at 80-90°C, or
- Exposure to low pressure steam at 105°C, or
- Exposure to steam at atmospheric pressure (i.e. a sauna at 100°C)

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Contact Information

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](http://Momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### DISCLAIMER:

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other

document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Silcat is a trademark of Momentive Performance Materials Inc.1033

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**