

SilCool* TIG830SP

Description

TIG830SP is a silicone grease that provides high thermal conductivity and low thermal resistance. The workability of TIG830SP makes it a good candidate for screen-printing and dispensing processes, and its dielectric and thermal performance contribute to help solving heat dissipation challenges in a variety of electronic components and designs.

Key Features and Typical Benefits

- High thermal conductivity
- Low thermal resistance
- Thin bond lines
- Highly workable - excels in screen-printing and dispensing processes
- Wide operating temperature range (-40 °C ~ 150 °C)
- Minimal weight loss at elevated temperatures
- Minimal ionic impurities


Typical Physical Properties

Property	Unit	Value
Color		Gray paste
Thermal conductivity ⁽²⁾	W/m·k	4.1
Viscosity (23 °C)	Pa·s	300
Penetration ⁽³⁾ (23 °C)		310
Specific Gravity (23 °C)		2.88
Bleed (150 °C, 24h)	wt%	0.0
Evaporation (150 °C, 24h)	wt%	0.3
Thermal Resistance ⁽¹⁾ (BLT 20 µm)	m m ² ·k/w	8
Volume Resistivity	Ω·cm	1.0 x 10 ¹²
Dielectric Strength	kV/0.25 mm	4.5
Volatile Siloxane (D ₄ -D ₁₀)	ppm	<100
Ionic Content (ppm)	Na ⁺	0.5
	K ⁺	0.0
	Cl ⁻	0.1

Typical properties are average data and should not be used as or to develop product specifications.

⁽¹⁾Laser lash analysis ⁽²⁾Hot wire method ⁽³⁾JIS K 2220


THERMAL RESISTANCE AND BLT



Note: Test data. Actual results may vary.

RELIABILITY DATA


THERMAL SHOCK RELIABILITY



Test method: Sandwich material between 10mmx10mm silicon die and AL, and apply 130kPa pressure. Cycle -55 to 125°C with dwell time of 10 minutes at each extreme and measure thermal resistance using the laser flash method.

Note: Test data. Actual test results may vary.

HIGH TEMPERATURE, HIGH HUMIDITY RELIABILITY



Test method: Sandwich material between 10mmx10mm silicon die and AL, and apply 130kPa pressure. Expose to high temperature and humidity (85°C, 85%RH) and measure thermal resistance using the laser flash method.

Note: Test data. Actual results may vary.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilCool is a trademark of Momentive Performance Materials Inc.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.