

## **SilForce™ SL6310 Thermal Solventless System – Catalyst**

### **Description**

SilForce SL6310 is a Pt-concentrate that can be used with our thermal solventless systems like SilForce SL6161, SL6961 or SL7061 as a Pt source. The SilForce SL6310 can also be used in combination with SilForce SL6600, SL6625 or other solventless pre-blends to increase the Pt-level. The SilForce SL6161, SL6961 or SL7061 system can improve the productivity, mainly on glassine and PE coated papers.

### **Product References**

SilForce SL6161 Base polymer with inhibitor  
SilForce SL4320 Cross-linker for filmic substrates  
SilForce SL6310 Platinum catalyst concentrate

### **Key Features and Typical Benefits**

#### **SilForce SL6310**

- SilForce SL6310: Concentrated catalyst outside of the pre-blends

#### **SilForce SL6161-system: Base polymer pre-blend**

- Versatile system for all release liners (papers & films)
- New technology suitable for lower temperature curing
- New generation of inhibitor for fast system
- High flexibility in terms of formulations

- Enhanced cross-linkers available for good anchorage of the release coating on several substrates
- Productivity gain in terms of machine capacity

### Typical Physical Properties

Property	Value
Viscosity, cps, 25 °C	180 - 300
Density, g/ml	ca. 0.97

Typical properties are average data and are not to be used as or to develop specifications.

### Potential Applications

SilForce SL6310 used in combination with the SilForce SL6161 and a cross-linker can be applied by any of the methods now being used commercially for solventless (and solvent based) silicone release coatings. These include three rolls differential offset gravure and various multiple smooth rolls configurations. Heat should be applied immediately after coating to initiate cure. Best results are obtained with zoned ovens. Operating the first oven zone at 95-115 °C will allow the coating to level, forming a continuous film before cure is initiated. Subsequent oven zones should be sufficiently high to achieve the required web exit temperature. Actual temperatures required for complete cure will be highly dependent on the performance of the oven and machine conditions. In general, minimum web temperature must be maintained a finite time (= dwell time) to obtain complete cure the time being dependent on oven length and the line speed.

### General Considerations for Use

#### Typical Storage Formulation

#### Important Note:

The suggested starting formulation in the tables is based on cure optimization. Destabilized (high) release may occur with some adhesives, solution acrylics in particular, at the suggested cross-linker levels. Please contact a Momentive Performance Materials Technical Representative for further information and guidance.

**Table 1: Typical starting formulations for glassine papers at a catalyst level of 50 ppm**

Component	0% CRA	5% CRA	10% CRA
SilForce SL6161	99	94	89
SilForce SL6031	-	5	10
SilForce SL4320	3.5	3.8	4.1
SilForce SL6310	1	1	1

### Bath Life

The working life of an activated bath will vary depending on ambient conditions. In general, the suggested formulation in the table will have a minimum bath life of 4 hours. The thin film bath life of SilForce SL6161 system is significantly shorter than the thin film life of the SilForce SL6600, SilForce SL6625 etc. systems.

### Bath Preparation

To ensure consistent results and maximize bath life, components should be mixed in the following order:

1. Weigh and add SilForce SL6161 to a clean, rust-free container/mixing vessel
2. Weigh and add the cross-linker (SilForce SL4320) to the above material
3. Agitate thoroughly
4. Weigh and add the platinum concentrate (SilForce SL6310) to above mix
5. Agitate thoroughly for 10-15 minutes to ensure homogeneity

Bath should be prepared just prior to use.

### Coating Weight/Substrates

SilForce SL6310 used in combination with the SilForce SL6161 and SL6600(E) systems is suitable for a variety of papers. These include supercalendered kraft, glassine, clay coated kraft, etc. The optimal coat weight will depend on the hold out and resolution of the surface, but generally 0.8-1.6 g/m<sup>2</sup> will provide a continuous silicone film. Coat weights can be determined by X-Ray Fluorescence. For machine trials, a simple, inexpensive method to calculate coat weight is available from Momenitive

## Performance Materials.

### **FDA Status**

SilForce SL6310 used in combination with the SilForce SL6161 systems comply with FDA regulations 175.105, adhesives, 175.320, resinous and polymeric coatings for polyolefin films 176.170, components of paper and paperboard in contact with aqueous and fatty foods, and 176.180, components of paper and paperboard in contact with dry foods.

### **Availability**

The SilForce SL6310 system may be ordered from Momentive Performance Materials Sales office nearest you or an authorized Momentive Performance Materials product distributor.

### **Containers**

5 kg pail

25 kg pail

### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information

provided by the manufacturer of such other materials.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

<b>Americas</b>	<b>Latin America</b>	<b>EMEA- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
<b>+1 800 295 2392</b> Toll free* <b>+704 805 6946</b> Direct Number	<b>Brazil</b> <b>+55 11 4534 9650</b> Direct Number	<b>Europe</b> <b>+390510924300</b> Direct number	<b>China</b> <b>800 820 0202</b> Toll free <b>+86 21 3860 4892</b> Direct number
<b>*All American countries</b>	<b>Mexico</b> <b>+52 55 2169 7670</b> Direct Number	<b>India, Middle East &amp; Africa</b> <b>+ 91 44 71212207</b> Direct number* <b>*All Middle Eastern countries, Africa, India,</b>	<b>Japan</b> <b>+81 3 5544 3111</b> Direct number  <b>Korea</b> <b>+82 2 6201 4600</b>

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### DISCLAIMER:

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR**

**OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.