

SilForce™ SS6800 Silicone Solution

Description

SilForce SS6800 is a silicone solution that utilizes a platinum catalyzed addition cure, being cross-linked by XC94-C4326 catalyst with SHF-475 as the cross-linker. It is used for coating on PEK paper, foils and plastic substrates.

Key Features and Typical Benefits

- Low temperature/high speed cure
- Low release of various adhesives
- Excellent subsequent adhesion
- Non-blocking
- General type

Typical Physical Properties (uncured)

| | |
|-----------------------------|------------------------|
| Appearance | Colorless, transparent |
| Silicone Solid, % | 30 |
| Viscosity (25 °C) Pa·s (cP) | 15 (15000) |
| Specific Gravity (25 °C) | 0.9 |
| Solvent | Toluene/Xylene |

Typical Physical Properties (cured)

| | |
|---|----|
| Release Force ⁽¹⁾ (0.3m/min) N/2.5m (gf/2.5cm) | 14 |
| Subsequent Adhesion Force % ⁽¹⁾ | 90 |
| Cure Time (Tack Free, 90 °C) s | 10 |

Typical properties are average data and are not to be used as or to develop specifications.

Potential Applications

- Release sheets for wallpaper, labels
- Release films
- Release papers for double-sided tape
- Water-repellent finishing for papers and fibers

⁽¹⁾ Test Conditions

1. Evaluation of Release Force

1-1. Preparation of silicone coated paper

Formulation. SilForce SS6800: SHF-475: XC94-C4326 =
100: 1.35: 1 (by weight)

Base sheet Polyethylene-laminated paper (75g/m²)

Coating weight of silicone. 0.3g/m² (dry)

Cure condition 30s at 140 °C

Aging condition. 1 day at 25 °C, 50%RH

1-2. Test tape

Tape Tesa 7475

Aging condition. 1 day at 70 °C, 50%RH

2. Evaluation of subsequent adhesion force

Test tape Nitto 31B

Aging condition. 20h at 70 °C

General Considerations for Use

PREPARATION OF COATING BATH

Dilute SilForce SS6800 to desired silicone concentration with solvent and stir until completely dissolved. Add the required amount of SHF-475 crosslinker and XC94-C4326 catalyst agent, then mix thoroughly.

Typical Formulation (for 5% silicone content)

| | |
|---------------------------------|-----------------------|
| SilForce SS6800. | 100 (weight parts) |
| Toluene (solvent) | 497.65 (weight parts) |
| SHF-475 (Crosslinker) | 1.35 (weight parts) |
| XC94-C4326 (catalyst). | 1 (weight parts) |
| Total | 600 (weight parts) |

Cure speed is dependent upon the amount of catalyst added and temperature. A preliminary test is recommended.

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

Notes

- SilForce SS6800 is an addition cure type. Proper care should be taken to ensure that catalytic poisons such as amines, sulfur, organic tin compounds, etc. are not mixed in the coating bath.

Current Packaging

Currently available in 18kg pail and 180kg drum.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers)

may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

| Americas | Latin America | EMEAI- Europe, Middle East, Africa & India | ASIA PACIFIC |
|--------------------------------|--|--|--|
| +1 800 295 2392 Toll free* | Brazil +55 11 4534 9650 Direct Number | Europe +390510924300 Direct number | China 800 820 0202 Toll free +86 21 3860 4892 Direct number |
| +704 805 6946 Direct Number | Mexico +52 55 2169 7670 Direct Number | India, Middle East & Africa + 91 44 71212207 Direct number* | Japan +81 3 5544 3111 Direct number |
| *All American countries | | *All Middle Eastern countries, Africa, India, | Korea +82 2 6201 4600 |

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS

OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.