

SilForce™ UV9400 Release Coating

SilForce* UV9400 Release Coating

Description

SilForce UV9400 release coating is a cycloaliphatic epoxy-functional linear polydimethylsiloxane polymer developed for photocurable release coating applications. UV9400 is blended with UV9380C or UV9390C photocatalyst prior to use, and is then applied to plastic or paper substrates using standard solvent-free silicone coating techniques. Catalyzed UV9400 coatings are rapidly crosslinked on exposure to focused ultraviolet light. The UV9400 polymer structure is designed to provide a highly crosslinked coating with minimal migration to PSA's laminated to cured UV9400 coatings. UV9400 provides easy release from most acrylic and rubber based pressure sensitive adhesives.

Key Features and Benefits

- Fast UV cure in air environment (inerting not required)
- Low temperature cure, ideal for thermally sensitive plastic and film liners
- Highly crosslinked coating, low silicone transfer
- Low, stable release from crosslinkable acrylic and SBR adhesives
- Flat Release Profile
- Nontoxic, low viscosity fluid easy to handle and use

PERFORMANCE

Properly coated and cured UV9400 release coatings provide easy, stable aged release from a wide variety of acrylic and SBR adhesives. Typical product performance is

displayed in Figures 1 and 2.

Figure 1





Figure 2



Typical Physical Properties

Property	UV9400 Polymer
Viscosity, 25° C	225 cstk
Solids*	> 99%
*(150° C weight loss)	
Epoxy Equivalent Weight (g/mole oxirane)	1700

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant

patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

UV9400, UV9380C and UV9390C will retain original properties for 12 months from date of shipment from Momentive Performance Materials when stored in original container at 25°C. Care must be taken to prevent inadvertent contamination by other chemicals including strong acids or bases, tin and titanium metal driers, water, amines and phosphorus compounds. UV9400 is not considered toxic, but best industrial hygiene practice is recommended for safe handling and use of the polymer, including eye protection and protective clothing to minimize skin contact.

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

BATH PREPARATION AND USE

100 parts of Silforce UV9400 are thoroughly mixed with 1 to 3 parts of UV9380C or UV9390C prior to use. In general, 1-2 parts of photocatalyst are recommended for film and plastic substrates, and 2-4 parts catalyst are needed for good cure on paper and glassine liners. At least 10 minutes' vigorous agitation is recommended to thoroughly disperse photocatalyst in UV9400. The catalyzed bath will appear hazy because the active iodonium ingredient of UV9380C is not completely miscible in UV9400 polymer, but the bath is sufficiently stable to permit at least a day's use without further agitation.

If a catalysed bath is allowed to stand undisturbed for more than a day, some catalyst will be observed to settle out of the mixture, necessitating thorough remixing before reuse. Properly cured coatings of UV9400/UV9380C will provide easy release from most acrylic and SBR adhesives. Differential release can be achieved by blending UV9400 with UV9430 controlled release polymer.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Availability

The products are available in the following containers:

Product	1 Gal	5 Gal	55 Gal
UV9400	---	18.2 kg (40 lbs)	182 kg (400 lbs)
UV9380c		3.64 kg (8 lbs)	18.2 kg (40 lbs)

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number

***All Middle Eastern Korea**
countries, Africa, India, +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.