

## **SilFORT FHC620 Formable Clear Coat with SilFORT SHP470FT2050 Primer**

### **Description**

SilFORT FHC620 formable clear coat is a thermally cured siloxane clear coating for use on various types and grades of polycarbonate (PC). When applied over SilFORT SHP470FT2050 primer (sold separately), it helps provide good abrasion and chemical resistance, as well as protection from natural weathering, to PC. SilFORT FHC620 formable clear coat can be applied and pre-cured on 2D PC sheeting and then final cured during the thermoforming of the sheeting into 3D PC parts, which enables more flexibility and efficiency in the production of such 3D parts while still providing the desired protection.

### **Key Features and Typical Benefits**

- Excellent 3D formability
- Excellent clarity
- Excellent abrasion and mar resistance
- Excellent solvent/chemical resistance
- Excellent adhesion to many grades of PC
- Easy to clean surface

### **Typical Physical Properties SilFORT SHP470FT2050 primer**

<b>Property</b>	<b>Unit</b>	<b>Typical Value</b>
Solids Content	%	9

Viscosity (at 25 °C)	cSt	85
Density (at 25 °C)	g/cm <sup>3</sup>	0.95
Shelf Life <sup>(1)</sup>	Months	48

(1) From date of manufacturing, in original unopened container at < 43 °C.

### SilFORT FHC620 formable clear coat

Property	Unit	Typical Value
Solids Content	%	22
pH	-	5.8
Viscosity (at 25 °C)	cSt	5.5
Density (at 25 °C)	g/cm <sup>3</sup>	0.985
Shelf Life <sup>(2)</sup>	Months	6

(2) From date of manufacturing, in original unopened container at <10 °C.

Typical properties are average data and are not to be used as or to develop specifications.

### Potential Applications

The combination of its formability and protective benefits makes SilFORT FHC620 formable clear coat an excellent candidate to consider for the coating of 3D thermoformed PC parts such as those produced for the automotive industry.

### General Considerations for Use

To promote adhesion of the clear coat to PC, the PC should first be primed with SilFORT SHP470FT2050 primer. The coating process consists of a pre-cure phase for the formable clear coat on 2D PC sheets, followed by a final-cure step during the forming operation of the PC-sheet into the desired 3D objects.

### Typical Coating Application (Pre-Cure Phase, sheet unformed)

	<b>SilFORT SHP470FT2050 primer</b>	<b>SilFORT FHC620 formable clear coat</b>
Application Methods	Flow, spray, dip, roller coating	Flow, spray, dip, roller coating
Reducing Solvents	1-Methoxy-2-propanol (CAS# 107-98-2) Diacetonalcohol (CAS# 123-42-2) <sup>(1)</sup>	1-Methoxy-2-propanol (CAS# 107-98-2) 2-Propanol (CAS# 67-63-0) <sup>(1)</sup>
Relative Humidity (application and ambient flash off)	Max. 50%	35 -55%
Room Temperature Flash Off	20 – 50 °C for 10 – 20 minutes <sup>(3)</sup>	23 – 27 °C for 10 – 20 min <sup>(2)</sup>
Thermal Pre-Cure	No (only tack-free)	60 °C for 60 min <sup>(3)</sup>
Thermoforming Temperatures	Typically between 150 and 180 °C during forming, depending upon customer specific requirements.	
Recommended Coating Thickness <sup>(4)</sup>	0.3 – 1.5 µm	3 – 8 µm

(1) Other compatible solvents may be considered.

(2) Tack-free time is depending on application method, sheet length and thickness.

(3) Total oven time in preheated convection oven. Typical sheet thickness of 6 mm.

(4) Refractive Index SilFORT SHP470FT2050 n = 1.53; SilFORT FHC620 n = 1.43.

### **Thermoforming of 3D PC Parts Resulting in Final Thermal Cure of Coating**

Typical thermoforming temperatures are between 150 and 180 °C during forming, depending upon 3D object specific requirements. The necessary temperatures, time and other conditions of thermoforming are dependent upon a series of factors including part dimensions, wall thickness, convection oven or IR-heater setup. One example of typical thermoforming conditions is 30 minutes at 175 °C for a PC sheet with thickness of 3 – 6 mm.

### **Packaging**

Currently available:  
25 kg Steel Pail with PE Liner.

### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### **Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### **Contact Information**

For product prices, availability, or order placement, contact our customer service at [Momentive.com/CustomerService/](http://Momentive.com/CustomerService/)

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### **DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS**

**OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SilFORT is a trademark of Momentive Performance Materials Inc.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**