

## SilFORT\* UVHC5000

### Description

SilFORT UVHC5000 is a clear, solvent based, UV-curing coating for use on polycarbonate parts to help protect against abrasion, chemical damage and degradation caused by ultraviolet radiation and weathering. It is an excellent candidate to consider for use on headlamp lenses for forward lighting, exterior/interior trim and exterior/interior polycarbonate sheets. It complies with the ECE automotive forward lighting regulations and is AMECA listed for five years exposure in Florida and Arizona.

### Key Features and Typical Benefits

- 5 year weatherability listing
- Improved resistance to microcracking
- Transparent
- Easy-to-clean properties
- High chemical resistance
- ECE and AMECA compliant
- Overspray can be recovered and re-used
- Application by spray, dip, roller and flow
- Adhesion to most plastics

### Typical Physical Properties

Property	Unit	Typical Value
Physical Form	-	Liquid
Appearance	-	Yellow
Solids Content	% by weight	approx. 45
Kinematic Viscosity (at 25 °C)	cSt	approx. 10

Density (at 25 °C)	g/cm <sup>3</sup>	approx. 1.01
Shelf Life <sup>(1)</sup>	Months	15

<sup>(1)</sup> From date of manufacturing, in original unopened container.

Typical properties are average data and are not to be used as or to develop specifications.

## Potential Applications

- Automotive Forward Headlight Lenses
- High Performance Sheets and Films

## General Considerations for Use

Application Method	Spray, flow, dip, roller coating, ink jetting
Reducing Solvents	1-methoxy-2-propanol (CAS#107-98-2) 2-Butanol (CAS#78-92-2) 2-Propanol (CAS#67-63-0) <sup>(2)</sup>
Relative Humidity (application and ambient flash off)	Max. 65%
Room Temperature Flash Off	20 - 30 °C for 1 - 3 minutes
Pre-heating	1.5 to 6 minutes to reach 65 - 95 °C parts surface temperature <sup>(3)(4)</sup>
Intermediate Cool Down	Optional
UV Cure	3 – 12 J/cm <sup>2</sup> UV-A (EIT Inc. Power Puck II Device) <sup>(5),(6)</sup>
Recommended Hardcoat Thickness <sup>(7)</sup>	8 - 16 μm
Recommended Thickness of Interpenetrating Layer	> 1 μm <sup>(8)</sup>

<sup>(2)</sup> Other compatible solvents may be considered.

<sup>(3)</sup> Longer pre-heating times may be required when using convection heating instead of IR-heating.

<sup>(4)</sup> Modified, high heat resistant PC grades may require higher pre-heat temperatures.

<sup>(5)</sup> Use of un-doped, medium pressure mercury arc lamps or microwave powered Hg lamps with > 80 W/cm power is recommended. Typical UV-irradiance is 0.2 to 0.6 W/cm<sup>2</sup>. 0.25 W/cm<sup>2</sup> or higher may be required to achieve desired adhesion results after harsh humidity cycles.

<sup>(6)</sup> For applications that mainly require chemical resistance against solvents such as ketones, SiIFORT UVHC5000 clear coat may be cured at a lower UV-dosage (1.5 J/cm<sup>2</sup>).

(7) Refractive Index  $n = 1.5$ .

(8) Higher thickness up to 6  $\mu\text{m}$  may further improve adhesion after harsh humidity cycles.

For best results in applying clear coat, filter the coating solution by combining a 5  $\mu\text{m}$  pre-filter, followed by a 1  $\mu\text{m}$  absolute gel-filter.

To help ensure adequate UV-cure, work with the UV-lamp supplier to select suitable UV-reflectors for the parts to be treated.

Do not expose product to any source of visible white light prior to UV-cure. To avoid exposure when white light is present, do not use semi-transparent pipework.

### **Packaging**

Currently available in:

25 kg Steel Pail with PE liner

180 kg Steel Drum with PE liner

25 kg (Pail)

181.6 kg Drum

### **Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information

provided by the manufacturer of such other materials.

### **Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### **Contact Information**

For product prices, availability, or order placement, contact our customer service at [Momentive.com/Customerservice/](https://www.momentive.com/Customerservice/)

For literature and technical assistance, visit our website at: [www.momentive.com](https://www.momentive.com)

### **DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under

end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SiIFORT is a trademark of Momentive Performance Materials Inc.

**Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.**