

Silplus* 60 CW

Heat Cured Elastomer

Description

Silplus 60 CW is a heat cured silicone rubber base compound. It is an excellent candidate to consider for use in the cable and wire industry.

Key Features and Typical Benefits

- excellent processing (high green strength)
- good mechanical profile
- very good electrical properties
- enhanced high temperature resistance

Typical Physical Properties

Typical Properties of the Uncured Base Compound			
Appearance			Translucent
Density	DIN 53 479 A	g/cm ³	1.20
Mooney Viscosity	DIN 53 523		
ML (4) 25°C		ME	58
Δ ML 0/ML4			≤20

Typical Properties of the Vulcanized Rubber			
100 (pbw) Silplus 60 CW heat cured silicone with 1.5 pbw bis-(2,4-dichlorobenzoyl)-peroxide (50%). Vulcanization conditions: 10 min. @ 120°C.			
Hardness	DIN 53 505	Shore A	63
Tensile Strength	DIN 53 504 S2	N/mm ²	11
Elongation at Break	DIN 53 504 S2	%	500
Tear Strength	ASTM D 624 die B	N/mm	24
Volume Resistivity	DIN IEC 93	Ohm•cm	1•10 ¹⁵
Dielectric Strength	IEC 243-1	kV/mm	25
Dielectric Constant	IEC 250	(50 Hz)	3.1
Dissipation Factor	IEC 250	(tan delta/1000 Hz)	2.6•10 ⁻⁴

Typical properties are average data and are not to be used as or to develop specifications.

Attention:

Using a peroxide other than bis-(2,4-dichlorobenzoyl)-peroxide (50%), might result in different mechanical properties.

Diacyl-peroxides like Di(2,4-dichlorobenzoyl)peroxide are non vinyl specific cross link peroxides (higher cross link density).

Diaryl-peroxides like Dicumylperoxide or Dialky-peroxides like 2,5-Dimethyl-2,5-di(tert. butylperoxy)hexane are vinyl specific cross link peroxides (lower cross link density).

Processing Recommendations

Various organic peroxides will vulcanize the compounding bases. Fabricators should select a curing agent based on the method of fabrication, desired properties and safety considerations. They are mixed into the rubber on a two-roll-mill, together with additives if necessary.

If the goods are to be vulcanized without pressure, e.g. in hot air or in an infrared radiation tunnel, bis-2,4-dichlorobenzoyl-peroxide (50%) is usually recommended. The dosage ranges from 1-2 parts (pbw) of cross-linking agent on 100 parts (pbw) of base compound. Good results have been achieved with a dosage of 1.5 parts (pbw). While

the cross-linking agent is being incorporated, the temperature of the compound should not exceed 40°C to avoid scorch. Therefore the rolls of the mixing mill should always be well cooled.

Regulatory Compliance

- Listed as UL 94 HB (file No. E205753)

Packaging

Silplus 60 CW heat cured silicone is available in 500 kg boxes.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at [Momentive.com/Customerservice/](https://www.momentive.com/Customerservice/)

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Silplus is a trademark of Momentive Performance Materials Inc.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.