

SiI TRUST™ SP100 Adhesive

High Strength and Elongation, Adhesive Sealant

Description

SiI TRUST SP100 is a one-component, fast cure, non-corrosive silicone adhesive sealant that cures on exposure to atmospheric moisture to form an elastic silicone rubber. SiI TRUST SP100 has a thixotropic paste consistency and excellent corrosion-free adhesion to metals, including copper, plastics, glass without the use of primers.

Key Features and Typical Benefits

- Fast room temperature cure, and neutral alkoxy cure type
- High strength and high elongation
- Excellent adhesion after extended aging, and excellent dielectric properties
- Wide operating temperature range from -50 to +200 °C
- Flame retardant : UL94HB recognized (File No.E56745 and E473056)

Typical Physical Properties

(JIS K 6249)

Property	Unit	Value
Uncured Properties (23 °C, 50%RH)		
Available Colors		White, Black
Tack-Free time	min	20
Cured Properties (7 days at 23 °C, 50%RH)		
Appearance		Elastic rubber
Density	g/cm ³	1.42
Hardness (Type A)		34
Tensile Strength	MPa	2.3
Elongation	%	650
Adhesive Strength ⁽¹⁾	MPa	1.9
Thermal Conductivity ⁽²⁾	W/m-K	0.38
Linear Expansion ⁽³⁾	1/K	2.0 x 10 ⁻⁴
Volume Resistivity	MΩ·m	5.0 x 10 ⁶
Dielectric Strength	kV/mm	20
Dielectric Constant (60Hz)		4.0
Dissipation Factor (60Hz)		0.04

Typical physical properties are average data and should not be used as or to develop product specifications.

⁽¹⁾Aluminum lap shear

⁽²⁾In-house test method

⁽³⁾In-house test method


Adhesion Performance

SiITRUST SP100-W has excellent bonding properties and adheres to many materials without primers.

<u>Materials</u>	<u>SP100-W</u>
Aluminum	O
Glass	O
Stainless Steel	O
Copper	O
Mild Steel	O
Zinc Plate	O
Nickel Plate	O
Acrylic Resin	O
Polyester	O
Epoxy Resin	O
Polycarbonate	O
ABS	O
PBT (Polybutylene terephtharate)	O
PPS (Polyphenylene sulfide)	O
PET (Polyethylene terephtharate)	O
PPE (Polyphenylene ether)	O
Modified PPO	O
Phenolic Resin	O
Nylon-6	O
Nylon-66	O
PVC (Polyvinyl chloride)	O
PE (Polyethylene)	X
PP (Polypropylene)	X

Note: Test results. Actual data may vary.
 O: Adhere completely (Cohesive failure)
 X: Does not adhere

Cure Performance



Note: Test data. Actual results may vary.

General Instructions for Use

- Substrate surface should be thoroughly cleaned with a suitable solvent such as alcohol, xylene, methyl ethyl ketone (MEK) etc.
- Wear eye protection and protective gloves as required while handling.
- Adequate ventilation must be maintained in the work place at all times.
- General adhesive for metals, glass, plastics, etc.
- Certain plastics may require surface treatments such as plasma or liquid primers to achieve best adhesion levels.

Packaging

- 333 ml cartridge in case of 10
- 25 kg pail
- 250 kg drum

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		*All Middle Eastern countries, Africa, India,	Korea
			+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SiiTRUST™ is a trademark of Momentive Performance Materials Inc.

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.