

Silwet* L-77 Ag spray adjuvant

Description


Silwet L-77 Ag spray adjuvant is a superspreading surfactant based on a trisiloxane ethoxylate. Silwet L-77 Ag spray adjuvant lowers the surface tension of spray solutions, beyond that which is achievable with conventional adjuvants.

Typically, Silwet L-77 Ag spray adjuvant (@ 0.1 wt %) gives an aqueous surface tension of 20.5 mN/m. On the other hand, an octylphenol ethoxylate containing 10 EO units (a commonly used nonionic surfactant) at 1.0 wt % gives a surface tension of only 30 mN/m.

The bottom line? Silwet L-77 Ag spray adjuvant helps lower the aqueous surface tension more effectively than conventional spray adjuvants.


Because Silwet L-77 Ag spray adjuvant is a superspreading surfactant, the contact angle of spray solutions on leaf surfaces is reduced, leading to an increase in spray coverage (Figure 1).

Figure 1: Spreading



Additionally, under specific conditions, Silwet L-77 Ag spray adjuvant promotes rapid uptake of agrochemicals into plants via stomatal infiltration. Spray solutions taken into plants in this way become rainfast, thereby improving application reliability (Figure 2).

Figure 2: Uptake



Silwet L-77 Ag spray adjuvant is nonionic in nature, making it useful with a broad range of agrochemical formulations.

Key Features and Benefits

- Superspreader
- Promotes spray volume reduction
- Promotes rapid uptake of agrochemicals (rainfastness)
- Improves spray coverage
- Nonionic
- Meets requirements of EPA 40CFR§180.910

Typical Physical Properties

Surface Tension (0.1%, mN/m) ^(a)	20.5
Cloud Point (0.1 wt%), °C	<10
Viscosity, cPs @ 25°C	20
Specific Gravity @ 25/25°C	1.007
Flash Point, ^(b) °C	116

(a) Surface Tension by Wilhelmy Plate Method.

(b) Pensky-Martens Closed Cup, ASTM Method D93

Potential Applications

Silwet L-77 Ag spray adjuvant has been used successfully in spray applications globally. Typical applications include:

Application	Typical Use Rate ^(a)
Plant Growth Regulators	0.025% to 0.05%
Herbicide	0.025% to 0.15%
Insecticide	0.025% to 0.1%
Fungicide	0.015% to 0.05%
Fertilizers and Micronutrients	0.015% to 0.1%

(a) Note: use rates are dependent on crop, agrochemical and spray volume requirements.

Product Usage

In Agrochemical Formulations

Silwet L-77 Ag spray adjuvant may be used as a component in agrochemical formulations. Although organosilicone surfactants are subject to hydrolysis under acidic or basic conditions, optimum performance is achieved by buffering the formulation to pH 6.5 -7.5. Additionally, it is recommended that Silwet L-77 Ag spray adjuvant be used at a concentration of at least 5%, based on the total formulation.

As A Tank Mix Adjuvant

Silwet L-77 Ag spray adjuvant, when used as a tank-side adjuvant may be used to improve spray coverage, improve uptake or to allow for a reduction in spray volume. Silwet L-77 Ag spray adjuvant is most effective as a tank-side adjuvant when spray mixtures are 1) within a pH range of 5-8, and 2) used within 24 hours of preparation.

High spray volumes, coupled with high surfactant rates, are not required to achieve sufficient coverage with Silwet L-77 Ag spray adjuvant. In fact, Silwet L-77 Ag spray adjuvant may provide adequate coverage in many low volume spray applications at rates between 0.025% and 0.1%.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.