

XL-PEARL * 23 HDPE 40

XL-PEARL© 23 HDPE 40

Description

XL-PEarl 23 silane is specially developed for the manufacture of XL-PEarl masterbatches based on porous polymer carriers. The technology is described in EP 0 426 073 and US 5,112,919 patents. XL-PEarl 23 silane is designed for crosslinking high-density polyethylene (HDPE) "PEX" pipe using XL-PEarl silane or the Spherisil⁽¹⁾ one step process.

This product must be used in combination with a catalyst and antioxidant masterbatch such as (PEarlstab* C-13'000, PEarlstab S-12'000 or PEarlstab I-14'000). It is only available for licensees of XL-PEarl silane technology.

(1) Silon International GmbH

Key Features and Benefits

- XL-PEarl 23 silane is based on a unique peroxide and silane combination that provides high grafting efficiency.
- A high onset temperature of the XL-PEarl 23 silane ensures good process stability and minimizes pregrafted and crosslinked particles during extrusion.
- XL-PEarl 23 silane is particularly suitable for low-odor applications.
- XL-PEarl silane can also be used with a wide range of polyethylene grades, including LDPE, LLDPE, MDPE, HDPE and the new single site catalyst resins, for optimum cost-effectiveness.
- Pipes manufactured using XL-PEarl silane technology show excellent mechanical properties and outstanding chemical resistance.
- Use of the quality-controlled XL-PEarl silane system results in pipes with high quality surface finish.

Typical Physical Properties

Appearance	Clear liquid
Color	Colorless
Viscosity, mPa s (cP), @ 23°C	2.5
Specific Gravity, g/cm ³ , @ 23°C	0.970

Potential Applications

- Crosslinking of high-density polyethylene pipes for:
- Domestic hot and cold water distribution
- Under-floor heating
- Central and district heating
- Transport of gases, compressed air and fluids
- Industrial pipes

XL-PEARL 23 silane status under European and national food contact regulations on plastic materials
The silane component in XL-PEARL 23 silane is listed with ref PM nr 26328 in the EU Directive 90/128/EEC on plastics for use as food contact, with a maximum QM of 'residual' silane of 5 mg/kg (QM = maximum permitted quantity of the 'residual' substance in the food product).

A European reference for the peroxide ingredients is the German BgVV, Section XLVI. It allows the use of these peroxides for food contact applications in crosslinked PE, with the restriction that the total amount of decomposition products in the final resin does not exceed 0.2%.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

XL-PEARL 23 MB.indd_Processing Recommendations_Image1.JPG

A) Extrusion Process

Addition of a catalyst AO masterbatch is required (PEARLSTAB* C-13'000, PEARLSTAB S-12'000 or PEARLSTAB I-14'000). Moisture content of the polyethylene base resin must be less than 200 ppm. Pre-drying the polyethylene base resin as well as catalyst and AO masterbatches at 70°C (158°F) by means of an air desiccator is highly recommended.

Optimum addition levels for a given application must be determined experimentally and depend on the properties (MFI and density) of the polyethylene resin used in production.

Recommended Resins Are:

Type of HDPE resin:

MeltIndex (190°C/2.16 kg)	0.2 to 8g/10min.
Density	0.940 to 0.960 g/cm ³

Optimum addition level of XL-PEarl 23 silane has to be determined experimentally. A starting point dose level is as follows:

XL-PEarl 23 silane	1.6 - 1.8%
CAT/AO Masterbatch (PEarlstab S-12'000)	3 - 5%
Melt temperature during the grafting	215 - 225°C

Our technical personnel will advise you regarding the proper operating conditions for the compounding equipment.

Commercially Available HDPE Resins:

HDPE	From	MFI	Density
Lupolen 5031L	Basell	5-7	0.952
Eltex/Fortiflex A4040	Solvay	4	0.944
Politeno IH57	Politeno	2.5	0.953
Nova 76 A	Nova	3.3	n/a
HDPE M 40060S	Sabic	4.0	0.960

B) Crosslinking

Rate of cure is dependent upon time, temperature and thickness of the article and available moisture.

Sufficient crosslinking can be achieved by any of the following methods:

- Immersion in water at 80-90°C (176-195°F), or
- Exposure to low pressure steam at 105°C (221°F), or
- Exposure to steam at atmospheric pressure (i.e., a sauna at 100°C (212°F)), or
- Ambient curing (only applicable to certain polymers)

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.