

SilCool TIA241GF

Liquid-Dispensed Silicone Thermal Pad / Gap Filler

Description

SilCool TIA241GF gap filler is a 2-component, soft, thermally conductive silicone material used to dissipate heat from electronic devices. Its non-slumping pasty consistency offers physical stability that can allow improved processing. SilCool TIA241GF gap filler can be used as a liquid dispensed alternative to pre-fabricated thermal pads in a broad array of thermal designs for electronic applications.

Key Features and Typical Benefits

- Good thermal conductivity
- Fast, low temperature cure
- Convenient 1:1 mix ratio by weight
- Retained softness after cure for enhanced stress relief during thermal cycling
- Excellent slump resistance (stays in place)
- Repairable
- Flame retardant: UL94V-0 equivalent
- Glass bead options available (180 & 250µm) for bond line thickness (BLT) control

Typical Physical Properties

Uncured Properties	SilCool TIA241GF (A) gap filler	SilCool TIA241 GF (B) gap filler
Appearance (Part A & B)	Blue	Pale Blue
Viscosity ⁽⁴⁾ Pa*s	250	130
Mix Ratio by Weight	1:1	
Viscosity ⁽⁴⁾ after Mixing Pa*s	130	
Thixo Index	2.6	
Work Life at 23 °C Hours	3	
Cure Conditions Hours		
at 100 °C	0.25	
at 70 °C	0.50	
at 23 °C	24	

Cured Properties (30 minutes at 100 °C)		
Appearance		Blue
Density (23 °C)	g/cm ³	3.14
Thermal Conductivity ⁽¹⁾	W/m•K	4.1
Thermal Resistance ⁽²⁾	mm ² •K/W	30 (BLT: 80µm)
Hardness (Type E)		45
Hardness (Shore 00)		70
Tensile Strength	MPa	0.2
Elongation	%	40
Volume Resistivity	MΩ•m	1.0 x 10 ⁴
Dielectric Strength	kV/mm	14
CTE ⁽³⁾	ppm/C°	110
Low Volatile (D ₄ -D ₁₀)	ppm	150
Flame Retardant	(UL94)	V-0 (equivalent)
Relative Temperature Index	(RTI)	150 °C (equivalent)

(1): Hot wire method / (2), (3): In-house test method.

(4): Rheometer

Typical physical properties are average data and are not to be used as or to develop specifications.

Potential Applications

Thermal interface for electronic components in Automotive, Consumer, Telecommunication, Lighting and Industrial applications.

General Considerations for Use

Materials such as water, sulfur, nitrogen compounds, organic metallic salts, phosphorus compounds, etc. contained in the surface of the substrate can inhibit curing. A sample patch should always be conducted before proceeding in order to determine substrate compatibility.

- Wear eye protection when handling uncured rubber as it can irritate eyes. In case of eye contact, immediately flush eyes well with water and contact a physician.
- Maintain adequate ventilation in the work place at all times.

While the typical operating temperature for silicone materials ranges from -45°C to 200°C, the long-term maintenance of its initial properties is dependent upon design related stress considerations, substrate materials, frequency of thermal cycles, and other factors.

Storage


- Store in a cool, dry place out of direct sunlight.
- Keep out of the reach of children.

Option for Glass Beads


- Material is available with spacers for bond line thickness control.
- Currently available glass bead sizes: 180µm and 250µm; other sizes can be made available upon request.

Additional Test Data


Thermal Resistance and BLT



BLT vs. Assembly Pressure



Thermal Resistance Reliability



Note: Test data. Actual results may vary.

Example Test Conditions:

Sandwich 0.02ml of SilCool TIA241GF gap filler between 10mm x 10mm silicon dies, assemble at 500kPa pressure and cure at 100 °C for 0.5 hours. Measure thermal resistance using Laser Flash Method.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for

its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		*All Middle Eastern countries, Africa, India,	Korea
			+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or

design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilCool™ es una marca comercial de Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.