

AnchorSil* 2000

AnchorSil* 2000

Description

AnchorSil 2000 anchorage additive is a 100% active organo-functional reactive polymer designed to improve anchorage of Momentive thermally cured solventless silicone release coatings to polyester films.

Key Features and Benefits

- Improves anchorage on a variety of treated and untreated polyester films
- Improves anchorage of formulations with and without controlled release additive
- Compatible with all Momentive thermally cured solventless silicone release coatings
- Easily mixes with Momentive thermally cured solventless silicone release coatings
- Does not adversely affect release performance, coverage and bath life of release coatings

Typical Physical Properties

Property	Value	Unit of Measure
Viscosity @ 25°C	215	cst, 25°C (77°F)
Density	8.819	Lbs./gal
Specific Gravity	1.060	-
Hydride Content	0.7	weight %
Flash Point (PMCC)	82	°C

Potential Applications

AnchorSil 2000 anchorage additive may be used with all Momentive vinyl functional

solventless thermally cured silicone release coatings for improved anchorage on a variety of polyester films.

Patent Status

Standard copy to come

Product Safety, Handling and Storage

The limited warranty period is 3 months from date of shipment from Momentive Performance Materials if stored in the original unopened container below 4°C (39°F). Note that Anchorsil 2000 anchorage additive is a reactive product and can evolve hydrogen over time if stored at temperatures greater than 4°C (39°F) (See Figure 4). Storage at temperatures greater than 4°C (39°F) will also shorten storage life (see Figure 5). If frozen, care should be taken not to introduce moisture from condensation. Opened, partially used containers should be tightly recapped and returned to storage below 4°C (39°F) when not in use. Introduction of moisture should be avoided and if capable, a dry nitrogen atmosphere should be replaced in order to ensure optimum storage stability.

Figure 4: AnchorSil 2000 Anchorage Additive Hydrogen Evolution Versus Storage Temperature





Figure 5: AnchorSil 2000 Anchorage Additive Viscosity Stability Versus Storage

Temperature



Standard copy to come

Processing Recommendations

AnchorSil 2000 anchorage additive is compatible with all Momentive thermally cured solventless silicone release coatings. For best results, it should be added to the silicone formulation at the same time the crosslinker is added and thoroughly mixed prior to use. The level of addition will depend on the type of polyester film and actual curing conditions. In general, 2 to 4 parts per hundred (pph) polymer addition of AnchorSil 2000 anchorage additive is sufficient to obtain optimum anchorage, but the actual required concentration should be established and optimized during extensive machine trials by the customer.

Table 1: Typical Starting Formulations for SL6625/SL6635 Release Coating System

	AnchorSil 2000 Anchorage Additive Concentration							
	0 pph		2 pph		3 pph		4 pph	
Component	Parts by Weight							
SL6625	100	75	100	75	100	75	100	75
SL6635	0	25	0	25	0	25	0	25
AnchorSil 2000 anchorage additive	0	0	2	2	3	3	4	4
SS4300C ⁽¹⁾	3.3	4.3	2.4	3.5	2.0	3.0	1.6	2.6

(1)SS4300C concentrations adjusted for hydride content in AnchorSil 2000 anchorage additive to maintain a constant SiH:Vi ratio. Contact your local Momentive technical or sales representative for further assistance.

Table 2: Typical Starting Formulations for SL7025 Release Coating System

	AnchorSil 2000 Anchorage Additive Concentration			
	0 pph	2 pph	3 pph	4 pph
Component	Parts by Weight			
SL7025	100	100	100	100
AnchorSil 2000 anchorage additive	0	2	3	4
SS4300C ⁽²⁾	4	3.1	2.7	2.3

(2)SS4300C concentrations adjusted for hydride content in AnchorSil 2000 anchorage additive to maintain a constant SiH:Vi ratio. Contact your local Momentive technical or sales representative for further assistance.

Note: Since AnchorSil 2000 anchorage additive contains hydride, the final amount of crosslinker in the formulation needs to be adjusted to maintain equal hydride to vinyl (SiH:Vi) ratio in formulations. This is particularly important in pressure sensitive constructions utilizing adhesives that are sensitive to hydride level. Thorough evaluation of the finished product performance is recommended before large quantities of material are manufactured.

AnchorSil 2000 anchorage additive improves the anchorage of thermally cured solventless silicone release coatings to a variety of polyester films. Higher web temperature, longer dwell time and in-line corona treatment have been found to further

improve anchorage. On some substrates and at specific curing conditions, corona treatment may be optional although still recommended as illustrated in Table 3 and Table 4.

Table 3: SL7025 Anchorage on Polyester Film at Various Web Temperatures and Oven Dwell Times.

		SL7025 with 3 pph AnchorSil 2000 Anchorage Additive	SL7025 with 3 pph AnchorSil 2000 Anchorage Additive	SL7025 only
Exit Web Temp	Dwell Time	With Corona	Without Corona	With Corona
(°F)	(sec)	(2W/ft ² /min)	–	(2W/ft ² /min)
250	6	No Rub Off	No Rub Off	Rub Off
250	4	No Rub Off	No Rub Off	Rub Off
250	3	No Rub Off	No Rub Off	Rub Off
250	2	No Rub Off	Rub Off	Rub Off
280	6	No Rub Off	No Rub Off	Rub Off
280	4	No Rub Off	No Rub Off	Rub Off
280	3	No Rub Off	No Rub Off	Rub Off
280	2	No Rub Off	Rub Off	Rub Off


Note: Black Clawson 5 roll coater, 142 gauge SKC polyester film, 95% RH chamber, 24 hours at 600°C

Table 4: SL6625 Anchorage on Polyester Film at Various Web Temperatures and Oven Dwell Times.

		SL6625 with 3 pph AnchorSil 2000 Anchorage Additive	SL6625 with 3 pph AnchorSil 2000 Anchorage Additive	SL6625 only
Exit Web Temp	Dwell Time	With Corona	Without Corona	With Corona
(°F)	(sec)	(2W/ft ² /min)	–	(2W/ft ² /min)
250	6	No Rub Off	Rub Off	Rub Off
250	4	No Rub Off	Rub Off	Rub Off
250	3	No Rub Off	Rub Off	Rub Off
250	2	No Rub Off	Rub Off	Rub Off
280	6	No Rub Off	No Rub Off	Rub Off
280	4	No Rub Off	No Rub Off	Rub Off
280	2	No Rub Off	Rub Off	Rub Off


AnchorSil 2000 anchorage additive does not affect coverage or bath life of formulated release coatings. At higher web temperatures, cure is not affected (see Figure 1). At lower web temperatures and shorter dwell times (e.g. higher line speeds), the cure is slower for formulations containing 3 pph AnchorSil 2000 anchorage additive versus the control formulation (see Figure 2). AnchorSil 2000 anchorage additive concentration and cure conditions should be optimized to maintain the desired level of extractable silicone at the best possible anchorage.

Figure 1: SL7025 With and Without 3 pph AnchorSil 2000 Anchorage Additive – Cure Profiles at 280°F Web Temperature



Note: Black Clawson pilot coater, 1.5 mil polyester film, 0.6 lbs/ream coating weight

Figure 2: SL7025 With and Without 3 pph AnchorSil 2000 Anchoage Additive - Cure Profiles at 250°F Web Temperature




Note: In order to obtain comparable cure between formulations with and without AnchorSil 2000 anchoage additive, it may be necessary to adjust crosslinker level. In doing so however, thorough evaluation of the finished product performance is recommended especially in the case where hydride sensitive adhesives are being used.

When fully cured at higher web exit temperatures, comparable release performance of

SL6625 easy release coating with various levels of SL4406 controlled release additive with and without AnchorSil 2000 anchorage additive at equal hydride to vinyl ratios is illustrated in Figure 3.

Figure 3: Release Performance of SL6625 with SL4406 Controlled Release Additive Tested with Tesa 7475 Tape After 4 Weeks RT Aging - Comparison Between Formulations With and Without 3 pph AnchorSil 2000 Anchorage Additive



Note: Pilot coater, 3 roll Differential Offset Gravure, 142 gauge SKC polyester film, coatings formulated at constant hydride to vinyl ratio of 2.3:1, Tesa 7475 applied offline and aged for 4 weeks at standard RT conditions

Limitations

Standard copy to come

お問合せ窓口

製品の価格、取り扱い状況およびご注文については、Momentive.com/Contact us/CustomerService/からカスタマーサービスへご連絡ください。

パンフレットおよび技術情報については、弊社ウェブサイトwww.momentive.comをご覧ください。

免責条項:

モメンティブ・パフォーマンス・マテリアルズならびにその子会社および関係会社(以下、総称

して「サプライヤー」といいます)の素材、製品およびサービスは、サプライヤーの標準販売条件に基づき販売されています。この標準販売条件は、該当する販売代理店契約または販売契約に含まれており、注文確認書や請求書の裏面に印刷され、また要求に応じて提供可能です。本書に記載の情報、推奨、または提言は、誠意をもって提供されていますが、サプライヤーは明示的にも黙示的にも、(i)本書に記載の結果が最終使用条件下でも得られること、および(ii)製品、素材、サービス、推奨または提言に取り入れられている設計の有効性もしくは安全性について、いかなる保証もいたしません。サプライヤーの標準販売条件に定めのあるものを除き、サプライヤーおよびその代理人は、本書に記載の素材、製品またはサービスの使用によって生じたいかなる損害に対しても責任を負わないものとします。サプライヤーの素材、サービス、推奨、または提言が、ユーザー自身の特定の使用目的に適しているか否かの判断については、各ユーザー自身が全面的に責任を負います。各ユーザーは、すべてのテストや分析を特定および実施して、サプライヤーの製品、素材、またはサービスが組み込まれている最終製品が安全であり、最終使用条件における使用に適していることを確認する必要があります。サプライヤーの署名入りの書面による合意がない限り、本書もしくはその他の文書または口頭による推奨または提言は、サプライヤーの標準販売条件の規定または本免責条項の変更、修正、優先、または権利放棄とはみなされないものとします。本書に含まれる素材、製品、サービスまたは設計の使用可能性または使用提案に関するいかなる記載も、当該使用または設計を対象とするサプライヤーの特許その他の知的財産権に基づくライセンスを付与することを意図してはならず、あるいはライセンスの付与と解釈してはならず、また、何らかの特許その他の知的財産権を侵害する素材、製品、サービスまたは設計の使用の提案を意図してはならず、また使用提案として解釈してはなりません。

Momentive および Momentiveのロゴは、Momentive Performance Materials Inc.の商標です。