

PEarlene* SiPC MB01 Silicone

Description

PEarlene silicone is a gum-containing master batch for the compounding and/or extruding of certain plastics, copolymers and elastomeric formulations that can help provide improved processability (extrusion rate, mold fill and power consumption) and/or performance (izod impact resistance, especially at low temperatures).

The PEarlene silicone line is a family of functional master batches containing high levels of ultra-high-molecularweight polysiloxane which are melt compounded into a thermoplastic polymer. This product line consists of several silicone gum masterbatches based on PE, PP and PC.

Key Features and Typical Benefits

- Improved lubricity of fabricated part
- Improved izod impact resistance especially at low temperatures
- Increased fabrication line throughput
- Reduced extrusion drive load
- Reduced extruder head pressure
- Reduced energy usage in processing

Typical Physical Properties

Form Uniform	Free flowing pellets
Color	Off-white
Density (gm/cc) at 20 °C	1.20 - 1.22
MFI (230 °C at 2.16 Kg)	2-4g / 10 min

Siloxane Content, %	30
Odor	Essentially odorless
Solubility in Water	Insoluble
Melting Point, °C	270

Typical properties are average data and are not to be used as or to develop specifications.

Polymer Modification:

PEarlene SiPC MB-01 silicone (PC: polycarbonate carrier)

These masterbatches modify the rheological characteristics of the resin or compound, which can allow for increased throughputs in production as well as a reduction in the drive torque and machine head pressure, and at increased levels can improve the surface appearance of the fabricated part and lower the coefficient of friction (CoF) on finished parts. It can also noticeably improve fine molded details and mold release. Typical usage levels are from 0.2% to 1.6% by weight of silicon gum.

Select the carrier compatible with your formulation or check with Momentive Performance Materials for detailed information.

Potential Applications

PEarlene silicone gum-containing masterbatches are free-flowing, dry, pelleted materials and excellent candidates to consider for compounding operations and extrusion-based fabrication processes including:

- Wire and cable extrusion,
- Pipe extrusion,
- Injection and compression molding,
- Blown and cast film,
- Foaming operations (closed and open cell as well as structural); thermoforming.

These masterbatches have shown to be effective in polyolefins (PP, PE and their copolymers) as well as EVA, nylon and PC. The product is manufactured to not contain any halogens.

Improper mixing or the use of the wrong type or wrong level of additive will not result in the expected performance enhancements.

General Considerations for Use

Generally, PEarlene silicone gum masterbatches can be added to the resin or compound during the final melt extrusion or fabrication step, and typically processed on conventional equipment under the same processing conditions recommended for the base resins and/or compounds. While no special conditions or process modifications are generally required, PEarlene silicone gum masterbatches must be melt processed under conditions that will assure a high level of homogeneity in the final product.

At addition levels between 0.2% to 1.6% of PEarlene silicone masterbatches by weight of silicone gum, the resin and/or compound will typically be rheologically modified, which can enable better mold flow and fill, replication of fine mold details with more precision, and easier part release without the need for a separate mold release agent.

The addition of PEarlene silicone gum masterbatches typically will improve the coefficient of friction (CoF) of the final part, enhance the surface finish, abrasion resistance, and mar resistance of the fabricated part and render the final part less subject to warpage. Generally, the tensile and elongation properties of the final products will only be slightly affected by the PEarlene silicone gum masterbatches, even at the highest recommended level of addition, and the impact resistance will be improved especially at low temperatures. The product is essentially odorless and colorless (though some grades are off-white), and will normally not affect the odor or color of the material it is added to, also after final fabrication.

Process benefits may include an increase in throughput and a reduction in machine torque and pressure in screw slippage, potentially lowering manufacturing variable costs. The process may also benefit from less frequent shut downs for screw, screen, die and tooling cleanup, as well as less effort being required for the cleaning of machine parts.

Please note that it might be necessary to increase the extrusion speed and reduce machine temperature settings to achieve the full benefit of the additional throughput

when using these masterbatches.

Compounds containing PEarlene silicone masterbatches may be available from your resin or compound supplier.

Patent Status

本書のいかなる内容も、関連特許が存在しないことを暗示したものではありません。またいかなる特許についても、その権利者による許可なしに、その特許が対象とする発明を実施するための許可、誘因または推奨を構成することはできません。

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

お問合せ窓口

製品の価格、取り扱い状況およびご注文については、Momentive.com/Contact us/CustomerService/からカスタマーサービスへご連絡ください。

パンフレットおよび技術情報については、弊社ウェブサイトwww.momentive.comをご覧ください。

免責条項:

モメンティブ・パフォーマンス・マテリアルズならびにその子会社および関係会社(以下、総称して「サプライヤー」といいます)の素材、製品およびサービスは、サプライヤーの標準販売条件に基づき販売されています。この標準販売条件は、該当する販売代理店契約または販売契約に含まれており、注文確認書や請求書の裏面に印刷され、また要求に応じて提供可能です。本書に記載の情報、推奨、または提言は、誠意をもって提供されていますが、サプライヤーは明示的にも黙示的にも、(i)本書に記載の結果が最終使用条件下でも得られること、および(ii)製品、素材、サービス、推奨または提言に取り入れられている設計の有効性もしくは安全性について、いかなる保証もいたしません。サプライヤーの標準販売条件に定めのあるものを除き、サプライヤーおよびその代理人は、本書に記載の素材、製品またはサービスの使用によって生じたいかなる損害に対しても責任を負わないものとします。サプライヤーの素材、サービス、推奨、または提言が、ユーザー自身の特定の使用目的に適しているか否かの判断については、各ユーザー自身が全面的に責任を負います。各ユーザーは、すべてのテストや分析を特定および実施して、サプライヤーの製品、素材、またはサービスが組み込まれている最終製品が安全であり、最終使用条件における使用に適していることを確認する必要があります。サプライヤーの署名入りの書面による合意がない限り、本書もしくはその他の文書または口頭による推奨または提言は、サプライヤーの標準販売条件の規定または本免責条項の変更、修正、優先、または権利放棄とはみなされないものとします。本書に含まれる素材、製品、サービスまたは設計の使用可能性または使用提案に関するいかなる記載も、当該使用または設計を対象とするサプライヤーの特許その他の知的財産権に基づくライセンスを付与することを意図してはならず、あるいはライセンスの付与と解釈してはならず、また、何らかの特許その他の知的財産権を侵害する素材、製品、サービスまたは設計の使用の提案を意図してはならず、また使用提案として解釈してはなりません。

Momentive および Momentiveのロゴは、Momentive Performance Materials Inc.の商標です。