

## PEarlene\* SiPP MB05 Silicone

### Description

PEarlene silicone gum containing masterbatches provide improved processability (extrusion rate, mold fill and power consumption) and performance (mar and scratch resistance) when used to compound or extrude certain plastics, copolymers or elastomeric formulations.

PEarlene silicone gum masterbatches are a family of functional masterbatches containing high levels of ultra- high- molecular- weight polysiloxane which are melt compounded into a thermoplastic polymer.

Typical usage levels are from 0.2% to 1.6% by weight of silicone gum.

The product line consists of several silicone gum masterbatches based on polyolefins (PE and PP) as well as PC.

Polymer Modification:

PEarlene SiPP MB-05 silicone (PP: polypropylene homopolymer)

These masterbatches modify the rheological characteristics of the resin or compound, which may allow for increased throughput in fabrication operations as well as reduction in drive torque and machine head pressure. These masterbatches are typically used at 0.2 to 1.6 % by weight of silicone gum.

To improve the surface appearance of the fabricated part, higher levels of the masterbatches are generally recommended. This should result in a lower coefficient of friction (CoF) on finished parts. It should also noticeably improve fine molded details and mold release. In addition, typical benefits of increased throughput in fabrication operations, as well as reduction in drive torque and head pressure, may allow for

savings in manufacturing variable costs.

Select the carrier compatible with your formulation or check with Momentive Performance Materials for detailed information.

**Key Features and Benefits**

- Improved lubricity of fabricated part
- Improved mar resistance
- Improved scratch resistance
- Increased fabrication line throughput
- Reduced extrusion drive load
- Reduced extruder head pressure
- Reduced energy usage in processing

**Typical Physical Properties**

Form	Uniform, free flowing micropellets
Description	Off- white, free from foreign materials
Nominal density (gm/cc) at 20°C	.94-.96
MFI (190°C @ 2.16 Kg)	13 g/10 min
Typical Usage Levels, % by weight	0.2 to 1.6
Active Ingredients, %	50
Odor	Essentially odorless
Solubility in water	Insoluble
Melting Point, °C	> 160 (PP carriers)

See MSDS (SDS) and final Technical Bulletin for additional details. Some physical properties may be estimated.

**Potential Applications**

PEarlene silicone gum masterbatches may be excellent candidates for consideration in compounding operations and extrusion based fabrication processes including: injection and compression molding; blown and cast film; foaming operations (closed and open cell as well as structural); thermoforming; rotomolding etc.

These masterbatches are believed to be highly effective in polyolefins such as PP .

Generally, the PEarlene silicone gum masterbatches can be added to the resin or compound during the final melt extrusion or fabrication step. The additive must be homogeneously mixed with the resin or compound in the melt process to yield the full cost effective benefit of the additive. Compounds containing PEarlene silicone gum masterbatches may be available from your resin or compound supplier.

Compound manufacturers can add the masterbatches during continuous or batch melt compounding operations.

Improper mixing or the use of the wrong type or wrong level of additive will not result in the expected performance enhancements.

### **Product Usage**

The PEarlene family of silicone gum based masterbatches are free-flowing, dry, pelleted materials which may be excellent candidates for consideration in formulating into a variety of resin based compounds. The product does not contain any halogens. The ultra- high- molecular- weight polysiloxanes have been shown to be effective in various applications. The product is used by blending and/or adding to resin or fully or partially formulated compounds and then melt processed. It is critical that the processing provides a homogenous distribution of the masterbatch in the final resin or compound. The melt processing typically can be accomplished employing the same fabrication conditions normally used for the base compound. Unmodified conventional handling and processing equipment has been used for this step.

The product is essentially odorless and colorless (though some grades are off- white). The product will not normally affect the odor or color of the material it is added to especially after final fabrication.

At low addition levels of PEarlene silicone masterbatches between 0.2% to 1.6 % by weight of silicone gum, the resin and/or compound will typically be rheologically

modified which may result in an improvement in flow. This may allow for better mold flow and fill, replication of fine mold details with more precision and easier part release without the need for a separate mold release agent. Parts made with these masterbatches are generally less subject to warpage. The process should benefit from an increase in throughput and a reduction in machine torque and pressure, and may thereby lower manufacturing variable costs.

With addition of PEarlene silicone gum masterbatches the coefficient of friction (CoF) of the final part will typically be improved, the surface finish will be enhanced, and the abrasion resistance and the mar resistance of the fabricated part will be enhanced.

Generally, the tensile and elongation properties of the final products will only be slightly effected by the PEarlene silicone masterbatches even at the highest recommended level of addition and the impact resistance will be improved especially at low temperatures.

#### **Patent Status**

Standard copy to come

#### **Product Safety, Handling and Storage**

Standard copy to come

#### **Processing Recommendations**

The family of PEarlene silicone gum based masterbatches are added to the formulation and typically processed on conventional equipment under the same processing conditions recommended for the base resins and/or compounds. No special conditions or process modifications are generally required. However, the PEarlene silicone gum masterbatches must be melt processed under conditions which will assure a high level of homogeneity in the final product. These ultra-high-molecular-weight based polysiloxane based masterbatches may prevent screw slippage.

It should be noted that it might be necessary to increase the extrusion speed and reduce machine temperature settings to get the full benefit of the additional throughput which may be available when using these masterbatches. The process may also benefit from less frequent shut downs for screw, screen, die and tooling cleanup. In addition the cleaning of machine parts will generally require less time and effort.

## Limitations

Standard copy to come

### お問合せ窓口

製品の価格、取り扱い状況およびご注文については、[Momentive.com/Contact us/ CustomerService/](https://www.momentive.com/Contact-us/CustomerService/)からカスタマーサービスへご連絡ください。

パンフレットおよび技術情報については、弊社ウェブサイト[www.momentive.com](http://www.momentive.com)をご覧ください。

### 免責条項:

モメンティブ・パフォーマンス・マテリアルズならびにその子会社および関係会社(以下、総称して「サプライヤー」といいます)の素材、製品およびサービスは、サプライヤーの標準販売条件に基づき販売されています。この標準販売条件は、該当する販売代理店契約または販売契約に含まれており、注文確認書や請求書の裏面に印刷され、また要求に応じて提供可能です。本書に記載の情報、推奨、または提言は、誠意をもって提供されていますが、サプライヤーは明示的にも黙示的にも、(i)本書に記載の結果が最終使用条件下でも得られること、および(ii)製品、素材、サービス、推奨または提言に取り入れられている設計の有効性もしくは安全性について、いかなる保証もいたしません。サプライヤーの標準販売条件に定めのあるものを除き、サプライヤーおよびその代理人は、本書に記載の素材、製品またはサービスの使用によって生じたいかなる損害に対しても責任を負わないものとします。サプライヤーの素材、サービス、推奨、または提言が、ユーザー自身の特定の使用目的に適しているか否かの判断については、各ユーザー自身が全面的に責任を負います。各ユーザーは、すべてのテストや分析を特定および実施して、サプライヤーの製品、素材、またはサービスが組み込まれている最終製品が安全であり、最終使用条件における使用に適していることを確認する必要があります。サプライヤーの署名入りの書面による合意がない限り、本書もしくはその他の文書または口頭による推奨または提言は、サプライヤーの標準販売条件の規定または本免責条項の変更、修正、優先、または権利放棄とはみなされないものとします。本書に含まれる素材、製品、サービスまたは設計の使用可能性または使用提案に関するいかなる記載も、当該使用または設計を対象とするサプライヤーの特許その他の知的財産権に基づくライセンスを付与することを意図してはならず、あるいはライセンスの付与と解釈してはならず、また、何らかの特許その他の知的財産権を侵害する素材、製品、サービスまたは設計の使用の提案を意図してはならず、また使用提案として解釈してはなりません。

Momentive および Momentiveのロゴは、Momentive Performance Materials Inc.の商標です。