

## SilForce\* FSR2000

### SilForce\* FSR2000 Release Coating

#### Description

The Silforce FSR2000 system is a multi-component, addition cure, thermal solventless release coating system designed for use in the manufacture of release liners for silicone pressure sensitive adhesive applications. SilGrip PSA6574 pressure sensitive adhesive is a high performance phenyl silicone PSA that should be used in conjunction with the FSR2000 release system to provide stable aged release.

The FSR2000 release coating is a fluorosilicone polymer containing platinum catalyst. Standard silicone inhibitors and crosslinkers can be used to control bath life and cure the system respectively. A typical system could include:

- FSR2000 Fluorosilicone base polymer with platinum catalyst
- SL6040-D1 Inhibitor
- SS4300c Homopolymer crosslinker

#### Key Features and Benefits

- Stable aged release against PSA6574 pressure sensitive adhesive
- Differential release possible with high vinyl silicone polymer additive
- Good uniform coverage
- Fast cure at low temperatures
- Cost effectiveness

### Typical Physical Properties

Property	Value
Appearance	Light yellow oil
Viscosity (cstk at 25°C)	230
Density (lb/gal)	8.6

### Patent Status

Standard copy to come

### Product Safety, Handling and Storage

The warranty period of FSR2000 release coating is 12 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at 25°C (77°F). Containers must be kept tightly closed when not in use.

Standard copy to come

### Processing Recommendations

#### APPLICATION AND CURE

Silforce FSR2000 release coating is supplied with platinum catalyst incorporated into the base polymer. However, an inhibitor and a crosslinker must be added to control bath life and obtain cure respectively. The converter has flexibility in the final release formulation that is actually used. As a starting point for evaluation, however, the following typical formulation could be considered:

- 100 parts FSR2000 base polymer/catalyst
- 0.5 parts SL6040-D1 inhibitor
- 4 parts SS4300c crosslinker

To ensure consistent results and maximize bath life, the components should be mixed just before use in the following order:

1. Weigh and add the base polymer/catalyst (FSR2000) and inhibitor (SL6040-D1) into a clean, rust-free container/mixing vessel.

2. Mix for 5 to 10 minutes with a high velocity air mixer at moderate speed.
3. Weigh and add the crosslinker (SS4300c) to the above mix.
4. Mix again (as described in step 2 above) to ensure homogeneity.

The working life of the activated bath varies depending on inhibitor level and ambient conditions. In general, the suggested starting formulation above will have a bath life of approximately 8 hours.

The FSR2000 release system can be applied by any of the methods now being used commercially for solventless silicone. These include three roll differential offset gravure and various smooth roll configurations.

Heat should be applied immediately after coating to initiate cure. Best results are obtained with zoned ovens with the first zone operating at 90-120°C (200-250°F) to allow the coating to level and form a continuous film before cure is initiated.

Subsequent zones should be sufficiently high to achieve a minimum exit web temperature of approximately 107°C (225°F). Actual temperatures required for complete cure will be highly dependent on machine conditions. In general, minimum web temperature must be maintained a finite time to obtain complete cure. This time is dependent on oven length and air velocity.

Approximate curing times as a function of oven air temperature for the starting formulation cited previously are shown in Table 1:

**Table 1**

Approximate Cure Times as a Function of Oven Air Temperature

<u>Temperature</u>	<u>Minimum Cure Time (sec)</u>
93°C (200°F)	30
107°C (225°F)	22
120°C (250°F)	10
135°C (275°F)	7
149°C (300°F)	5

The FSR2000 release coating system is suitable for a variety of paper, plastic, and plastic laminated substrates. These include supercalendared kraft, glassine, clay

coated kraft, polyethylene coated kraft, polyester films, etc.

Coating weight will depend on the hold out and resolution of the surface, but generally 0.8-1.6 g/m<sup>2</sup> (0.5-1.0 lbs/3000ft<sup>2</sup>) will provide a continuous silicone film.

Coating weights are determined by X-ray fluorescence. For machine trials a simple, inexpensive method to calculate coating weight is available from Momentive Performance Materials.

**RELEASE VALUES**

Crosslinker level can have an impact on release values as shown in Table 2 below. The table shows release values obtained using two levels of crosslinker (SS4300c) against PSA6574 pressure sensitive adhesive. Conditions are listed below. This information is intended to be used only as a general guide.

**Table 2**  
Effect of Crosslinker Level on Release

SS4300c Crosslinker Level(%)	3.3	5.0
Initial Release(g/in)	5	5
20 hr/70°C Release (g/in)	5	7
1 wk/70°C Release (g/in)	7	9

**Conditions:**

- Substrate: Kammerer AV100 Glassine
- Equipment: Dixon Pilot Coater, 3-Roll Differential Offset Gravure
- Coat weight: Approximately 1.1 lb/ream
- Cure time/temp: 12 sec/350°F
- Adhesive: PSA6574 transfer coated on lab coater, approximately 2 mil build (dry), adhesive dried 2 min/300°F
- Release test: 300 in/min, 180° peel

If differential release is desired, use of a high vinyl linear silicone polymer can increase

release levels of the FSR2000 release system. Typical formulations may include up to 30% SL6500 vinyl silicone polymer. Such formulations may double the release value of FSR2000 release system against PSA6574 pressure sensitive adhesive. Such applications should be carefully evaluated since increased levels of SL6500 vinyl silicone polymer may adversely affect release stability.

The application method and catalysis of the SilGrip PSA6574 pressure sensitive adhesive also can affect release levels. In general, lower release values are obtained with direct coating of the PSA6574 to the face stock, followed by lamination to the cured FSR2000 release coating. Generally, higher release values are seen when the PSA6574 is coated on the cured FSR2000 release coating and then transferred to the face stock.

Additionally, catalysis of PSA6574 with benzoyl peroxide (BPO) will generally result in higher release values.

Table 3 below indicates the effect of the PSA6574 pressure sensitive adhesive catalysis and coating method on release values. Again, this is informational only. Coating conditions are listed below the table.

**Table 3**

Release Values as a Function of PSA6574 Coating Method and Catalysis

<b>BPO Concen.(%)</b>	<b>Coating Method</b>	<b>Initial Release (g/in)</b>	<b>20 hr/70°C Release (g/in)</b>	<b>1 wk/70°C Release (g/in)</b>
0	Transfer	4	4	7
2	Transfer	7	8	38
2	Direct	2	2	2

**Conditions :**

- Substrate: Kammerer AV100 glassine
- Equipment: Dixon Pilot Coater, 3-Roll Differential Offset Gravure
- Coat Weight: Approximately 0.95 lb/ream
- Cure Time/Temp: 12 sec/350°F
- Adhesive: PSA6574 coated and catalyzed as indicated in Table 3, catalyzed

adhesive cured at 350°F/2 min, uncatalyzed adhesive dried at 300°F/2 min,  
approximately 2 mil dry adhesive build

- Release test: 300 in/min, 180° peel

## Limitations

Standard copy to come

## お問合せ窓口

製品の価格、取り扱い状況およびご注文については、[Momentive.com/Contact us/ CustomerService/](https://www.momentive.com/Contact-us/CustomerService/)からカスタマーサービスへご連絡ください。

パンフレットおよび技術情報については、弊社ウェブサイト[www.momentive.com](http://www.momentive.com)をご覧ください。

## 免責条項:

モメンティブ・パフォーマンス・マテリアルズならびにその子会社および関係会社(以下、総称して「サプライヤー」といいます)の素材、製品およびサービスは、サプライヤーの標準販売条件に基づき販売されています。この標準販売条件は、該当する販売代理店契約または販売契約に含まれており、注文確認書や請求書の裏面に印刷され、また要求に応じて提供可能です。本書に記載の情報、推奨、または提言は、誠意をもって提供されていますが、サプライヤーは明示的にも黙示的にも、(i)本書に記載の結果が最終使用条件下でも得られること、および(ii)製品、素材、サービス、推奨または提言に取り入れられている設計の有効性もしくは安全性について、いかなる保証もいたしません。サプライヤーの標準販売条件に定めのあるものを除き、サプライヤーおよびその代理人は、本書に記載の素材、製品またはサービスの使用によって生じたいかなる損害に対しても責任を負わないものとします。サプライヤーの素材、サービス、推奨、または提言が、ユーザー自身の特定の使用目的に適しているか否かの判断については、各ユーザー自身が全面的に責任を負います。各ユーザーは、すべてのテストや分析を特定および実施して、サプライヤーの製品、素材、またはサービスが組み込まれている最終製品が安全であり、最終使用条件における使用に適していることを確認する必要があります。サプライヤーの署名入りの書面による合意がない限り、本書もしくはその他の文書または口頭による推奨または提言は、サプライヤーの標準販売条件の規定または本免責条項の変更、修正、優先、または権利放棄とはみなされないものとします。本書に含まれる素材、製品、サービスまたは設計の使用可能性または使用提案に関するいかなる記載も、当該使用または設計を対象とするサプライヤーの特許その他の知的財産権に基づくライセンスを付与することを意図してはならず、あるいはライセンスの付与と解釈してはならず、また、何

らかの特許その他の知的財産権を侵害する素材、製品、サービスまたは設計の使用の提案を意図しておらず、また使用提案として解釈してはなりません。

Momentive および Momentiveのロゴは、Momentive Performance Materials Inc.の商標です。