

## SilForce™ SL6575

### SilForce\* SL6575

#### Description

SL6575 is a thermal cure solventless silicone release coating system designed for use in the manufacture of release liners for pressure sensitive tapes and labels. SL6575 includes a vinyl silicone polymer, a cure catalyst, and an inhibitor for ease of formulation. SL6575 is characterized by a flat dynamic release profile. It may be suitable for use on paper and certain film substrates in one-and two-sided constructions.

The SL6575 system consists of easy and tight release polymers that are delivered mixed with platinum catalyst and inhibitor. The SL6575 system can be used with either of three silicone crosslinkers.

- SL6575 Easy Release Polymer pre-blend
- SL4406 Tight Release Polymer (CRA) pre-blend
- SS4300c Homopolymer Crosslinker, or
- SL4320 Enhanced crosslinker, or
- SL6020-D1 Copolymer Crosslinker

SL6020-D1 crosslinker is recommended for fast cure at low temperature. SS4300c is used for superior anchorage to difficult substrates such as films or clay coated kraft. SL4320 combines the fast cure performance of SL6020-D1 with the anchorage enhancement of SS4300c.

#### Key Features and Benefits

- Flat release profile for high speed label dispensing
- Low extractable silicone when properly cured
- Compatible with most acrylic and rubber based adhesives
- Controlled release available with SL4406 pre-blend
- Good bulk and thin film bath life
- Easy to handle and to formulate (pre-blended system)

### Typical Physical Properties

Property	Value	Unit of Measure
Viscosity, Ostwald, 25C	225 - 350	cstk
Density, 25°C	8.07	Lb./gal
VOC (EPA Method 24)	0.1	%
Appearance	Clear to slightly hazy	

### REGULATORY STATUS

All components of the SL6575 system are on TSCA, EINECS, and other inventories.

The SL6575 system without tight release polymer complies with these FDA regulations:

- 175.320, resinous and polymeric coatings for polyolefin films
- 176.180, components of paper and paperboard in contact with dry foods for use as release surfaces for pressure sensitive adhesives.
- 176.170, components of paper and paperboard in contact with aqueous and fatty foods

### Potential Applications

Possible applications include release liners for pressure sensitive tapes and labels.

### Patent Status

Standard copy to come

## **Product Safety, Handling and Storage**

**CAUTION NOTE:** SL6020-D1, SL4320, and SS4300C crosslinkers generate flammable hydrogen gas on contact with strong acids, bases, and oxidizing agents. Empty containers of the crosslinkers should not be reused.

The limited warranty period for SL6575 is 12 months from date of shipment from Momentive Performance Materials if stored in original unopened container at or below 25°C (77°F).

Standard copy to come

## **Processing Recommendations**

### **APPLICATION**

The SL6575 coating system can be applied by most of the commercial methods in use for solventless silicone coating. These include three-roll differential offset gravure and various smooth roll configurations. Heat should be applied immediately after coating to initiate cure.

Good results are obtained by use of zoned ovens. Operation of the first oven zone at 90 - 120 °C(200 - 250 °F) allows the silicone to level and form a continuous film before crosslinking commences. Subsequent oven zones should be high enough in temperature to achieve required web (substrate) temperature to insure crosslinking of the silicone. A web temperature of 120 °C (250 °F) is generally required for fast, complete cure of SL6575.

This information is intended as a guide; actual web temperature required for optimal performance is dependent on machine conditions, oven type, oven air velocity, coating weight, and substrate. A certain minimum web temperature must be maintained for a certain finite time for satisfactory cure of SL6575 release coating. This time and temperature are a function of oven length, oven air velocity, crosslinker concentration, and basis weight of substrate.

### **FORMULATION RECOMMENDATIONS**

PARTS BY WEIGHT			
Component	No CRA	20% CRA	40% CRA
SL6575	100	80	60
SL4406	0	20	40
SL4320	8	9	10

To obtain better anchorage (on clay coated krafts or films), SS4300C crosslinker is recommended. To calculate amount of SS4300C required, multiply the amount of SL4320 noted in table above by 0.79. If faster cure is needed, SL6020-D1 crosslinker is recommended; multiply the SL4320 charge by 1.38.

Suggested formulations in the above table are based on cure optimization studies and are substrate and adhesive-dependent. High and unstable release, particularly from aggressive acrylic adhesives, can result from use of too much crosslinker. We suggest that users of SL6575 system consult with the technical assistance staff at Momentive Performance Materials for help in formulation of release coatings.

## BATH LIFE

The working life of a fully formulated solventless silicone release agent will vary dependent on catalyst and inhibitor levels, ambient temperature and humidity, and crosslinker levels. The formulations suggested in the above table will have a minimum useable life of 8 hours. If formulated unused coating is saved, refrigerated storage will extend its useful life.

## Preparation of Coating Formulations

To ensure consistent results and long bathlife, the components of the coating bath should be mixed in this order: weigh and add the base polymers (SL6575 and SL4406 CRA) first, to a clean mixing vessel, agitate for a few minutes, then add the SL4320 or other crosslinker. The complete coating bath should be mixed for 10-15 minutes to create a homogeneous mixture. Baths should be prepared just before use.


## Coat Weights and Substrates

The SL6575 system can be applied to a variety of papers such as supercalendered and clay coated krafts and glassine and to certain film substrates. Coating weight required for good release performance depends on holdout and surface smoothness of the liner. Most papers will need 1.0 - 1.5 g/m<sup>2</sup> (0.6 - 0.9 lb/3000 foot<sup>2</sup>) applied silicone to furnish a smooth, continuous silicone surface. Film or film-laminate substrates require

less applied silicone than papers.

### Release Profile


The variation of force required to delaminate an adhesive/facestock lamina from a release liner as a function of peel speed is the dynamic peel release profile. The release profile of a given cured silicone release coating is dependent on the type of release coating, the PSA, liner, and facestock used in the construction. In general, highly crosslinked silicone coatings are higher modulus materials than analogous lightly crosslinked coatings and their release from PSAs is less dependent on peel speed. That is, highly crosslinked silicones display less build in release as peel speed increases, a flatter peel response. SL6575 has a high vinyl content relative to other solventless release systems such as SL6100, therefore cured coatings of SL6575 exhibit a flat release profile compared to cured coatings of SL6100-based systems as illustrated in Figure 1.



### Controlled Release Action

A Controlled Release Additive (CRA) is used to modify the force required to delaminate

(peel) a label or tape from the silicone coated release liner. We recommend SL4406 for use as a CRA with SL6575, as it is compatible with SL6575 and is very efficient. SL6635 preblend CRA can also be used with SL6575. The CRA effect of SL4406 in the SL6575 release coating is illustrated in Figure 2 below.



## Limitations

Standard copy to come

## Availability

Products may be ordered from Momentive Performance Materials, Waterford, NY12188, the Momentive Performance Materials sales office nearest you or, where appropriate, an authorized Momentive Performance Materials product distributor.

## Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

## Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	<b>Brazil</b>	<b>Europe</b>	<b>China</b>
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	<b>Mexico</b>	<b>India, Middle East &amp; Africa</b>	<b>Japan</b>
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b>
			+82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

## DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE.

**EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\* SilForce™は Momentive Performance Materials Inc. の商標です。

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.