

## **SiIFORT\* SHC1200**

### **SiIFORT\* SHC1200**

#### **Description**

SiIFORT SHC1200 Hard Coat

SHC1200 hard coat has been found to yield a clear mar-resistant film when applied to a suitably prepared plastic substrate. It can be applied by flow, dip or spray coating.

#### **SiIFORT SHP401 Primer**

SHP401 air-dried primer is used as an adhesion promoter for SHC1200 hard coat on polycarbonate resin. It can be applied by flow, dip or spray coating.

#### **Key Features and Benefits**

- Fast cure
- Abrasion resistance
- Scratch resistance
- Good clarity
- Solvent/chemical resistance

#### **SHP401 Primer**

- No thermal cure required
- Improves coating adhesion
- Improves water resistance

- Improves ultraviolet resistance

### **SHP401 Primer/SHC1200 Hard Coat on polycarbonate (2 - 4 micron Topcoat Thickness)**

#### Cured Film Properties

Film Thickness, slow dip coat, 10-18 cm/min withdrawal, 18-20% solids at 22C	2 – 4 micron
Taber Abrasion, 500 cycles 500G on primed polycarbonate (CS10F wheel)	< 6.0 % Haze measured per ASTM D1003. *
Index of Refraction	1.4

\*Humidity during coating and testing will affect final values.

#### **Typical Physical Properties**

<b>Property</b>	<b>SHC1200 Hard Coat</b>	<b>SHP401 Primer</b>
Solids Content, %	20 ± 1	2.1 ± 0.2
Solvent	Methanol, Isobutanol, Isopropanol	1-Methoxy-2-propanol, Diacetone Alcohol
Flash Point, PMCC	19.4C	36.1C
Density, g/cm <sup>3</sup>	0.911	0.959
p <sup>H</sup>	7.3 ± 0.2	-
Viscosity, cstk @ 25°C	20 ± 3	4 - 7
Dry Film Thickness, micron	2.75 - 4.5	0.5
VOC, g/l	710	937

#### **Patent Status**

本書のいかなる内容も、関連特許が存在しないことを暗示したものではありません。またいかなる特許についても、その権利者による許可なしに、その特許が対象とする発明を実施するための許可、誘因または推奨を構成することはできません。

#### **Product Safety, Handling and Storage**

##### **CAUTION**

Compatibility of Momentive Performance Materials hard coat and polycarbonate resin is dependent on a number of factors including operational stresses, chemical exposure,

temperature levels, impact and exposure to ultraviolet light.

While it is up to the end user to determine what application specific testing is appropriate, it is suggested that all polycarbonate resin applications be tested for at least thirty (30) days for compatibility and crazing with this hard coat before use. There is no dependable substitute for careful testing of prototypes of production parts in typical operating environments.

### **SHC1200 Hard Coat**

Refrigeration is required.

The warranty period is 3 months form date of shipment from Momentive Performance Materials if stored in the original unopened container at or below -15 °C (<5 °F).

### **SHP401 Primer**

Store and ship at ambient temperature approximately 2-43°C.

When stored in original sealed containers, SHP401 primer will have a warranty period of 6 months. Exposure to low temperatures may cause some solid precipitation. If this occurs, the precipitate may be redissolved by submerging the vented container in a water bath. Mix until homogeneous.

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

## **Processing Recommendations**

### **General Requirements**

Coating area should be clean, dust-free, well-ventilated and with the relative humidity controlled to 40% +/-10% as required to achieve acceptable coated appearance and performance. If necessary, parts should be washed or wiped clean with isopropyl alcohol, a mild detergent solution and clean water rinse, or an ultrasonic bath followed by a filtered air blow-off and a final ionized-air blow-off. Cleanliness is critical for the production of good parts. Both primer and hard coating solutions should be filtered continuously or just prior to use to approximately 0.5 to 1.0 micron, using a 3 to 5 micron pre-filter. Electric or indirect gas-fired ovens with good convection and air exchange are recommended.

### **SHC1200 Hard Coat**

The hard coat can be applied to primed parts by dip, flow, or spray coating in a well ventilated area. Use caution. Methyl alcohol, Isopropyl alcohol, Diacetone alcohol and Isobutyl alcohol contained in SHC1200 hard coat are hazardous. Read HANDLING & SAFETY. Do not proceed until this information is read and understood. Relative humidity in the coating area should not exceed 50% to avoid solvent blushing. The equipment used to apply SHC1200 silicone resin is of the same type used for the primer. Additionally, the dip tank must be refrigerated so that the hard coat resin can be maintained at about 4C. Maintain constant circulation and < 1 micron filtration. SHC1200 hard coat should air dry for about 20 minutes followed by thermal cure. After reaching part temperature, the coating cures at 130C in 30 minutes. For acrylic substrates cure at 90C for 1 - 2 hours.

### **SHP401 Primer**

The primer can be applied by dip, spray or flow coating to polycarbonate parts that have an initial stress level under 1000 psi. If a higher stress level is found to exist, the tool and molding conditions should be adjusted to reduce residual stress on parts. Alternatively, parts can be annealed to reduce stress, (for example, 30 minutes at 130C for each 2.5 cm of part thickness.) If necessary, primer solids content may be reduced by adding 1-Methoxy-2-Propanol/Diacetone alcohol (85/15) or pure 1-Methoxy-2-Propanol. The primer should be applied to obtain a dry film thickness of approx. 0.5 micron. After application, the primer should air dry until tack free (approximately 10

minutes). Recirculate the primer through a 1micron or finer filter.

### Availability

SHC1200 hard coat and SHP401 can be ordered from Momentive Performance Materials.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### お問合せ窓口

製品の価格、取り扱い状況およびご注文については、[Momentive.com/Contact us/ CustomerService/](https://www.momentive.com/Contact-us/CustomerService/)からカスタマーサービスへご連絡ください。

パンフレットおよび技術情報については、弊社ウェブサイト[www.momentive.com](http://www.momentive.com)をご覧ください。

### 免責条項:

モメンティブ・パフォーマンス・マテリアルズならびにその子会社および関係会社(以下、総称して「サプライヤー」といいます)の素材、製品およびサービスは、サプライヤーの標準販売条件に基づき販売されています。この標準販売条件は、該当する販売代理店契約または販売契約に含まれており、注文確認書や請求書の裏面に印刷され、また要求に応じて提供可能です。本書に記載の情報、推奨、または提言は、誠意をもって提供されていますが、サプライヤーは明示的にも黙示的にも、(i)本書に記載の結果が最終使用条件下でも得られること、および(ii)製品、素材、サービス、推奨または提言に取り入れられている設計の有効性もしくは安全性について、いかなる保証もいたしません。サプライヤーの標準販売条件に定めのあるものを除き、サプライヤーおよびその代理人は、本書に記載の素材、製品またはサービスの使用によって生じたいかなる損害に対しても責任を負わないものとします。サプライヤーの素材、サービス、推奨、または提言が、ユーザー自身の特定の使用目的に適しているか否かの判断については、各ユーザー自身が全面的に責任を負います。各ユーザーは、すべてのテストや分析を特定および実施して、サプライヤーの製品、素材、またはサービスが組み込まれている最終製品が安全であり、最終使用条件における使用に適していることを確認する必要があります。サプライヤーの署名入りの書面による合意がない限り、本書もしくはその他の文書または口頭による推奨または提言は、サプライヤーの標準販売条件の規定または本免責条項の変更、修正、優先、または権利放棄とはみなされないものとします。本書に含まれる素材、製品、サービスまたは設計の使用可能性または使用提案に関するいかなる記載も、当該使用または設計を対象とするサプライヤーの特許その他の知的財産権に基づくライセンス

を付与することを意図してはならず、あるいはライセンスの付与と解釈してはならず、また、何らかの特許その他の知的財産権を侵害する素材、製品、サービスまたは設計の使用の提案を意図しておらず、また使用提案として解釈してはなりません。

Momentive および Momentiveのロゴは、Momentive Performance Materials Inc.の商標です。