

TSK5421L

低温潤滑用シリコングリース

TSK5421Lは、シリコンオイルを基油とし、金属セッケンを配合した潤滑用グリースです。特に耐寒性が要求される潤滑用途に適しています。

特 長

- 耐寒性に優れています。
- 使用温度範囲: -60～+180℃

用 途

- モーター、ポンプ、ファン等の潤滑
- 各種ベアリング、バルブ、ギア、シールなどの潤滑
- 有機ゴムパッキンのシール

特性例 (JIS K 2220)

項 目		特性値
外 観		白色グリース状
混和ちょう度		290
離油度 (150℃,24h)	%	4.0
加熱減量 (150℃,24h)	%	0.5
滴点	℃	211
酸化安定度	MPa	0.00

水洗耐水度 (79°C,1h)	%	7.0
銅板腐食 (100°C,24h)		腐食なし


各種プラスチックに与える影響

プラスチック	外観変化
ABS	なし
PBT	なし
PPS	なし
ポリカーボネート	なし
66ナイロン	なし
NBR	なし


試験条件:幅12mm、長さ80mm、厚さ2mmのテストピースを長さ75mmに湾曲させ、その湾曲部分にTSK5421Lを塗布する。次に70°Cの恒温槽に250時間放置した後、TSK5421Lを拭き取りその表面を観察する。外観変化のないものを「なし」と表示する。

注) 実際に使用する試験体で予備試験をしてから使用してください。

低温トルク試験結果(JIS K 2220)



温度による不混和ちょう度の変化



取扱い上の注意

- 取扱い時には、保護眼鏡および必要に応じて保護手袋を着用してください。
- 換気のよい所で使用してください。

保管

- 直射日光を避け、湿気の少ない冷暗所に保管してください。
- 子供の手の届かない所に保管してください。

荷姿・梱包

- 100gチューブ(1ケース20P)
- 1kg金属缶(1ケース10P)
- 18kgペール

消防法

非危険物。指定可燃物の合成樹脂類に該当

特許状況

本書のいかなる内容についても、関連特許が存在しないことを暗示したものと解釈してはならず、またいかなる特許についても、その権利者による許可なく、その特許が対象とする発明を実施するための許可、誘因または推奨を構成するものと解釈してはなりません。

製品の安全性、取り扱いおよび保管

製品の安全情報、安全な取扱手順、個人用保護具（必要な場合）、緊急サービスの連絡先情報、および安全な保管に必要な条件については、最新の安全データシート（SDS）および製品ラベルで確認してください。SDS は www.momentive.com で入手するか、あるいは MPM の担当者にご依頼ください。他の素材を MPM 製品（例：プライマー）と合わせて使用する際は、追加的な注意が必要になる場合があります。他の素材の製造者による安全情報を読み、それに従ってください。

制限

お客様はモメンティブ・パフォーマンス・マテリアルズ製品を評価し、特定の用途に対する使用適合性をご自身で判断する必要があります。

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
Brazil	Europe	China	
+1 800 295 2392	+390510924300	800 820 0202	
Toll free*	Direct number	Toll free	
+704 805 6946		+86 21 3860 4892	
Direct Number		Direct number	
Mexico	India, Middle East & Africa	Japan	
+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111	
Direct Number	Direct number*	Direct number	

***All Middle Eastern Korea**
countries, Africa, India, +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.