

WSC1042 Clear

Weatherstrip Coating

Description

WSC1042 clear weatherstrip coating is a single component matte translucent water-based silicone coating system that thermally cures to form a resilient silicone film. The cured coating can help to provide substrate surfaces such as EPDM rubber with lubricating water repellency and easy release characteristics. WSC1042 clear coating is an excellent candidate to consider for colored profiles, such as door or window seals where a smooth surface is preferred to impart low friction surfaces. WSC1042 clear can also be considered for use as an assembly aid at a low applied thickness for double glazing seals, as a permanent clean assembly aid in place of soap solutions, or oil emulsions that have a limited work life.

Key Features and Typical Benefits

- Single component coating
- Excellent freeze release characteristics
- Excellent abrasion resistance
- Water based, lower VOC content and NMP free formulation
- Low static, dynamic CoF, and smooth transition for low noise generation
- Extended bath and storage life
- Excellent adhesion to EPDM , TPE and other rubber formulations
- Fast heat cure process (approx.1 minute)
- Long term performance

Typical Physical Properties

Property	WSC1042 Clear Silicone Base Emulsion
Color	Pale Yellow

Solids Content (%)	29
Density (@ 23°C)	1.026
Viscosity (DIN 4 cup @ 23°C (seconds))	15
Viscosity (mPas , Brookfield #2 @ 30 rpm)	7.0
pH	8.5
Solvent	Water

Typical properties are average data and are not to be used as or to develop specifications.

Typical Cured Product Properties

Property	Test Method	Value
Coefficient of friction (Static and Dynamic)	DIN 53375	~ 0.3
Abrasion Resistance (Crockmeter 900 g load)	Dry Crockmeter	> 5000 cycles
Appearance	Visual	Matte Black
Freeze Release	TL 523 45	Pass
Repaintability	TSM 1701 G	Pass
Paint Staining	TSM 1701 G	Pass

Typical properties are average data and are not to be used as or to develop specifications.

Typical Cure Schedule

Complete cure in any specific application is a function of coating thickness, part geometry and the heat transfer characteristics of the substrate to which the coating is being applied.

Although the prepared coating will cure at an ambient temperature, it is not recommended as the adhesion and full abrasion performance may not be realized. An absolute minimum part temperature range of 80-120°C at the point of application is recommended to achieve the full coating performance.

NOTE : Curing at ambient temperature is not recommended.

Part Temperature (actual not oven set point)				
Cure Temperature (°C)	160°C	150°C	100°C	80°C
Cure Time (at temperature)	1 minute	2 minutes	5 minutes	10 minutes

Typical Coating System Preparation

The coating is supplied ready to use but may be diluted for dip tank application or where multiple spray nozzles are being used.

General Considerations for Use

It is vitally important to thoroughly mix the WSC1042 clear base component to ensure any settled ingredients are well re-dispersed before use, as settling of the matting agent and friction modifier can occur on storage. Once fully mixed (be sure that no sediment remains in the pail), the coating is ready to use.

The bath should be kept under constant agitation to prevent settling of the active powders and to ensure maximum bath life. For best results, the substrate should be clean and dry and have a minimum temperature of 80°C, as lower application temperatures can adversely affect the adhesion and appearance of the coating. In general, temperatures up to 160°C or higher for a limited duration will not affect the coating and may actually lead to productivity gains.

For optimum coating adhesion and performance, ensure all surfaces are clean and dry before applying the coating solution. The substrate temperature should be between 80 – 230°C for on-line application and a minimum of 80°C part temperature at the time of coating for off-line applications.

WSC1042 clear weatherstrip coating is recommended to be sprayed, although dip coating has been used with success.

This coating is generally applied using multiple HVLP or electrostatic spray guns with an aircap diameter > 1.0mm. To avoid blocking of the guns, the coating should be filtered through a 200 micron mesh after the coating is prepared. It is a good practice to install a further filter between the holding tank and spray guns. Most on-line applications use multiple spray guns to achieve even coverage of the profile during extrusion.

It is important to apply sufficient material to achieve an initial wet look in order to help ensure continuous coverage and good coating adhesion. It is also possible to employ multiple spray heads in tandem in order to help ensure sufficient coating is applied and that no areas are left uncoated during the application process.

Typical bath life is 22 - 36 hours in a closed container which does not allow the surface to dry and form a skin which cannot be re-dispersed. Continuous slow speed agitation of the coating bath is recommended to reduce the possibility of settling of the matting agents and friction modifiers.

The applied coating thickness will depend on the application method and the required end-use requirements. Dry film thicknesses are typically between 3 and 10 microns dry film thickness.

Current Packaging

WSC1042 clear

20 liter plastic pails with 18 kg fill

Patent Status

本書のいかなる内容も、関連特許が存在しないことを暗示したものではありません。またいかなる特許についても、その権利者による許可なしに、その特許が対象とする発明を実施するための許可、誘因または推奨を構成することはできません。

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE

EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.