

## ECC3051S

### Solvent Free Conformal Coating

#### Description

ECC3051S is a one-component, low viscosity silicone conformal coating material that cures on exposure to atmospheric moisture to form a flexible protective coating. ECC3051S conformal coating cures quickly in ambient conditions without the need for curing equipment, and can achieve faster tack-free time with exposure to mild heat. ECC3051S conformal coating can help reduce the potential for corrosion of electronic components, and under certain test conditions\* has been found to surpass other polymers such as acrylics, polyurethane, polyolefin and other silicone polymers in corrosion prevention.

#### Key Features and Typical Benefits

- Fast tack-free time
- Low volatility
- Solvent-free formulation (100% solid content)
- Contains UV indicator for ease in inspection under black light
- Continuous operating temperature range of -40 ~ 150 °C
- Flame retardant: UL94V-0 certified (File No. E135148)
- Meets IEC60068-2-52 Severity 5 standard for Salt Spray performance
- Meets IEC60068-2-60 Method 4 standard for Mixed Gas Corrosion performance
- Meets IPC-CC-830B / MIL-I-46058C standard for Appearance, Fluorescence, Thickness, Flexibility, Dielectric Withstanding Voltage, Moisture and Insulation

Resistance, Thermal Shock, Temperature and Humidity Aging.

### Typical Physical Properties (JIS K 6249)

<u>Property</u>	<u>Unit</u>	<u>Value</u>
<b>Typical Uncured Properties (23 °C / 50% RH)</b>		
Appearance		Translucent
Viscosity	mPa·s	550
Tack-free Time <sup>(1)</sup>	min	5
Cure Time <sup>(2)</sup> (23 °C, 50% RH)	min	30
Cure Time <sup>(2)</sup> (60 °C, 15% RH)	min	2

### Typical Physical Properties, continued

<u>Property</u>	<u>Unit</u>	<u>Value</u>
<b>Typical Cured Properties (3 days at 23 °C / 50% RH)</b>		
Appearance		Translucent
Density	g/cm <sup>3</sup>	0.98
Hardness (Type A)		22
Volume Resistivity	MΩ·m {Ω·cm}	1 x 10 <sup>7</sup> {1 x 10 <sup>15</sup> }
Dielectric Strength	kV/mm	20
Dielectric Constant (60Hz)		2.60
Dielectric Loss (60Hz)		0.001
Low Molecular Siloxane (D <sub>4</sub> -D <sub>10</sub> )	wt%	0.01

Typical properties are average data and are not to be used as or to develop specifications.

<sup>(1)</sup>Thickness: 100 um

<sup>(2)</sup>Thickness: 100um, 180 °peel

### Potential Applications

- Conformal coating of electrical and electronic parts
- Moisture-proof coating of circuit boards
- Thin section potting of electrical and electronic parts

### **General Considerations For Use**

- Substrate surface should be thoroughly cleaned with a suitable solvent such as alcohol, xylene methyl ethyl ketone (MEK) etc.
- Wear eye protection and protective gloves as required while handling.
- Adequate ventilation must be maintained in the work area at all times.
- While the typical operating temperature for silicone materials ranges from -45°C to 200°C, the long-term maintenance of its initial properties is dependent upon design related stress considerations, substrate materials, frequency of thermal cycles, and other factors.

### **Currently Available Packaging**

- 1kg can in case of 10
- 18kg pail
- 18kg bladder pack

\*Based upon comparative tests performed by or contracted by Momentive and conducted in 2016 according to IEC standards for salt spray and mixed gas corrosion tests, using a sample of select non-Momentive, competitive product offerings.

### **Patent Status**

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392	<b>Brazil</b>	<b>Europe</b>	<b>China</b>
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	<b>Mexico</b>	<b>India, Middle East &amp; Africa</b>	<b>Japan</b>
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number

**\*All Middle Eastern                      Korea**  
**countries, Africa, India,                +82 2 6201 4600**

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.