

InvisiSil™ IVS9520 Highly Transparent Glob Top

Description

InvisiSil* IVS9520 is two-component, high transparency, low viscosity and thixotropic liquid silicone rubber. This product cures with heat to an elastic rubber and can help provide high heat/UV-light resistance.

InvisiSil IVS9520 highly transparent glob top can enable consistent dispensing performance and flow-ability to form a good dome shape for COB (chip on board) LED and SMD LED Package.

Key Features and Typical Benefits

- Self-Dome Lens Formation
- High transparency
- No yellowing
- Excellent high and low temperature resistance
- UV resistance
- Excellent adhesion
- Thixotropic consistency

Typical Physical Properties

<u>Typical Physical Properties of the Uncured Rubber</u>		A Component	B Component
Appearance		Translucent	Turbid

Viscosity (23 ° C)	Pa.s	9	0.5
Mix ratio by weight		5.1	
Viscosity after mixing (23 ° C) ⁽¹⁾	Pa.s	18	
Viscosity after mixing (23 ° C) ⁽²⁾	Pa.s	81	
Pot Life (23 ° C)	hr	8	
<p>(1); No. 6 spindle, 20rpm (2); No. 6 spindle, 2rpm</p> <p><u>Typical properties of the cured rubber:</u> Mixing ration of components A : B = 5 : 1; Curing : 3hr. 150°C</p>			
Basic Properties			
Density (23 ° C)	JIS K 6249	g/cm3	1.08
Shore A hardness	JIS K 6249		50
Tensile strength	JIS K 6249	MPa	6.8
Elongation at break	JIS K 6249	%	130
Lap shear strength (Aluminum)		MPa	2.5
Optical Properties			
Transmittance (1mm) %		400nm	96
		700nm	98
Refractive Index at 25°C : 589nm		(n _D ²⁵)	1.43
Thermal Properties			
CTE linear (40-90°C)		ppm/°C	270

Typical properties are average data and are not to be used as or develop specificatons.

*InvisiSil is a trademark of Momentive Performance Materials Inc.

Potential Applications

InvisiSil IVS9520 highly transparent glob top is an excellent candidate to consider for use in the following elastomeric articles:

- LED Lighting COB and lens application
- Other illumination optics

- Auto Lighting COB and lens application
- Electronics Flash lens of mobile phone camera module

Sensing lenses

Other optics

- Solar Secondary optics for concentrating PVs

General Considerations for Use

Each of the components ((A) and (B)) need to be weighed out to the clean container by ratio of 5:1. And then, mix them thoroughly with clean tools to generate thixotropy. Careful mixing (especially on the bottom and the side of the container) is necessary. The mixture needs to be deaerated to remove air entrapped during mixing. Dispense the mixture on the part to cure with heat. Stepwise cure is recommended. Recommended conditions are 80°C for 1hr (1st step) and 150°C for 3hrs (2nd step). All parts should be as clean and dry as possible prior to applications. Materials such as water, sulfur, nitrogen compounds, organic metallic salts, phosphorus compounds, etc. contained in the surface of the substrate can inhibit curing. It is recommended that a preliminary test is performed to determine the compatibility.

Packaging Types

InvisiSil IVS9520 highly transparent glob top currently is available in bottle kit (5P of 500g-A and 1P of 500g-B)

Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-

the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		*All Middle Eastern countries, Africa, India,	Korea
			+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*InvisiSil™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.

