

## SilForce™ SL6031

### CRA for Thermal Solventless System

#### Description

Silforce SL6031 is a general purpose Controlled Release Additive (CRA) for use with our base polymer pre-blends, such as SilForce SL6162, SL6962 and SL7562S, primarily in the manufacture of glassine and PE coated kraft papers to increase release force. It can also be used for Kraft paper and PET films by adjusting the level of catalyst accordingly and selecting the right cross-linker. When coating PET film the Anchorsil\* 2000 adhesion promoter can be added into the bath as a candidate for untreated PET films.

#### Product References

- SilForce SL6162: Base polymer
- SilForce SL6031: Controlled release additive
- SilForce SL6210: Concentrated catalyst (Pt)
- SilForce SL4380: Cross-linker for papers and films (1)

(1) Depending on the substrate and/or processing conditions other cross-linkers may be considered.

#### Key Features and Typical Benefits

- System versatility for all release liners (papers & films)
- Lower-temperature curing enabled

- New generation of inhibitor for fast system
- High formulation flexibility
- Enhanced cross-linker for good anchorage of the release coating
- Productivity gain in terms of machine capacity

### Typical Physical Properties

**Table 1:**

Property	SilForce SL6162	SilForce SL6031
Viscosity, cstks, 25 °C	170 - 300	1500 - 2700
Density, kg/l	0.97	1.04

Typical properties are average data and are not to be used as or to develop specifications.

### Potential Applications:

SilForce SL6031 in combination with a base polymer coating, cross-linker and catalyst may be considered for use with standard liners used in the label industry, such as:

- Glassine papers
- SCK papers
- Clay-coated kraft papers
- PE coated papers
- PET films
- Polyolefin films

### General Considerations for Use

The SL6031 CRA in combination with a solventless release base polymer (like SilForce SL6162 for example) can be applied by any of the methods now being used commercially for solventless silicone, including three rolls differential, offset gravure, and various multiple smooth rolls configurations. Heat should be applied immediately after coating to initiate cure. Best results are obtained with zoned ovens. Operating the first oven zone at 90-120 °C will allow the coating to level, forming a continuous film before cure is initiated. Subsequent oven zones should be sufficiently high to achieve the required web exit temperature. Actual temperatures required for complete cure will



as well as ambient conditions. At levels shown in the sample formulations, the expected minimum bath life is 6-8 hours under normal processing conditions.

As the thin film bath life of the SilForce SL6162 system is significantly shorter than the thin film bath life of the SilForce SL6600, SL6625 etc. systems, the coating head should be cleaned if the machine is stopped for more than 20 minutes

### **Bath Preparation**

To ensure consistent results and maximize bath life, components should be mixed in the following order:

1. Weigh and add polymers (SilForce SL6162 for example) to a clean, rust-free container/mixing vessel
2. Weigh and add the CRA SilForce SL6031
3. Agitate thoroughly
4. Weigh and add the crosslinker (for example SilForce SL4330) to above mix
5. Agitate thoroughly
6. Weigh and add the platinum concentrate (SilForce SL6210) to above mix
7. Agitate thoroughly
8. Weigh and add the Anchorsil\* 2000 to above mix (when needed)
9. Agitate thoroughly for 10-15 minutes to ensure homogeneity.

Bath should be prepared just prior to use.

### **Coating Weight/Substrates**

The optimal coat weight will depend on the hold out and resolution of the surface, but generally 0.8-1.6 g/m<sup>2</sup> will provide a continuous silicone film. Coat weights can be determined by X-Ray Fluorescence.

### **FDA Status**

SilForce SL6031 controlled release additive is compositionally compliant with 21 CFR 175.320 (resinous and polymeric coatings for polyolefin films). The end user has sole responsibility for determining that its product complies with all applicable FDA specifications and limitations and is fit for food contact use.

### Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392	<b>Brazil</b>	<b>Europe</b>	<b>China</b>
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free

Direct Number			+86 21 3860 4892
			Direct number
*All American countries	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	<b>Japan</b> +81 3 5544 3111 Direct number
		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such

modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SilForce™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.