



SilFORT™ MHC2710 Clearcoat

Description

SilFORT MHC2710 Clearcoat is a thermally cured, siloxane-based, primerless hardcoat system used principally to protect bare aluminum substrates. Allowing the elimination of the anodization process for certain applications, its use can lead to significant cost savings and an improved sustainability profile. SilFORT MHC2710 Clearcoat offers scratch resistance, chemical resistance, as well as excellent acid and alkali resistance in the range of pH 1.0 to 13.5, while allowing the appearance of the substrate to be maintained. Series 3000 and 5000 aluminum alloys treated with SilFORT MHC2710 Clearcoat will typically exhibit the best corrosion performance in salt spray testing.

This direct-to-metal sol-gel coating system can generally be applied by either spray, dip, or flow coating, allowing for greater design freedom. Curvatures, radii and orifices can typically be managed in the coating process without making any design compromises. The gloss level of the coating can also be adjusted to the desired optical appearance by the incorporation of Momentive's SilFORT MHC Matte additive, allowing high gloss, semi-gloss and low gloss parts.

Key Features and Typical Benefits

- Direct-to-metal / primerless adhesion
- Elimination of anodization process
- Exceptional pH resistance (pH 1.0 to >13.5)
- Good corrosion resistance
- Excellent scratch resistance
- Excellent chemical resistance
- Wide application window

Typical Physical Properties

Property ⁽¹⁾	Unit	SilFORT MHC2710 Clearcoat	
Physical Form	-	Liquid	
Color	-	Colorless	
Solids Content	%	Approx.25	
Density (@ 25°C)	g/cm ³	Approx. 0.98	
Kinematic Viscosity (@	cSt	Approx. 4	
25°C)			
рН	-	Approx. 5	
Shelf Life ⁽²⁾	Days	90 (stored below 10°C)	

1. As supplied. Typical properties are average data and are not to be used as or to develop specifications.

2. From date of manufacture.

Potential Applications

- Exterior automotive parts made from aluminum (e.g. window trim, roof rails)
- Interior automotive parts made from aluminum
- Cookware
- Industrial parts

General Considerations for Use

	SilFORT MHC2710 Clearcoat
Application Method	Spray, flow, dip
Reducing Solvents ⁽³⁾	1-Butanol (CAS# 71-36-3)
	2-Propanol (CAS# 67-63-0)
Recommended Coating Thickness ⁽⁴⁾	4.0 – 6.0 μm

3. If necessary for application process, other suitable solvents may be considered.

4. Other thicknesses can be considered but may affect performance.

SilFORT MHC2710 Clearcoat is a cross-linking product, sensitive to extended exposure to elevated temperature. Storage at lower temperatures (< 0°C) may increase typical shelf-life beyond 3 months.

Once the product has reached ambient temperature it should be used within 7 days. Re-refrigeration to less than 10°C should be considered when product will not be used within 24 hours.

For a particle-free surface, components should be processed in a climate-controlled cleanroom environment that complies with ISO14664-1, equal to or lower than class 6.

Before applying any coating, part surface temperature should be <35°C.

For more detailed guidance on the use of SilFORT MHC2710, please request the accompanying Processing Guide, from your local Momentive representative.

Packaging

Products are currently available in:

- 5 Gallon Pail (40.0 lbs, 18.2 kg)
- Other packaging sizes available upon request

Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되 어서는 안됩니다.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an aroundthe-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information Email commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American	Mexico	India, Middle East &	Japan
countries	+52 55 2169 7670	Africa	+81 3 5544 3111
	Direct Number	+ 91 44 71212207	Direct number
		Direct number*	
		*All Middle Eastern	Korea
		countries, Africa, India,	+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH. SUPPLIER MAKES NO WARRANTY OR **GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED** HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE. SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS **OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilFORT™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.