

SiIFORT™ SHC1200

SiIFORT* SHC1200

Description

SiIFORT SHC1200 Hard Coat

SHC1200 hard coat has been found to yield a clear mar-resistant film when applied to a suitably prepared plastic substrate. It can be applied by flow, dip or spray coating.

SiIFORT SHP401 Primer

SHP401 air-dried primer is used as an adhesion promoter for SHC1200 hard coat on polycarbonate resin. It can be applied by flow, dip or spray coating.

Key Features and Benefits

- Fast cure
- Abrasion resistance
- Scratch resistance
- Good clarity
- Solvent/chemical resistance

SHP401 Primer

- No thermal cure required
- Improves coating adhesion
- Improves water resistance

- Improves ultraviolet resistance

SHP401 Primer/SHC1200 Hard Coat on polycarbonate (2 - 4 micron Topcoat Thickness)

Cured Film Properties

Film Thickness, slow dip coat, 10-18 cm/min withdrawal, 18-20% solids at 22C	2 – 4 micron
Taber Abrasion, 500 cycles 500G on primed polycarbonate (CS10F wheel)	< 6.0 % Haze measured per ASTM D1003. *
Index of Refraction	1.4

*Humidity during coating and testing will affect final values.

Typical Physical Properties

Property	SHC1200 Hard Coat	SHP401 Primer
Solids Content, %	20 ± 1	2.1 ± 0.2
Solvent	Methanol, Isobutanol, Isopropanol	1-Methoxy-2-propanol, Diacetone Alcohol
Flash Point, PMCC	19.4C	36.1C
Density, g/cm ³	0.911	0.959
p ^H	7.3 ± 0.2	-
Viscosity, cstk @ 25°C	20 ± 3	4 - 7
Dry Film Thickness, micron	2.75 - 4.5	0.5
VOC, g/l	710	937

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

CAUTION

Compatibility of Momentive Performance Materials hard coat and polycarbonate resin is dependent on a number of factors including operational stresses, chemical exposure,

temperature levels, impact and exposure to ultraviolet light.

While it is up to the end user to determine what application specific testing is appropriate, it is suggested that all polycarbonate resin applications be tested for at least thirty (30) days for compatibility and crazing with this hard coat before use. There is no dependable substitute for careful testing of prototypes of production parts in typical operating environments.

SHC1200 Hard Coat

Refrigeration is required.

The warranty period is 3 months form date of shipment from Momentive Performance Materials if stored in the original unopened container at or below -15 °C (<5 °F).

SHP401 Primer

Store and ship at ambient temperature approximately 2-43°C.

When stored in original sealed containers, SHP401 primer will have a warranty period of 6 months. Exposure to low temperatures may cause some solid precipitation. If this occurs, the precipitate may be redissolved by submerging the vented container in a water bath. Mix until homogeneous.

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safehandling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

General Requirements

Coating area should be clean, dust-free, well-ventilated and with the relative humidity controlled to 40% +/-10% as required to achieve acceptable coated appearance and performance. If necessary, parts should be washed or wiped clean with isopropyl alcohol, a mild detergent solution and clean water rinse, or an ultrasonic bath followed by a filtered air blow-off and a final ionized-air blow-off. Cleanliness is critical for the production of good parts. Both primer and hard coating solutions should be filtered continuously or just prior to use to approximately 0.5 to 1.0 micron, using a 3 to 5 micron pre-filter. Electric or indirect gas-fired ovens with good convection and air exchange are recommended.

SHC1200 Hard Coat

The hard coat can be applied to primed parts by dip, flow, or spray coating in a well ventilated area. Use caution. Methyl alcohol, Isopropyl alcohol, Diacetone alcohol and Isobutyl alcohol contained in SHC1200 hard coat are hazardous. Read HANDLING & SAFETY. Do not proceed until this information is read and understood. Relative humidity in the coating area should not exceed 50% to avoid solvent blushing. The equipment used to apply SHC1200 silicone resin is of the same type used for the primer. Additionally, the dip tank must be refrigerated so that the hard coat resin can be maintained at about 4C. Maintain constant circulation and < 1 micron filtration. SHC1200 hard coat should air dry for about 20 minutes followed by thermal cure. After reaching part temperature, the coating cures at 130C in 30 minutes. For acrylic substrates cure at 90C for 1 - 2 hours.

SHP401 Primer

The primer can be applied by dip, spray or flow coating to polycarbonate parts that have an initial stress level under 1000 psi. If a higher stress level is found to exist, the tool and molding conditions should be adjusted to reduce residual stress on parts. Alternatively, parts can be annealed to reduce stress, (for example, 30 minutes at 130C for each 2.5 cm of part thickness.) If necessary, primer solids content may be reduced by adding 1-Methoxy-2-Propanol/Diacetone alcohol (85/15) or pure 1-Methoxy-2-Propanol. The primer should be applied to obtain a dry film thickness of approx. 0.5 micron. After application, the primer should air dry until tack free (approximately 10 minutes). Recirculate the primer through a 1micron or finer filter.

Availability

SHC1200 hard coat and SHP401 can be ordered from Momentive Performance Materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY

“SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SiIFORT™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.