

## Silopren™ LSR 2725/40

Liquid Silicone Rubber

### Description

Silopren LSR 2725/40 is a two-component liquid silicone rubber for injection molding, which offers robust primer-less adhesion to a wide range of substrates including PBT but without adhesion to the mold. The initial bond strength allows for demolding, however full bond strength is reached after some storage at room temperature. Additionally, Silopren LSR 2725/40 is self-lubricating. The self-lubricating effect is achieved by a fluid which exudes out of the vulcanizate over an extended period of time. It typically starts between a few hours and one day after vulcanization. This combination of features makes Silopren LSR 2725/40 liquid silicone rubber ideal for cost-efficient injection molding of hard-soft-combinations with integrated and lubricated sealing.

### Key Features and Typical Benefits

- Primer-less adhesion to many thermoplastic
- No adhesion to the mold /no special mold treatment needed
- Self-lubricating for easy assembly
- High temperature stability
- Excellent stability and flexibility at low temperatures
- Favorable aging behavior and weathering resistance
- Good dielectric and mechanical properties
- Easy to be pigmented with LSR color-pastes

### Potential Applications

Because of its outstanding adhesion properties, Silopren LSR 2725/40 liquid silicone rubber is an excellent candidate for manufacturing parts where engineering plastics

need to be combined with integrated sealing or dampening properties in an over-molding or insert molding process.

- Connector-Assemblies
- Housings and Boxes
- Other soft-hard combinations

**Typical Physical Properties**

<u>Typical physical properties of the uncured rubber:</u>		<b>A-Part</b>	<b>B-Part</b>
Appearance		Whitish	Translucent
Viscosity in Pa•s at 20°C and shear rate = 10 s <sup>-1</sup>	DIN 53018	500	300

<u>Typical physical properties of the vulcanized rubber:</u>			
Mix ratio A:B = 1:1; Vulcanization conditions: 10 min. 175 °C			
Density	DIN 53 479 A	g/cm <sup>3</sup>	1.10
Hardness	DIN 53 505	Shore A	40
Tensile strength	DIN 53 504 S2	N/mm <sup>2</sup>	8
Elongation at break	DIN 53 504 S2	%	600
Tear strength	ASTM D 624 die B	N/mm	35
Compression Set, 22h at 120 °C	DIN ISO 815	%	10
Compression Set, 22h at 150 °C	DIN ISO 815	%	20

Typical properties are average data and are not to be used as or to develop specifications.

**General Considerations for Use**

Ready-to-use mixtures (of the components A and B) are typically fed directly to the injection-molding machine from the original kits by means of a metering and mixing unit. The mixture, consisting of the two components in the ratio 1:1, is injected into the heated mold. The fast curing process does not generate by-products. Silopren LSR 2725/40 liquid silicone rubber contains 2% of a special silicone fluid, which migrates to the surface of the molded part over time and provides a self-lubricating effect. This process however, is influenced by several factors, which are specific for each part and depend upon:

- ratio of the volume to the surface area
- type and concentration of pigment added

- storage time and temperature

### **Compliance**

Silopren LSR 2725/40 liquid silicone rubber is not compositionally compliant with 21 CFR §177.2600. and should only be used for the production of technical articles. For further information please contact Momentive Performance Materials.

### **Packaging**

Silopren LSR 2725/40 is currently available in 2 x 20 kg Pail-Kits and 2 x 200 kg Drum-Kits.

### **Patent Status**

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### **Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### **Contact Information**

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	<b>Brazil</b> +55 11 4534 9650 Direct Number	<b>Europe</b> +390510924300 Direct number	<b>China</b> 800 820 0202 Toll free +86 21 3860 4892 Direct number
*All American countries	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	<b>Japan</b> +81 3 5544 3111 Direct number
		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE

**FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Silopren™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.