

## Silopren™ LSR 3696/25

### Silopren\* LSR 3696/25

Liquid Silicone Rubber

#### Description

**Silopren LSR 3696/25** liquid silicone rubber is a two-component liquid silicone rubber for injection moulding processes. This material is an excellent candidate to consider for the manufacture of elastomeric articles requiring self-lubricating properties. The self-lubricating effect is achieved by a fluid which exudes out of the vulcanizate over an extended period of time. It typically starts between a few hours and one day after vulcanization. **Silopren LSR 3696/25** liquid silicone rubber shows an excellent compression set after vulcanization without post-curing.

#### Key Features and Typical Benefits

Vulcanizates consisting of **Silopren LSR 3696/25** liquid silicone rubber are typically distinguished by the following properties:

- ultra-low compression set without post-cure
- self-lubricating properties
- low viscosity
- fast cure
- low modulus
- high thermal stability
- increased crack resistance
- outstanding resistance to aging
- easy to color

#### Typical Physical Properties

Typical properties of the uncured material:			
		<b>A-Part</b>	<b>B-Part</b>

Appearance			whitish	whitish
Fluid Content		%	6	6
Viscosity $\gamma=10s^{-1}$ at 20°C	DIN 53 018	Pa·s	270	300
The pot-life of the mixture of the two components (closed vessel) at 20 degrees Celsius is three days. Increased temperatures reduce the pot-life. <u>Typical properties of Silopren LSR 3696/25 liquid silicone rubber:</u> Mixing ratio of components A:B=1:1. Vulcanization: 10 min. at 175°C				
Density		DIN 53 479 A	g/cm <sup>3</sup>	1.08
Hardness		DIN 53 505	Shore A	24
Modulus 50%		DIN 53 504 S2	N/mm <sup>2</sup>	0.3
Modulus 100%		DIN 53 504 S2	N/mm <sup>2</sup>	0.5
Modulus 200%		DIN 53 504 S2	N/mm <sup>2</sup>	1
Modulus 300%		DIN 53 504 S2	N/mm <sup>2</sup>	1.5
Tensile strength		DIN 53 504 S2	N/mm <sup>2</sup>	6.5
Elongation at break		DIN 53 504 S2	%	710
Tear strength		ASTM D 624 die B	N/mm	12
Compression set (22h/175°C)		DIN ISO 815	%	19

Typical data are average data and are not to be used as or to develop product specifications.

### Potential Applications

Because of the outstanding properties, **Silopren LSR 3696/25** liquid silicone rubber is an excellent candidate to consider for use in wire harness applications for the following elastomeric articles:

- cable seals
- mat seals
- grommets
- gaskets
- plug seals

### Processing Considerations:

Ready-to-use mixtures (of the components A and B) are typically fed directly to the

injection-molding machine from the original drums by means of a metering and mixing unit. The mixture, consisting of the two components in the ratio 1:1, is injected into the heated mold. At mold temperatures of 170-230 degrees Celsius, the addition-curable silicone rubber usually cures within a few seconds. The curing process does not generate splitting products. High curing speed and easy demolding can help enable fully automated production of large numbers of articles in short cycle times. **Silopren LSR 3696/25** liquid silicone rubber contains 6 percent of a special silicone fluid, which migrates to the surface of the molded part over time and provides a self-lubricating effect. This process, however, is affected by several factors, which are specific for each part and depend upon:

- ratio of volume to surface area
- type and concentration of pigment added
- storage time and temperature during storage

**Silopren LSR 3696/25** liquid silicone rubber should only be used for the production of technical articles. For further information please contact Momentive Performance Materials Inc.

#### **Packaging:**

**Silopren LSR 3696/25** liquid silicone rubber is available in 2x20kg pail kits and 2x200kg drum kits.

#### **Patent Status**

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

#### **Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order

Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

**Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

**Contact Information**

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

**Telephone**

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392	<b>Brazil</b>	<b>Europe</b>	<b>China</b>
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	<b>Mexico</b>	<b>India, Middle East &amp; Africa</b>	<b>Japan</b>
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b>
			+82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS**

**OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Silopren™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.