

AnchorSil* 2000

AnchorSil* 2000

Description

AnchorSil 2000 anchorage additive is a 100% active organo-functional reactive polymer designed to improve anchorage of Momentive thermally cured solventless silicone release coatings to polyester films.

Key Features and Benefits

- Improves anchorage on a variety of treated and untreated polyester films
- Improves anchorage of formulations with and without controlled release additive
- Compatible with all Momentive thermally cured solventless silicone release coatings
- Easily mixes with Momentive thermally cured solventless silicone release coatings
- Does not adversely affect release performance, coverage and bath life of release coatings

Typical Physical Properties

Property	Value	Unit of Measure
Viscosity @ 25°C	215	cst, 25°C (77°F)
Density	8.819	Lbs./gal
Specific Gravity	1.060	-
Hydride Content	0.7	weight %
Flash Point (PMCC)	82	°C

Potential Applications

AnchorSil 2000 anchorage additive may be used with all Momentive vinyl functional solventless thermally cured silicone release coatings for improved anchorage on a variety of polyester films.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

The limited warranty period is 3 months from date of shipment from Momentive Performance Materials if stored in the original unopened container below 4°C (39°F). Note that Anchorsil 2000 anchorage additive is a reactive product and can evolve hydrogen over time if stored at temperatures greater than 4°C (39°F) (See Figure 4). Storage at temperatures greater than 4°C (39°F) will also shorten storage life (see Figure 5). If frozen, care should be taken not to introduce moisture from condensation. Opened, partially used containers should be tightly recapped and returned to storage below 4°C (39°F) when not in use. Introduction of moisture should be avoided and if capable, a dry nitrogen atmosphere should be replaced in order to ensure optimum storage stability.

Figure 4: AnchorSil 2000 Anchorage Additive Hydrogen Evolution Versus Storage Temperature





Figure 5: AnchorSil 2000 Anchorage Additive Viscosity Stability Versus Storage Temperature



Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains

an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Processing Recommendations

AnchorSil 2000 anchorage additive is compatible with all Momentive thermally cured solventless silicone release coatings. For best results, it should be added to the silicone formulation at the same time the crosslinker is added and thoroughly mixed prior to use. The level of addition will depend on the type of polyester film and actual curing conditions. In general, 2 to 4 parts per hundred (pph) polymer addition of AnchorSil 2000 anchorage additive is sufficient to obtain optimum anchorage, but the actual required concentration should be established and optimized during extensive machine trials by the customer.

Table 1: Typical Starting Formulations for SL6625/SL6635 Release Coating System

	AnchorSil 2000 Anchorage Additive Concentration							
	0 pph		2 pph		3 pph		4 pph	
Component	Parts by Weight							
SL6625	100	75	100	75	100	75	100	75
SL6635	0	25	0	25	0	25	0	25
AnchorSil 2000 anchorage additive	0	0	2	2	3	3	4	4
SS4300C ⁽¹⁾	3.3	4.3	2.4	3.5	2.0	3.0	1.6	2.6

(1)SS4300C concentrations adjusted for hydride content in AnchorSil 2000 anchorage additive to maintain a constant SiH:Vi ratio. Contact your local Momentive technical or sales representative for further assistance.

Table 2: Typical Starting Formulations for SL7025 Release Coating System

	AnchorSil 2000 Anchorage Additive Concentration			
	0 pph	2 pph	3 pph	4 pph
Component	Parts by Weight			
SL7025	100	100	100	100
AnchorSil 2000 anchorage additive	0	2	3	4
SS4300C ⁽²⁾	4	3.1	2.7	2.3

(2)SS4300C concentrations adjusted for hydride content in AnchorSil 2000 anchorage additive to maintain a constant SiH:Vi ratio. Contact your local Momentive technical or sales representative for further assistance.

Note: Since AnchorSil 2000 anchorage additive contains hydride, the final amount of crosslinker in the formulation needs to be adjusted to maintain equal hydride to vinyl (SiH:Vi) ratio in formulations. This is particularly important in pressure sensitive constructions utilizing adhesives that are sensitive to hydride level. Thorough evaluation of the finished product performance is recommended before large quantities of material are manufactured.

AnchorSil 2000 anchorage additive improves the anchorage of thermally cured solventless silicone release coatings to a variety of polyester films. Higher web temperature, longer dwell time and in-line corona treatment have been found to further improve anchorage. On some substrates and at specific curing conditions, corona treatment may be optional although still recommended as illustrated in Table 3 and Table 4.

Table 3: SL7025 Anchorage on Polyester Film at Various Web Temperatures and Oven Dwell Times.

		SL7025 with 3 pph AnchorSil 2000 Anchorage Additive	SL7025 with 3 pph AnchorSil 2000 Anchorage Additive	SL7025 only
Exit Web Temp	Dwell Time	With Corona	Without Corona	With Corona
(°F)	(sec)	(2W/ft ² /min)	–	(2W/ft ² /min)
250	6	No Rub Off	No Rub Off	Rub Off
250	4	No Rub Off	No Rub Off	Rub Off
250	3	No Rub Off	No Rub Off	Rub Off
250	2	No Rub Off	Rub Off	Rub Off
280	6	No Rub Off	No Rub Off	Rub Off
280	4	No Rub Off	No Rub Off	Rub Off
280	3	No Rub Off	No Rub Off	Rub Off
280	2	No Rub Off	Rub Off	Rub Off

Note: Black Clawson 5 roll coater, 142 gauge SKC polyester film, 95% RH chamber, 24 hours at 600°C


Table 4: SL6625 Anchorage on Polyester Film at Various Web Temperatures and Oven Dwell Times.

		SL6625 with 3 pph AnchorSil 2000 Anchorage Additive	SL6625 with 3 pph AnchorSil 2000 Anchorage Additive	SL6625 only
Exit Web Temp	Dwell Time	With Corona	Without Corona	With Corona
(°F)	(sec)	(2W/ft ² /min)	–	(2W/ft ² /min)
250	6	No Rub Off	Rub Off	Rub Off
250	4	No Rub Off	Rub Off	Rub Off
250	3	No Rub Off	Rub Off	Rub Off
250	2	No Rub Off	Rub Off	Rub Off
280	6	No Rub Off	No Rub Off	Rub Off
280	4	No Rub Off	No Rub Off	Rub Off
280	2	No Rub Off	Rub Off	Rub Off

AnchorSil 2000 anchorage additive does not affect coverage or bath life of formulated release coatings. At higher web temperatures, cure is not affected (see Figure 1). At lower web temperatures and shorter dwell times (e.g. higher line speeds), the cure is slower for formulations containing 3 pph AnchorSil 2000 anchorage additive versus the control formulation (see Figure 2). AnchorSil 2000 anchorage additive


concentration and cure conditions should be optimized to maintain the desired level of extractable silicone at the best possible anchorage.

Figure 1: SL7025 With and Without 3 pph AnchorSil 2000 Anchorage Additive – Cure Profiles at 280°F Web Temperature



Note: Black Clawson pilot coater, 1.5 mil polyester film, 0.6 lbs/ream coating weight

Figure 2: SL7025 With and Without 3 pph AnchorSil 2000 Anchorage Additive - Cure Profiles at 250°F Web Temperature




Note: In order to obtain comparable cure between formulations with and without AnchorSil 2000 anchorage additive, it may be necessary to adjust crosslinker level. In doing so however, thorough evaluation of the finished product performance is recommended especially in the case where hydride sensitive adhesives are being used.

When fully cured at higher web exit temperatures, comparable release performance of SL6625 easy release coating with various levels of SL4406 controlled release additive with and without AnchorSil 2000 anchorage additive at equal hydride to vinyl ratios is illustrated in Figure 3.

Figure 3: Release Performance of SL6625 with SL4406 Controlled Release Additive Tested with Tesa 7475 Tape After 4 Weeks RT Aging - Comparison Between Formulations With and Without 3 pph

AnchorSil 2000 Anchorage Additive



Note: Pilot coater, 3 roll Differential Offset Gravure, 142 gauge SKC polyester film, coatings formulated at constant hydride to vinyl ratio of 2.3:1, Tesa 7475 applied offline and aged for 4 weeks at standard RT conditions

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

For product prices, availability, or order placement, contact our customer service at Momentive.com/CustomerService/

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and

perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*AnchorSil is a trademark of Momentive Performance Materials Inc.1033

Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.