

## Magnasoft™ SilQ

### Magnasoft\* SilQ

#### Description

The globalization of the textile markets has had significant repercussions for the industry, not the least of which is the ever-increasing number of new lines that are being launched annually by retailers. This has affected textile mills and dye houses as much as anyone else. As a result, they are seeking multifunctional products and developing forgiving processes in order to reduce costs and to market fabrics with long-term appeal to consumers. Textile enhancer Magnasoft SilQ was developed and patented by Momentive Performance Materials' laboratories in response to such market needs.

Magnasoft SilQ textile enhancer is part of our prestigious line of textile enhancers, which includes such world-known grades as Magnasoft SRS and Magnasoft DerMa NT. Magnasoft SilQ textile enhancer is a linear, non-reactive, high molecular weight quaternary aminosilicone polymer with the various components having been carefully engineered to meet strict performance requirements.

Magnasoft SilQ textile enhancer can deliver a luxuriously soft and flexible hand feel to most types of cellulosic, regenerated cellulosic and cellulosic blends of fabrics and garments. This typically is further enhanced by a deep, voluminous and smooth softness that is not usually associated with silicone materials.

Fabrics treated with Magnasoft SilQ textile enhancer typically are hydrophilic and, remarkably, retain hydrophilicity even after high temperature dry/cure conditions as well as on ageing of the fabric.

Though Magnasoft SilQ textile enhancer is easily dispersible in water in the presence

of certain emulsifiers, its affinity for the fiber surface is such that it largely remains on the fabric even after repeated home laundry cycles.

Emulsions of Magnasoft SilQ textile enhancer have exhibited outstanding shear stability and low yellowing at extremes of pH and temperature in tests conducted in our laboratories. As a result, Magnasoft SilQ textile enhancer may be applied onto fabrics using most types of finishing equipment, including high speed padding, kiss rolls, exhaustion, jet finishing and others.

### Key Features and Benefits

- Slippery, voluminous and in-depth softness on virtually all types of fabrics as opposed to a greasy hand feel
- Due to excellent exhaustibility and affinity with fibers, exhibits unique and unusually powerful softness effect at low use levels
- Quickly absorbs water and perspiration; minimal impact on the hydrophilic nature of cotton and cotton blends
- Fabrics and garments treated with Magnasoft SilQ textile enhancer remain hydrophilic on aging
- Provides stretch recovery with bouncy and drapable effect, particularly on knits
- Almost self-emulsifiable; can generate emulsions that possess high shear and pH stability (acid & alkaline)
- Exhibits durable softness to home laundry washes, particularly on cellulose based fabrics
- Causes virtually no yellowing of white and light shade fabrics
- Typically does not affect the shade of dark color fabrics

### Typical Physical Properties

Property	Unit	Value
Appearance	–	Light yellow liquid
Flash Point	°C	> 100
Viscosity at 25°C	CSt	15,000
Density at 25°C	gr/cm <sup>-3</sup>	0.980

The data values of typical physical properties should not be used as specifications.

## Potential Applications

Magnasoft SilQ textile enhancer is a textile softener that can deliver a rich range of advantages to virtually all types of knit and woven fabrics. Magnasoft SilQ textile enhancer can be particularly effective on cotton knits and woven fabrics where it provides slippery, voluminous and pliable hand-feel as well as quick water/perspiration absorption in addition to typical silicone softener effects.

Magnasoft SilQ textile enhancer is normally applied as a water emulsion. Because of its polar nature, Magnasoft SilQ textile enhancer is easily dispersed in water using emulsifiers in simple mixing devices and containers widely available throughout the industry. There is typically no need for homogenization or colloid milling to emulsify Magnasoft SilQ textile enhancer. Table 1 shows a typical guide formulation and procedure to prepare a 20% silicone actives emulsion of Magnasoft SilQ textile enhancer. If such emulsions are intended to be stored for extended periods, it is recommended that a biocide be added to retain sterility.

Emulsions of Magnasoft SilQ textile enhancer possess extraordinary shear stability in a wide pH range (3~12), at high temperatures and in the presence of salts in tests conducted in our laboratories. Therefore, Magnasoft SilQ textile enhancer may be applied under very demanding conditions such as high speed continuous pad-bath finishing, jet finishing, foam and spraying finishing, processes that are typically designed for mass textile finishing potentially resulting in considerable costs savings to the textile mills.

Optimum dose levels of Magnasoft SilQ textile enhancer are subject to type of fabric and level of softness required, but 10~30 g/l (for 0.2~0.6% silicone pick-up) of 20% silicone actives emulsion is typically recommended.

Magnasoft SilQ textile enhancer may be combined, blended or formulated with a broad range of cationic and/or nonionic textile auxiliaries as well as other silicone materials, so as to differentiate the performance. Typically, these may include organic quats, amphoteric (betaines) or imidazolines, alkylolamine ester, fatty acid amide, ethoxylated/propoxylated surfactants, polyethylene wax emulsions, starch, other water soluble or emulsifiable polymers, amino silicones, amino/polyether silicones or other silicone emulsions. Such formulations may be developed for use in specific applications such as textile finishing, spinfinishes, thread lubrication etc.

**Table 1: Guide Formulation for Microemulsion of Magnasoft SilQ Textile Enhancer†**

Ingredients	20% Silicone Active Formulation [weight%]	Function	Notes
Magnasoft SilQ textile enhancer	23.5	Silicone Active	
Tridecyl Alcohol 6EO Ethoxylate	4.2	Emulsifier	HLB 11.5
Tridecyl Alcohol 12EO Ethoxylate	8.8	Emulsifier	HLB 14.6
Glacial Acetic Acid	0.3		
Sodium Acetate	0.3		
Water	62.9		

**Procedure**

1. Charge Magnasoft SilQ textile enhancer and emulsifiers. Mix well till fully homogeneous
2. Dissolve sodium acetate and acetic acid into water
3. Slowly add the water solution to silicone/emulsifiers blend while mixing. Avoid stirring too much air into the mixture
4. Filter into the containers

Magnasoft SilQ MB.indd\_img\_1.JPG

Magnasoft SilQ MB.indd\_img\_2.JPG

**High Temperature Stability at Acidic and Alkaline****pH Stability at 80°C**

Bath pH	Emulsion of Magnasoft SilQ textile enhancer (20% actives)	Amino microemulsion (15% actives)	Benchmark I	Benchmark II
pH 3	Clear & Stable	Unstable, Silicone oil droplets	Clear & Stable	Clear & Stable
pH 7	Clear & Stable	Unstable, Silicone oil droplets	Clear & Stable	Clear & Stable
pH 10	Clear & Stable	Unstable, Silicone oil droplets	Unstable, Some silicone oil droplets	Unstable, Some silicone oil droplets
pH 12	Clear & Stable	Unstable, Many Silicone oil droplets	Unstable, silicone oil droplets	Unstable, Many silicone oil droplets

### Patent Status

Standard copy to come

### Product Safety, Handling and Storage

Standard copy to come

### Limitations

Standard copy to come

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

#### Americas

+1 800 295 2392

Toll free\*

+704 805 6946

Direct Number

#### Latin America

##### Brazil

+55 11 4534 9650

Direct Number

#### EMEAI- Europe, Middle East, Africa & India

##### Europe

+390510924300

Direct number

#### ASIA PACIFIC

##### China

800 820 0202

Toll free

+86 21 3860 4892

*All American countries	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	Direct number <b>Japan</b> +81 3 5544 3111 Direct number
		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement

contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*Magnasoft™ é uma marca registrada da Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.